



MSR FT

SILYL MODIFIED POLYMER

KEY BENEFITS

- High Grab
- Excellent UV-resistance
- Long open time

PRODUCT DESCRIPTION

Bostik MSR Fast Tack is a 1-component, permanently elastic, fast curing construction adhesive, specifically developed for bonding and sealing applications in the yacht and boat building industry. Bostik MSR FT has been tested and certified to the International Maritime Organisation Fire Test Procedures for Surface Flammability, following FTP 2010 requirements. Apart from that MSR FT has been approved for use in flooring applications.

APPLICATIONS

- Direct bonding of screens and windows (Substrates Glass, PMMA or PC)
- Bonding push borders
- Bonding and sealing deck fittings
- Bonding deck hatches, portholes and bollards
- Bonding deck fittings
- Bonding deck/hull connections

FEATURES

- High green strength; Reduced or no clamping time necessary
- Good adhesion on commonly used materials without the use of a primer e.g. ceramic coated glass, PMMA and PC
- Paint compatible with most industrial paint and lacquer systems, both alkyd resin- and dispersion based. (due to the numerous different types of industrial paint a compatibility test is recommended before use, please consult with the paint supplier).

METHOD OF USE

Bostik MSR FT can easily be extruded with a hand or air pressure gun at temperatures between +5°C and +35°C. In bonding applications, the substrates need to be assembled within 30 minutes (at 23°C/50% R.H.) of applying MSR FT. A minimum adhesive thickness of 2 mm is recommended. Cleaning tools or removing uncured residue of MSR FT can be done with a clean colourless cloth, wetted with Bostik Liquid 1 or Bostik Cleaner E.

TECHNICAL DATA

Basic Material		Silyl Modified Polymer (SMP)
Specific Gravity	[g/ml]	ca. 1.5
Skin Forming Time 23°C/50% R.H.	[min]	ca. 20
Curing Mechanism		Moisture
Curing Speed after 24hrs 23°C/50% R.H.	[mm]	ca. 3
Shore A Hardness		ca. 60
Colour		Black
Volume Change	[%]	< 3
Tensile Stress At 100% ISO 37 (dumbbells)	[MPa]	ca. 2.4
Tensile Stress At Break ISO 37 (dumbbells)	[MPa]	ca. 2.9
Elongation At Break ISO 37 (dumbbells)	[%]	ca. 200
Shear Stress ISO 4587	[MPa]	ca. 2.3
Temperature Resistance	[°C]	-40 to +110 *
Application Temperature	[°C]	+ 5 to +40
UV And Weather Resistance		Excellent

* = 10 Cycles of 7 hours at 110°C followed by 17 hours at 23°C/50%RH

PACKAGING DESCRIPTION

290ml cartridge

ADHESION

Bostik MSR FT adheres well without primer on most clean, dry, dust and grease free substrates. Due to the wide variety of substrates available Bostik recommends adhesion testing prior to use.

Windows with a ceramic coating/frit on the glass surface should be thoroughly cleaned with Bostik Cleaner I prior to the application of MSR FT. When no ceramic coating/frit is present, or when the coating provides insufficient protection against UV-radiation, the use of Bostik Prep G plus is mandatory to provide adequate UV-protection of the adhesive bond-line.

No adhesion will be obtained on untreated polyethylene, polypropylene and Teflon.

Where, due to great thermal or physical loads, high adhesion demands are required, the use of Bostik Prep CS or Prep M is recommended, especially under wet conditions. Prep CS and Prep M degrease and prepare the surface of the substrate for bonding in one single step.

On plain, untreated wooden surfaces and porous substrates, Bostik Prep P is recommended to prepare the surface for bonding. For more details on Prep G Plus, Prep CS, Prep M and Prep P consult the concerned Technical Data Sheet.


STORAGE STABILITY

Bostik MSR Fast Tack can be stored for 18 months in cartridge and 12 months in sausage, in original unopened container in a dry place at temperatures between +5°C and +30°C.

FURTHER INFORMATION

The following publication is available on request:

- Material Safety Data Sheets (MSDS).
- Certificate GL elastomeric adhesive, class A and B
- This product has been tested and certified to the International Maritime Organisation (IMO) Fire Test Procedures for surface flammability. Not only are the fire retardant properties excellent, but also the production quality is ensured and regularly audited by Bureau Veritas, which guarantees the constant quality Bostik stands for.



DISCLAIMER

Bostik provides this Technical Data Sheet ("TDS") for descriptive and informational purposes only. It does not constitute a warranty, a contract, or a substitute for expert or professional advice. Please refer to the local product Safety Data Sheet for health and safety information. The statements, technical information, data, and recommendations contained in this TDS are provided "AS IS" without any warranties or guarantees of any kind. They represent typical results for the products based solely on Bostik's research. Since the conditions and methods of use of the products are beyond our

Bostik SA
51, Esplanade du Général de Gaulle,
92800 Puteaux – France
Smart help: +33 149 007 502
www.bostik.com

All advice, recommendations, figures and safety regulations provided are based on careful investigations, as well as the current state of our experience and are without obligation. Although the documentation has been compiled with the greatest care, we do not accept any liability for inaccuracies, mistakes, typesetting or printing errors. We reserve the right to modify the respective product if we deem it necessary. Since the design, the quality of the substrate and the processing conditions are beyond our assessment, no liability can be accepted for work performed on the basis of this documentation. We therefore advise you to carry out practical tests on site yourself. Our general Terms and Conditions of Sale and Delivery apply to all our sales and deliveries.

control, Bostik expressly disclaims any and all liability for any damages of any kind that may result from the use of the products, the results obtained, or reliance on the information contained herein.