



BOSTIK

MSR BC

SILYL MODIFIED POLYMER

KEY BENEFITS

- Long open time
- Excellent adhesion
- Easy Tooling

PRODUCT DESCRIPTION

Bostik MSR Bedding Compound is a 1-component, permanently elastic adhesive/sealant suitable for use in marine bedding applications.

Bostik MSR Bedding Compound has been tested and certified to the International Maritime Organisation Fire Test Procedures for Surface Flammability, following FTP 2010 requirements. Apart from that MSR Bedding Compound has been approved for use in flooring applications.

Bostik MSR Bedding Compound has excellent resistance to UV, weather and temperature, and exhibits excellent adhesion performance on a wide variety of substrates (minimal or no pre-treatment necessary)

APPLICATIONS

- Bostik MSR Bedding Compound is designed for bonding teak planks and artificial planks on wooden, steel, aluminium or polyester decks.
- Bostik MSR Bedding Compound is suitable for bonding/sealing waterproof plywood subdeck on a wooden, steel, aluminium or polyester subdeck.

FEATURES

- Solvent and isocyanate free
- Excellent UV-resistance and ageing properties; good resistance against fresh and salt water
- Sound and vibration dampening properties
- MED Certified by Bureau Veritas: IMO FTP code 2010

METHOD OF USE

For specific application instructions consult the Bostik instruction brochure "Application manual for bonding and caulking of teak decks"

Bostik MSR Bedding Compound can easily be extruded with a hand or air pressure gun at temperatures between +5°C and +35°C, it can also easily be spread with a trowel.

In bonding applications, the substrates need to be assembled within 45 minutes (at 23°C/50% R.H.) of applying MSR Bedding Compound. A minimum adhesive thickness of 2 mm is recommended.

In sealing applications, MSR Bedding Compound should be tooled or smoothed within 25 minutes (at 23°C/50% R.H.) using a spatula or putty knife, occasionally moistened with a soap solution. Ensure to avoid soap solution penetrating between joint surface and adhesive, as this will cause loss of adhesion. Cleaning tools or removing uncured residue of MSR Bedding Compound can be done with a clean colourless cloth, wetted with Bostik Liquid 1 or Bostik Cleaner E.

TECHNICAL DATA

Basic Material		Silyl Modified Polymer (SMP)
Specific Gravity	[g/ml]	ca. 1.3
Skin Forming Time	[min]	ca. 40
23°C/50% R.H.		
Curing Mechanism		Moisture
Curing Speed	[mm]	ca. 2
23°C/50% R.H.		
Shore A Hardness		ca. 32
Colour		White, Light grey, Black, Teak Brown
Volume Change	[%]	ca. < 3
Tensile Stress At 100%	[MPa]	ca. 1.0
ISO 37 (dumbbells)		
Tensile Stress At Break	[MPa]	ca. 1.9
ISO 37 (dumbbells)		
Elongation At Break	[%]	ca. 300
ISO 37 (dumbbells)		
Shear Stress	[MPa]	ca. 1.8
ISO 4587		
Temperature Resistance	[°C]	-40 to +110*
Application Temperature	[°C]	+ 5 to +40
UV And Weather Resistance		Excellent

* = 10 Cycles of 7 hours at 110°C followed by 17 hours at 23°C/50%RH.

PACKAGING DESCRIPTION

290ml cartridge
600ml sausage

ADHESION

Bostik MSR Bedding Compound adheres well without primer on most clean, dry, dust and grease free substrates. Due to the wide variety of substrates available Bostik recommends adhesion testing prior to use.

No adhesion on untreated polyethylene, polypropylene and Teflon.

Where, due to great thermal or physical loads, high adhesion demands are required, the use of Bostik Prep CS or Prep M (TF) is recommended, especially under wet conditions. Prep CS and Prep M (TF) degrease and prepare the surface of the substrate for bonding in one single step.

On plain, untreated wooden surfaces and porous substrates, Bostik Prep P is recommended to prepare the surface for bonding. For more details on Prep CS, Prep M (TF) and Prep P consult the concerned Technical Data Sheet.


STORAGE STABILITY

Bostik MSR Bedding Compound can be stored for 18 months in cartridge and 12 months in sausage, in the original, unopened container in a dry place at temperatures between +5°C and +30°C.

FURTHER INFORMATION

The following publication is available on request:

- Material Safety Data Sheets (MSDS).
- Certificate GL elastomeric adhesive, class A and B
- This product has been tested and certified to the International Maritime Organisation (IMO) Fire Test Procedures for surface flammability. Not only are the fire retardant properties excellent, but also the production quality is ensured and regularly audited by Bureau Veritas, which guarantees the constant quality Bostik stands for.



DISCLAIMER

Bostik provides this Technical Data Sheet ("TDS") for descriptive and informational purposes only. It does not constitute a warranty, a contract, or a substitute for expert or professional advice. Please refer to the local product Safety Data Sheet for health and safety information. The statements, technical information, data, and recommendations contained in this TDS are provided "AS IS" without any warranties or guarantees of any kind. They represent typical results for the products based solely on Bostik's research. Since the conditions and methods of use of the products are beyond our control, Bostik expressly disclaims any and all liability for any damages of any kind that may result from the use of the products, the results obtained, or reliance on the information contained herein.