



BOSTIK

PREP M (TF)

SURFACE PREPARATION

KEY BENEFITS

- One step surface pre-treatment
- Fast drying
- Easy to use

PRODUCT DESCRIPTION

Bostik Prep M (TF) is a one-step pre-treatment designed to improve the adhesion of most Bostik elastic bonding products on closed surface substrates.

APPLICATIONS

- Pre-treatment of aluminium, steel, copper and brass, powder-coated and lacquered metals
- Pre-treatment of polyester (GRP) substrates, ABS, PVC and other plastics/composites

METHOD OF USE

Substrates should be clean, dry, dust and grease-free. Prep M (TF) container should be kept closed until the moment of use. Do not use Prep M (TF) directly from the original container but pour as much Prep M (TF) into a clean glass or metal container as can be used within 30 minutes and immediately close the original container firmly. Do not return unused material to the original container. If necessary e.g. if heavily contaminated, substrates may first be cleaned with Cleaner I or Cleaner 14, allow cleaners to dry for 5 minutes before application of Prep M (TF).

Prep M (TF) should not be applied in thick layer or multiple layers. Apply using a clean, colourless lint free cloth dampened with Prep M (TF) and wipe the bonding surface. Allow to dry for at least 5 minutes before applying adhesive or sealant. Best results are obtained when the bonding/sealing is realised within 6 hours after application. Avoid contact with the cleaned, pre-treated surface, as this can lead to poor adhesion.

(Note: Prep M (TF) should not be applied to areas that require painting. If painting after sealant application is required, mask the area before application of Prep M (TF). Prep M (TF) residue can be removed from substrates with Cleaner I or Cleaner 14.)

TECHNICAL DATA

Specific Gravity	[g/ml]	ca. 0.8
Colour		Transparent
Physical Form		Low viscous liquid
Dry Content	[%]	ca. 8
Drying Time	[min]	ca. 5
	20°C/50% R.H.	
Flash Point	[°C]	ca. 9
	(Closed Cup)	
Application Temperature	[°C]	+5 to +30

PACKAGING DESCRIPTION

500ml can

STORAGE STABILITY

Prep M (TF) can be stored for up to 12 months in the unopened container in a dry area at temperatures between +5°C and +30°C. Once opened, Prep M (TF) can be used for a maximum of 2 weeks (container should be firmly closed when not in use).

FURTHER INFORMATION

The following publication is available on request:
- Material Safety Data Sheets (MSDS).

DISCLAIMER

Bostik provides this Technical Data Sheet ("TDS") for descriptive and informational purposes only. It does not constitute a warranty, a contract, or a substitute for expert or professional advice. Please refer to the local product Safety Data Sheet for health and safety information. The statements, technical information, data, and recommendations contained in this TDS are provided "AS IS" without any warranties or guarantees of any kind. They represent typical results for the products based solely on Bostik's research. Since the conditions and methods of use of the products are beyond our control, Bostik expressly disclaims any and all liability for any damages of any kind that may result from the use of the products, the results obtained, or reliance on the information contained herein.

Bostik SA
51, Esplanade du Général de Gaulle, 92800 Put-
eaux – France
Smart help: +33 149 007 502 www.bostik.com

All advice, recommendations, figures and safety regulations provided are based on careful investigations, as well as the current state of our experience and are without obligation. Although the documentation has been compiled with the greatest care, we do not accept any liability for inaccuracies, mistakes, typesetting or printing errors. We reserve the right to modify the respective product if we deem it necessary. Since the design, the quality of the substrate and the processing conditions are beyond our assessment, no liability can be accepted for work performed on the basis of this documentation. We therefore advise you to carry out practical tests on site yourself. Our general Terms and Conditions of Sale and Delivery apply to all our sales and deliveries.