



Den Braven

# Panelcleaner

Cleaner for panel bonding



## PRODUCT DESCRIPTION

Zwaluw Panelcleaner® is a de-greasing cleaner for non porous surfaces. Zwaluw Panelcleaner® is part of a panel bonding portfolio of Zwaluw Panelfix®, Zwaluw Paneltape, Zwaluw Panelcleaner® en Zwaluw Primer-PF®.

## APPLICATIONS

Zwaluw Panelcleaner® was developed for de-greasing and cleaning of panels and aluminium supports, use in combination with Zwaluw Panel Fix®.

## DIRECTION FOR USE

General information timber/aluminium frame work and panel work  
Minimum joint width between the panels: 6 mm  
Distances between frame parts depending on panel thickness: 400-650 mm  
Minimum width end frame lath: 70 mm  
Minimum width mid frame lath: 55 mm  
Minimum width connection frame: 7 0mm  
Minimum frame thickness: 19 mm  
Minimum ventilation space behind the panel: 20 mm

Pre-treatment frame work

Apply Zwaluw Primer-PF® in one opaque layer and allow to dry at least for 1 hour. Moisture content of the timber frame work

may not exceed 18%!

Application Spacer Tape

Apply Zwaluw Paneltape when Zwaluw Primer-PF® is fully cured (1 to 24 hours) in a vertical continuous line. Press firmly and cut with a sharp knife. Do not remove the release paper of the Zwaluw Paneltape.

Pre-treatment panel work

Use Zwaluw Panelcleaner® to clean the rear of the panel at the adhesion. Thoroughly clean by using two cloths.

Apply panel adhesion

Apply Zwaluw Panelfix® only with the supplied V-nozzle in a triangular shape with a width and height of 10 mm in a vertical continuous line next to the Zwaluw Paneltape.

Panel mounting

Remove the release paper of the Zwaluw Paneltape. Apply the panel within 10 minutes of removing the release paper. Once the panel touches the Zwaluw Paneltape no adjustments can be made. When the panel is mounted correctly, press firmly.

## TECHNICAL SPECIFICATIONS

Density	0,72 g/ml
Frost Resistance	Up to -15°C
Flash point	-14°C

These are typical values

## SURFACE PREPARATIONS AND FINISHING

Zwaluw Panelcleaner® removes any trace of grease and mild surface contamination, improving adhesion. When Zwaluw Panelcleaner® is evaporated the surface will cool down. This may result in condensation and moisture on the surface. We advise allowing the surface to dry for 10 minutes after cleaning before applying sealant or adhesive to the substrate. Replace the cleaning tissues regularly.

## SHELF LIFE

In unopened original packaging between +5°C and +25°C, shelf life till 12 months after production date, stored in a dry place.

## HEALTH & SAFETY

Product Safety Data Sheet must be read and understood before use. These are available on request and via our websites

## WARRANTY & GUARANTEE

Bostik warrants that its product complies, within its shelf life, to its specification.

## DISCLAIMER

All information in this document and in all our other publications (including electronic ones) is based on our current knowledge and experience and is the exclusive (intellectual) property of Bostik. No part of this document may be copied, shown to third parties, reproduced, communicated to the public or used in any other way without Bostik written consent. The technical information in this document serves as an indication and is non-exhaustive. Bostik is not liable for any damage, either directly or indirectly, due to (editorial) errors, incompleteness and/or incorrectness of this document. This includes, but is not limited to, incompleteness and/or incorrectness due to technological changes or any research conducted between the date of publication of this document and the date on which the product is acquired. Bostik reserves the right to amend the wording of this document. Bostik cannot be held liable for any damage, either directly or indirectly, due to the use of the product(s) depicted in this document. The user must read and understand the information in this document and other documents relating to the products prior to the use of the product. The user is responsible for performing all the requisite tests to make sure that the product is suitable for its intended use. We have no influence in what way the product is applied and/or any circumstances relating to events occurring during storage or transport and therefore we do not accept any liability for damage whatsoever. All deliveries are made exclusively in accordance with our general terms of conditions which have been filed at the Dutch Chamber of Commerce.