



Den Braven

# Repox® Fast

Fast curing 2-component elastic and paintable wood repair compound based on epoxy resins



## DIRECTION FOR USE

Suitable for small repairs from 2 mm up to 20 mm.

## TECHNICAL SPECIFICATIONS

Application Temperature		+2°C to +30°C
Density		1,30 g/ml
Frost Resistance		Up to -15°C
Temperature Resistance		-20°C to +80°C
Paintable	@ +23°C/50% RH	> 30 min
Sandable	@ 23°C/50% RH	> 15 min

These are typical values

## PRODUCT DESCRIPTION

Zwaluw RepoX® Fast is an extremely quick drying, permanently elastic, solvent free, 2-component wood repair system, for smaller repairs based on epoxy resin. Zwaluw RepoX® Fast comes with a COT report LAB12-0118-RAP and complies with the regulation according the COT quality description 04.20 Wood Repair Compound.

## KEY BENEFITS

- Apply out of the cartridge with a professional caulking gun
- Non shrinking, high flow resistance, moisture resistant
- Almost odourless
- Ready to use
- Sandable and paintable after 60 minutes
- No primer required
- For interior and exterior use

## APPLICATIONS

Zwaluw RepoX® Fast was specifically developed to repair nail and screw holes, knots and tears in longitudinal direction and other defects of wood. Suitable for small repairs with a minimum of 2-3mm to 15-20mm. For use on doors, window frames, stairs and sheet material such as chipboard, block board and plywood. Also as a repair compound for furniture. Suitable for interior and exterior use.

## LIMITATIONS

Not suitable for PE, PP, PC, PMMA, PTFE, soft plastics, neoprene and bituminous substrates, Can not be applied with an air pressure gun

## SURFACE PREPARATIONS AND FINISHING

Zwaluw RepoX® Fast does not require primer. The treatment area must be dry clean and free of oil. Remove loose parts and old peeling paint. Remove weathered, damaged and soft parts of the wood with a chisel leaving the healthy wood exposed. The place area of repair should be sharp angled. Never let the wood taper off. Apply Zwaluw RepoX® Fast at ambient temperatures of +2°C. By keeping the cartridge at +15°C the drying process will not be delayed.

## PAINTABILITY

Zwaluw RepoX® Fast can be sanded after 15-20 minutes and paintable after 30 minutes with water based and synthetic based paints. Zwaluw RepoX® Fast paintable with most paint systems. We recommend testing compatibility with paint prior to application.

## **CLEANING**

Uncured material and tools can be cleaned by using Zwaluw Cleaner. Cured material can only be mechanically removed. Hands can be cleaned with Zwaluw Wipes.

## **SHELF LIFE**

In unopened original packaging between +5°C and +25°C, shelf life till 12 months after production date, stored in a dry place.

## **HEALTH & SAFETY**

Product Safety Data Sheet must be read and understood before use. These are available on request and via our websites

## **WARRANTY & GUARANTEE**

Bostik warrants that its product complies, within its shelf life, to its specification.

## **DISCLAIMER**

All information in this document and in all our other publications (including electronic ones) is based on our current knowledge and experience and is the exclusive (intellectual) property of Bostik. No part of this document may be copied, shown to third parties, reproduced, communicated to the public or used in any other way without Bostik written consent. The technical information in this document serves as an indication and is non-exhaustive. Bostik is not liable for any damage, either directly or indirectly, due to (editorial) errors, incompleteness and/or incorrectness of this document. This includes, but is not limited to, incompleteness and/or incorrectness due to technological changes or any research conducted between the date of publication of this document and the date on which the product is acquired. Bostik reserves the right to amend the wording of this document. Bostik cannot be held liable for any damage, either directly or indirectly, due to the use of the product(s) depicted in this document. The user must read and understand the information in this document and other documents relating to the products prior to the use of the product. The user is responsible for performing all the requisite tests to make sure that the product is suitable for its intended use. We have no influence in what way the product is applied and/or any circumstances relating to events occurring during storage or transport and therefore we do not accept any liability for damage whatsoever. All deliveries are made exclusively in accordance with our general terms of conditions which have been filed at the Dutch Chamber of Commerce.