

Technical Data Sheet

SX MIGHTY STRENGTH FAST ACTING CYANOACRYLATE ACTIVATOR ACTIVATOR FOR CYANOACRYLATES



PRODUCT DESCRIPTION

A low viscosity solvent based cyanoacrylate adhesive activator which is fast acting.

KEY BENEFITS

- Fast acting

APPLICATIONS

To accelerate the curing speed of SX Superglue cyanoacrylate adhesive used primarily on wood mitre joints or on porous, acidic or difficult to bond surfaces.

DIRECTION FOR USE

Shake can well before use. Holding the can approximately 20 cm away, spray onto one of the surfaces to be bonded for no longer than 1 second. Allow solvent to evaporate. Apply SX Superglue Adhesive to the other surface and assemble parts accurately holding for approximately 10 seconds. The bond will be instant.

Excessive use may cause discolouration on PVCu surfaces.

TECHNICAL SPECIFICATIONS

Application Temperature	+5°C to +30°C
Curing Time	Very fast - usually < 10 secs

SURFACE PREPARATIONS AND FINISHING

Surfaces to be bonded must be clean, dry and free from grease. A patch test on a hidden area is recommended.

PACKAGING DESCRIPTION

For product specifications, please refer to the Product Detail Page

COLOUR

Colourless

SHELF LIFE

In unopened original packaging between +5°C and +25°C, shelf life is up to 12 months from production date, stored in a dry place

HEALTH & SAFETY

Product Safety Data Sheet must be read and understood before use. These are available on request and via our websites

WARRANTY & GUARANTEE

Siroflex warrants that its product complies, within its shelf life, to its specification.

DISCLAIMER

All information in this document and in all our other publications (including electronic ones) is based on our current knowledge and experience and is the exclusive (intellectual) property of Bostik. No part of this document may be copied, shown to third parties, reproduced, communicated to the public or used in any other way without Bostik written consent. The technical information in this document serves as an indication and is non-exhaustive. Bostik is not liable for any damage, either directly or indirectly, due to (editorial) errors, incompleteness and/or incorrectness of this document. This includes, but is not limited to, incompleteness and/or incorrectness due to technological changes or any research conducted between the date of publication of this document and the date on which the product is acquired. Bostik reserves the right to amend the wording of this document. Bostik cannot be held liable for any damage, either directly or indirectly, due to the use of the product(s) depicted in this document. The user must read and understand the information in this document and other documents relating to the products prior to the use of the product. The user is responsible for performing all the requisite tests to make sure that the

product is suitable for its intended use. We have no influence in what way the product is applied and/or any circumstances relating to events occurring during storage or transport and therefore we do not accept any liability for damage whatsoever. All deliveries are made exclusively in accordance with our general terms of conditions which have been filed at the Dutch Chamber of Commerce.

