

Technical Data Sheet

SX DECORATORS ANTI-CRACK PAINTABLE CAULK ACRYLIC UNIQUE ACRYLIC SEALANT WHICH PREVENTS CRAZE CRACKING WITH MOST PAINTS



PRODUCT DESCRIPTION

A high quality acrylic caulk which is paintable and has the unique benefit of preventing craze cracking and discolouration of paint when painted with most water based and synthetic paints. This product adheres to most surfaces perfectly without the use of a primer, even slightly damp substrates. This product has very low odour, is easy to apply and is not corrosive towards metals.

KEY BENEFITS

- Paintable with water based and synthetic paints
- Reduces craze cracking and discolouration of the paint
- Perfect adhesion without the use of primer on most, even slightly damp substrates
- For interior and exterior use (only use in good, dry weather conditions and it must stay dry for at least 5 hours after application)
- Almost odourless
- Easy to apply and clean
- Non corrosive towards metals

APPLICATIONS

Specifically developed for sealing connection joints between stairs, walls, ceilings, skirtings, windowsills, wooden and metal window frames, concrete and brickwork and for filling cracks, screw and nail holes in walls and ceilings of wood, plaster, gypsum, brickwork and concrete. For exterior applications only.

DIRECTION FOR USE

Cut the cartridge seal and screw on the nozzle which

should be cut to the required size. Using a skeleton gun, apply the product into the gap or joint ensuring a good solid fill. If required, place masking tape along edges removing within 10 minutes of application. Always tool using a spatula or stick wetted with water within 10 minutes of application.

100% Modulus	DIN 53504 S2	0,70 N/mm ²
Application Temperature		+5°C to +40°C
Base		Acrylic dispersion
Application Rate	@ Ø3 mm/4 bar	260 g/min
Curing Time	@ +23°C/50% RH	2 mm/24 hrs
Density	ISO 1183-1	1,66 g/ml
Elongation At Break	DIN 53505/ ISO 868	200%
Flow	ISO 7390	< 2 mm
Frost Resistance		Up to -15°C
Joint Movement		7,5%
Shore A Hardness	DIN 53505 / ISO 868	40
Skin Formation	DBTM 16	10 minutes @ +23°C/50% RH
Temperature Resistance		-20°C to +75°C
Tensile Strength	DIN 53504	0,70 N/mm ²

LIMITATIONS

- Not suitable for continuous exposure to water,
- Not suitable for PE, PP, PC, PMMA, PTFE, soft plastics, neoprene and bituminous substrates,
- *Exterior applications only in good, dry weather, and it must stay dry for at least 5 hours after application

SURFACE PREPARATIONS AND FINISHING

Ensure surfaces are clean and grease free

PAINTABILITY

Paintable with most water based and synthetic paints when fully dry. We recommend testing compatibility with paint prior to application.

CLEANING

Uncured sealant can be removed with water.

SHELF LIFE

In unopened original packaging between +5°C and +25°C, shelf life is up to 18 months from production date, stored in a dry place.

BOSTIK CERTIFICATIONS

- A+ French VOC Regulation
- Emission EC1 Plus – very low emission
- EN 15651-1: F-EXT-INT 7.5P



HEALTH & SAFETY

Product Safety Data Sheet must be read and understood before use. These are available on request and via our websites

LIMITED WARRANTY

Siroflex warrants that its product complies, within its shelf life, to its specification.

DISCLAIMER

All information in this document and in all our other publications (including electronic ones) is based on our current knowledge and experience and is the exclusive (intellectual) property of Bostik. No part of this document may be copied, shown to third parties, reproduced, communicated to the public or used in any other way without Bostik written consent. The technical information in this document serves as an indication and is non-exhaustive. Bostik is not liable for any damage, either directly or indirectly, due to (editorial) errors, incompleteness and/or incorrectness of this document. This includes, but is not limited to, incompleteness and/or incorrectness due to technological changes or any research conducted between the date of publication of this document and the date on which the product is acquired. Bostik reserves the right to amend the wording of this document. Bostik cannot be held liable for any damage, either directly or indirectly, due to the use of the product(s) depicted in this document. The user must read and understand the information in this document and other documents relating to the products prior to the use of the product. The user is responsible for performing all the requisite tests to make sure that the product is suitable for its intended use. We have no influence in what way the product is applied and/or any circumstances relating to events occurring during storage or transport and therefore we do not accept any liability for damage whatsoever. All deliveries are made exclusively in accordance with our general terms of conditions which have been filed at the Dutch Chamber of Commerce.

