



Cempolatex 1 Pack

A CEMENT BASED LATEX SUB-FLOOR SMOOTHING COMPOUND

Date: 3 October 2019

Fact Sheet No.: TDS00179

YOUR SMART ADVANTAGES

- Flexible and rapid setting
- Suitable for use with underfloor heating
- Protein free formulation

USES

Bostik Cempolatex 1 Pack is a latex modified, protein-free self-smoothing subfloor compound. It has excellent bonding properties and good flexibility that will accommodate the movement of closely fitted suspended flooring. It is easy to apply and has good flow.

Bostik Cempolatex 1 Pack is suitable for interior use. It is suitable for use with warm water underfloor heating systems provided a surface temperature of 27°C is not exceeded. The heating must be switched off for at least 48 hours before and after application. Bostik Cempolatex 1 Pack is ideal for smoothing and levelling properly prepared concrete, sand/cement screeds, quarry tiles, rigid timber floors, stone, brick and terrazzo floors, asphalt floors. Bostik Cempolatex 1 Pack may also be used as a floor topping/concrete re-surface with the addition of Bostik SBR, and for patching up to 100mm thickness. Bostik Cempolatex 1 Pack is suitable for warm water underfloor heating systems when used as a levelling compound.

PRODUCT CHARACTERISTICS

Form	Dry, free flowing powder
Colour	Grey
Composition	Protein-free, polymer modified Portland cement based compound
Odour	Low
Specific Gravity	1.6 approx.
Solids Content	100%

Product Codes	30812516 25kg
Storage/Shelf Life	Store for up to 6 months from date of manufacture when stored in the original, unopened packaging, clear of the ground, under cool, dry conditions within the temperature range of +5°C to +30°C. Protect from frost and excessive draughts.

TYPICAL PERFORMANCE DATA (approx.)

Application Temperature	5°C to 25°C
Application Thickness	3-5mm
Coverage	Approx. 5m ² at 3mm thickness Approx. 3m ² at 5mm thickness
Working Time	Approx. 20 minutes at 20°C
Drying Times	Foot traffic: 2 to 4 hours approx. at 20°C To lay floor covering: 16 hours approx. at 20°C Re-surfacing: 4 weeks before protective coating Note: Drying/covering times will be extended at lower temperatures
Compressive Strength	≥ 16 N/mm ² at 28 days

DIRECTIONS FOR USE

IMPORTANT: Before using Bostik Cempolatex 1 Pack refer to the relevant Health & Safety Data Sheet, available at www.bostik.com/uk

All phases of installation should comply with the latest editions of:

BS CP102 Code of Practice for protection of buildings against water from the ground.

BS 5325 Code of Practice for installation of textile floor coverings.
BS 8203 Code of Practice for installation of resilient floor coverings.

PREPARATION

1. Use personal protective equipment as required.
2. Ensure the floor and air temperature remains above 5°C throughout the application and during drying.
3. Surface preparation is essential even on new concrete or existing levelling compounds.
4. Ensure the subfloor is sound, clean, dry, free from surface laitance and contamination such as grease or thick layers of old adhesive residue or bitumen.
5. Ensure there is an effective damp-proof membrane that conforms to BS 8203:1987.
6. Fill any deep depressions (20 - 25 mm) using a mixture of Bostik Cempolatex 1 Pack and sharp sand. Trowel to a smooth finish. Allow 24 hours before proceeding, 48 to 72 hours if more than 50% of the floor is patched.
7. Switch off underfloor heating at least 48 hours before application and keep switched off for at least 48 hours after to ensure complete drying has occurred.

Wooden Floors:

8. Bostik Cempolatex 1 Pack can be applied over mosaic and wood blocks directly bonded to solid floors when there is an effective damp-proof membrane in or beneath the sub-floor.
9. Bostik Cempolatex 1 Pack is suitable for use on stiff suspended floors constructed of chipboard, plywood or tongue and groove boards provided there is adequate ventilation under the floor.
10. Do not use on floors with a flexible surface, e.g. plain edge boards
11. Do not use on boarded floors where joists are fixed directly to concrete because of lack of ventilation and consequent risk of decay.

PRIMING

12. Prime very porous surfaces or extremely dry surfaces with Bostik Cempolay Universal Primer diluted with 2 parts water. Allow to dry before applying Bostik Cempolatex 1 Pack.
13. Prime non-porous surfaces with undiluted Bostik Universal Primer and apply Bostik Cempolatex 1 Pack.

MIXING RATIO

Levelling compound:

14. 25 kg Bostik Cempolatex 1 Pack to 5 litres clean, cold water.

Filling compound for depressions 20 - 25mm:

15. 25 kg Bostik Cempolatex 1 Pack to 5 litres water to 25kg sharp, dry sand.

Floor topping & patching compound for depressions 25-100 mm deep:

16. 25 kg Bostik Cempolatex 1 Pack to 3.5 litres to 1.5 litres Bostik SBR to 25 kg sharp, dry sand.

Asphalt and adhesive contaminated surfaces:

17. 25 kg Bostik Cempolatex 1 Pack to 3.5 litres water to 1.5 litres Bostik SBR.

MIXING

18. Slowly add Bostik Cempolatex 1 Pack to clean, cold water according to application ratios above.
19. Stir continuously until a smooth, homogenous paste is attained using an electric stirrer or electric drill with paddle.
20. Do not mix more compound than you can use in approximately 20 minutes.
21. Do not re-temper or add water.
22. When adding sand always add after gauging the powder.

APPLICATION

Flooring compound:

23. Apply a thin scrape coat with a plasterer's trowel to difficult surfaces such as quarry tiles. Not recommended for general application use.
24. Immediately pour and spread the rest of the mix on the subfloor to a minimum of 3 mm thickness and a maximum thickness of 5 mm.
25. Leave for approximately 16 hours before applying floor covering. Discard mix if it starts to gel.
26. Protect the surface from damage prior to laying a floor covering.

Filling compound:

27. For depressions 20 - 25 mm deep add sharp sand. See mix ratios. Trowel to a smooth finish.
28. If 50% or more of the area is patched leave for 48 to 72 hours before proceeding.

Patching compound:

29. For depressions 25 - 100 mm deep modify mix with Bostik Cementone SBR. See mix ratios.
30. Prime area to be patched with Bostik Universal Primer diluted in the ratio 1 part SBR to 2 parts water. Brush in well.
31. Allow to dry for approx. 1 hour.
32. Pack the hole with 10 - 20mm aggregate (pea gravel) leaving a 5mm gap at the surface.
33. Pour the SBR modified Bostik Cempolatex compound into the aggregate until all the voids are filled just covering the aggregate.
34. Allow to set for approx. 4 hours.
35. Finish by levelling off with a further layer of SBR modified Bostik Cempolatex One Pack.

Asphalt and sub-floors contaminated with sound adhesive residue:

36. Modify the mix with Bostik SBR. See Mixing Ratio section.

Floor topping on concrete or screed surfaces:

37. Modify mix with Bostik SBR. See Mixing Ratio section.
38. Prime area with Bostik Universal Primer diluted in the ratio 1 part Bostik Universal Primer to 2 parts water. Brush in well.
39. Allow to dry for approx. 1 hour.
40. Apply the SBR modified Bostik Cempolatex 1 Pack compound and allow to dry. Protect from damage.

CLEANING

41. Clean tools and equipment immediately after use with soapy water.
42. Do not allow to cure. Once cured, can only be removed mechanically.

PRECAUTIONS IN USE

For any application not covered please contact Technical Services on +44 (0)1785 272625 or visit www.bostik.com/uk for advice.

Recommendations and suggestions are for guidance only, since conditions of use are completely beyond our control.

For health and safety instruction, first aid measures and spillage and disposal instructions, see separate Health and Safety Data Sheet for Bostik Cempolatex 1 Pack available at www.bostik.com/uk

BOSTIK HOTLINE

Smart help +44 (0) 1785 272625



**CONSTRUCTION PRODUCT REGULATION
DECLARATION OF PERFORMANCE**

No.:TDS00179

Product Description: **BOSTIK CEMPOLATEX ONE PACK 25 kg**
Product Code: **5011734036659**
Intended Use: **Cementitious Screed Material**
Manufacturer: **Bostik Ltd**
Contact Address: **Common Road
Stafford
ST16 3EH**
System of Assessment: **System 4**
Harmonised Standard: **EN 13813:2002**
Notified Body:
Declared Performance: **CT-C16-F6**

Essential Characteristics	Performance	Harmonised technical specification
Reaction to Fire	F	EN 13813:2002
Compressive strength	≥ 16 N/mm²	
Flexural Strength	≥ 6 N/mm²	

The performance of the Bostik Cempolatex One Pack 5011734036659 is in conformity with the declared performance shown in the table above.

This declaration of performance is issued under the sole responsibility of Bostik Ltd.

Signed for and on behalf of Bostik Ltd by:

Name: Alison Jamieson

Function: S.H.E.Q. Manager

Signature: 

Date: May 2014

This disclaimer is issued by Bostik Limited ("the Company") and applies to the use of any products supplied by the Company ("the Products") displayed on this Technical Data Sheet ("TDS"). Please read this disclaimer carefully before using any of the Products. Using this TDS and/or the Product constitutes your acceptance of this disclaimer. Its contents shall prevail over any directions of use and any disclaimer and/or exclusion or limitation of liability of the Company which may appear on the packaging of the Products.

This disclaimer sets out the entire financial liability of the Company (including any liability for the acts or omissions of its employees, agents and sub-contractors) to any user of the Products ("Product User") in respect of any use made or resale by the Product User, of any of the Products in this TDS.

This disclaimer does not affect the Company's liability for death or personal injury arising from the Company's negligence in respect of the Products, nor its liability for fraud, or fraudulent misrepresentation, nor any other liability which cannot be excluded or limited under applicable law.

The Company's total liability however arising and whether caused by tort (including negligence and breach of statutory duty), breach of contract or otherwise, arising in connection with the use made or resale by the Product User of any of the Products in this TDS shall be limited to the price paid for the Product by the Product User.

The Company shall not be liable to the Product User for any pure economic loss, loss of profit, loss of business, depletion of goodwill or otherwise, in each case whether direct, indirect or consequential, or any claims (including in respect of personal injury insofar as not caused by the Company's negligence) for consequential compensation whatsoever (howsoever caused) which arise out of or in connection with the use made or resale by the Product User of any of the Products in this TDS.

The Company shall not be liable to the Product User in relation to any loss for any use which is inappropriate or use which is otherwise than in accordance with the relevant instructions for use of the Products in this TDS or on the Product. Product Users are advised to confirm the suitability of the Products by their own tests.

This TDS covers just one of a large range of products supplied by the Company.

Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This TDS supersedes all previous TDSs relating to the Products, and users of it must ensure that it is the current issue. Destroy all previous TDS, and if in any doubt, contact the Company, quoting the code number in the top right hand corner on the front of this document.

Sales	Tel: 0844 371 1192	Fax: 01785 241818	customer.service@bostik.com
Technical Advice	Tel: 0844 371 1197	Fax: 01785 272867	technical.service@bostik.com
Safety Data Sheets	Tel: 01785 272625	Fax: 01785 212962	sds.box-eu@bostik.com