



1040 FIBER QUICK

TECHNICAL DATASHEET

Version: 2021-10-21

PRODUCT DESCRIPTION

Bostik Fiber Quick is cement based, fibre reinforced, self-levelling, pumpable, levelling compound for various subfloors like concrete, shipboard etc... The material requires a light mechanical smoothing with a toothed trowel to achieve a surface flat and smooth enough for floor covering.

AREA OF USAGE

Bostik Fiber Quick is suitable as a base for carpets like linoleum, PVC and rubber as well as for wooden floors, tiles and similar material in houses, bathrooms, offices, hospitals, schools and nurseries. Fiber is well suitable for embedding electrical and waterborne under-floor heating. Fiber Quick can also be used for floating floor constructions in dry areas. Usually, the final surface does not need any further treatment such as grinding or fine screeding. Recommended thickness is 4-30 mm. Does not contain casein.

WORKING INSTRUCTION


[iplus FieldValue='Instruction for use'/]

SAFETY

The product contains cement and can cause irritation. Avoid inhaling dust and use facial protection. Should the product get into your eyes, rinse immediately with water for 15 minutes and seek medical help. For further information, please see material safety data sheet.

CONTACT US

TEL +46 (0)42-19 50 00
info.se@bostik.com



TECHNICAL DATA

Binder	Special cement blend
Ballast	Natural sand, 0.5 mm max.
Thickness	4-30 mm
Pot life	20 minutes
Material consumption	1.65 kg per m ² and mm
Water demand	20 weight%, 0.20 liter per kg of screed
Flow (EN 12706)	150-160 mm
Application temperature	+10°C +25°C
Compression strength	30 MPa
Adhesion to subfloor	> 0.5 MPa
Shrinkage, 28 days	< 0,5 .
Reaction to fire	A2fl-s1 (EN 13501-1)
Cleaning	Immediately with water
Package size	25 kg bag
Storage	6 months in a dry, cool environment and unopened package

CONTACT US

TEL +46 (0)42-19 50 00

info.se@bostik.com

