

Laboratory for Fire Safety

Classification of reaction to fire in accordance with EN_13501-1:2018 of Bostik Paneltack HM adhesive bonding system for Cembrit Patina fiber cement panel

Classification report

Report number Y 2424-4E-RA-001 dated 25 October 2021



Laboratory for Fire Safety

Classification of reaction to fire in accordance with EN_13501-1:2018 of Bostik Paneltack HM adhesive bonding system for Cembrit Patina fiber cement panel

Classification report

Client Bostik Benelux B.V. Denariusstraat 11 4903 RC Oosterhout The Netherlands Issued by Peutz bv Lindenlaan 41 NL-6584 AC Molenhoek Postbus 66 NL-6585 ZH Mook The Netherlands



Notified body no. NB 2264

Product name Bostik Paneltack HM adhesive bonding system for Cembrit Patina fiber cement panel

Y 2424-4E-RA-001
25 October 2021
HL/NvD//Y 2424-4E-RA-001
ing. H.H.A. Leenders
ing. N.F. van Dijk
+31 858 228 636
n.vandijk@peutz.nl

This classification report consists of 12 pages and may only be used or reproduced in its entirety. This document is the original version and written in English.

peutz bv, postbus 66, 6585 zh mook, +31 85 822 86 00, mook@peutz.nl, www.peutz.nl kvk 12028033, opdrachten volgens DNR 2011, lid NLingenieurs, btw NL.004933837B01, ISO-9001:2015

mook - zoetermeer - groningen - düsseldorf - dortmund - berlijn - nürnberg - leuven - parijs - lyon



Table of contents

1	Introduction	4
2	Product description	5
2.1	General	5
2.2	Harmonised product standard	5
2.3	Product identification	5
3	Reports and results in support of this classification	9
3.1	Reports	9
3.2	Results	9
3.3	Classification criteria	10
4	Classification and field of application	11
4.1	Reference of classification	11
4.2	Classification	11
4.3	Field of application	11
5	Limitations	1 2

Y 2424-4E-RA-001 /AF103BE9/ HARML



1 Introduction

On behalf of Bostik Benelux B.V. an investigation was performed with respect to the reaction to fire properties of Bostik Paneltack HM adhesive bonding system for Cembrit Patina fiber cement panel.

This classification report defines the reaction to fire classification of the product in accordance with the procedures described in EN 13501-1: 2018.



For this type of measurements the Laboratory for Fire safety has been accredited by the Dutch "Raad voor Accreditatie" (RvA).

The RvA is member of EA MLA (**EA MLA**: **E**uropean **A**ccreditation Organisation **M**ulti**L**ateral **A**greement: http://www.european-accreditation.org).

EA: "Certificates and reports issued by bodies accredited by MLA and MRA members are considered to have the same degree of credibility, and are accepted in MLA and MRA countries."



² Product description

2.1 General

The information in this chapter is based on information provided by the client.

The product investigated is Bostik Paneltack HM, an adhesive bonding system for Cembrit fiber cement panels, hereinafter also called 'the product'. The intended application is adhesives for the fixing of façade panels.

2.2 Harmonised product standard

According to the client there was no harmonised European product for the Paneltack HM adhesive bonding system at the time the tests were conducted and this report was drawn up. Because the investigation concerns the reaction to fire properties of the paneltack adhesive bonding system in combination with Cembrit Patina, the reaction to fire investigation is based on 'mounting and fixing provisions' from the product standard for flat fibre cement panels EN 12467:2012+A2:2018.

2.3 Product identification

The most important parameters for identifying the product are summarized in Tables 2.1 and 2.2 below.

Product	Bostik Paneltack HM adhesive bonding system for Cembrit Panels
Bostik Paneltack HM adhesive bonding system	
Date of sample arrival:	04-06-2021
Name of the manufacturer:	Bostik Benelux B.V.
Sampling done by:	W. Treffers
Sampling date:	02-06-2021
Identification of samples:	Table 2.2
Cembrit Patina fibre cement panel	
Date of sample arrival:	17-06-2021
Name of the manufacturer:	Cembrit BV, Vonderweg 7, 7468 DC ENTER
Sampling done by:	M. van der Most
Sampling date:	15-06-2021
Identification of samples:	Table 2.2

t2.1 General information of product to be tested



t2.2 Additional information of product to be tested

Product	Bostik Paneltack HM adhesive bonding system for Cembrit Panels
Type of product	Adhesive bonding system for the fixing of cladding panels for façade cladding
Description	The adhesive bonding system consists of:
	 – 1: Pretreatment for cladding panel: Bostik Primer Q
	 – 2: Pretreatment for support construction: Bostik Primer SX Black
	– 3: Bostik Foamtape
	– 4: Bostik Paneltack HM
	– 5: Façade panel

Paneltack HM		
Type of product	Bostik Paneltack HM (High Modulus) is a moisture-curing, elastic adhesive with high modulus based on SMP ((Silyl Modified Polymers), specially developed for bonding fibre-cement boards, natural stone and aluminium composite cladding panels.	Portik
Application	Applied on each vertical profile of the subframe as one uninterrupted bead, 1 hour	
	after pre-treatment with the primer	PANEL
Manufacturer	Bostik Benelux B.V., The Netherlands	
Product / EAN code	30132201	ADMENNE TUASTICHER KEERE FER ASSEADENMANTER GEVELPELART - PANNELAUDE FACADE PANEL - FASSADENDLATTE
Batch no.	LOT. FA21215563 BB. 08/2022	
Colour	Black	
Weight [kg/m ¹]	1.5 g/ml	And Constructional of the discount of the construction of the c
Specifications	Cartridge 290 ml	
Use of flame retardants	No	



Rostik Foamtane		
Type of product	FoamTape is part of the complete Panel lack system and the proper adhesive thickness between the panel and th fixation of the panel or substrate until the Paneltack HN lasting bond.	serves as a spacer for the adnesive bead, to ensure he support structure. FoamTape provides an initial 1™ adhesive has cured, while ensuring a strong,
Application	Applied on each vertical profile of the subframe, 1 hour after pre-treatment with the primer	
Manufacturer	Bostik Benelux B.V., The Netherlands	
Product / EAN code	30182771	
Batch no.	162101-14	
Colour	Black	And a second
Weight [kg/m ¹]	Approx. 60 kg/m ³	
Specifications	Double-sided adhesive FoamTape 12 x 3 mm	
Use of flame retardants	No	
Bostik Primer SX Black		
Type of product	Primer SX Black is a black-coloured liquid primer for Pre wooden support structures to which cladding panels wi	-treatment and improved adhesion of smooth-plane II be bonded
Application	Applied on each vertical profile of the subframe (using a roller) prior to bonding	a
Manufacturer	Bostik Benelux B.V., The Netherlands	Bostik
Product / EAN code	30023350	PRIMER
Batch no.	DB21585420	
Colour	Black	
Weight [kg/m¹]	1.03 g/ml	
Use of flame retardants	No	
Bostik Primer Q		
Type of product	Primer for pretreatment of the cladding panel. The Prim	er is a transparent polyurethane suitable for use wit
	various panels and wall cladding materials, including so	me fiber cement boards (FCB) and porous substrates
Application	Applied on the back of the cladding panel to pre-treat the bonding side of the cladding panel prior to bonding the panel by positioning and pressing the panels onto the foamtape and paneltack adhesive	Bostik
Manufacturer	Bostik Benelux B.V., The Netherlands	
Product / EAN code	30612664	Purplement provided PM
Batch no.	DB16952444	and the second s
Colour	Transparent / brown	A Contraction of the Contraction
Weight [kg/m ¹]	1.2 g/ml	
Use of flame retardants	No	



Cembrit Patina		
Type of product	Cembrit Patina is a through coloured fibre cement be solution in all types of constructions.	pard used as cladding panel of a ventilated facade
Manufacturer	Cembrit BV, Vonderweg 7, 7468 DC ENTER	
Product / EAN code	PHU QB 141-152 EN12467 A4 NT	
Batch no.	CE 5B033650 43030304 - 23/03/2021 - P222	
Colour	P22 (Pearl)	
Density	1550 kg/m ³	
Specifications	8 mm thickness	
Use of flame retardants	No	

Peutz was not involved in the selection of the test specimen (or of its materials). The laboratory cannot make any declaration about the representativeness of the provided specimen and the samples made available. The values mentioned are the nominal values as given by the client, unless otherwise stated (MV, measured value).



Reports and results in support of this classification

3.1 Reports

The client has confirmed that the reports provided (see Table 3.1) may be used for this classification.

t3.1 Reports in support of classification

Name of laboratory	Name of client	Number and date of report	Test method
			Field of application rules
Peutz bv	Bostik Benelux B.V.	Y 2424-2E-RA-001; 25-10-2021	EN 13823:2020
Peutz bv	Bostik Benelux B.V.	Y 2424-3E-RA-001; 25-10-2021	EN-ISO 11925-2:2010

3.2 Results

The results obtained are summarised in Tables 3.2 and 3.3.

t3.2 Summary of test results EN 13823

			Re	sults
Parameter		Number of tests	Continuous parameters (average)	Compliance parameters
FIGRA _{0,2MJ}	[W/s]		22	-
FIGRA _{0,4MJ}	[W/s]		22	-
THR _{600s}	[MJ]	3	1.8	-
SMOGRA	[m ² /s ²]		7	-
TSP _{600s}	[m ²]		44	-
LFS reaching edge			-	Ν
Flaming droplets/particles				
- FDP $\leq 10 \text{ s}$			-	Ν
- FDP > 10 s			-	Ν



t3.3 Summary of test results EN-ISO 11925-2

Flame application time 30 s			Results			
	Parameter	Number of tests	Continuous parameters (average)	Compliance parameters		
Surface exposure	$Fs \le 150 \text{ mm}$,	-	J		
Igni	Ignition of filter paper	6	-	Ν		
Edge exposure	$Fs \le 150 \text{ mm}$	<i>,</i>	-	J		
	Ignition of filter paper	6	-	Ν		
Edge exposure	$Fs \le 150 \text{ mm}$		-	J		
per layer	Ignition of filter paper	10	-	Ν		

3.3 Classification criteria

The classification to be obtained is based on the classification criteria given in EN 13501-1. In Tables 3.4 and 3.5 these criteria are summarised.

t3.4 Classification criteria

Test	Parameter		Class		
	Continuous (average) or compliance		В	C	D
EN-ISO 11925-2	Flame spread \leq 150 mm		Y	Ŷ	Y
EN 13823	FIGRA _{0,2MJ}	[W/s]	≤ 120	-	-
	FIGRA _{0,4MJ}	[W/s]	-	≤ 250	≤ 750
	THR _{600s}	[MJ]	≤ 7,5	≤ 15	-
	LFS reaching edge		Ν	Ν	-

t3.5 Criteria additional classifications

Test	Parameter		Class			Class		
	Continuous (average) or compliance		s1	s2	s3	d0	d1	d2
EN-ISO 11925-2	Ignition of filter paper		-	-	-	N	Ν	Y
	Note: ignition of filter paper leads to classi	ification d2, ir	respective o	f the results fo	r FDP in EN 138	23		
EN 13823	SMOGRA	[m ² /s ²]	≤ 30	≤ 180	not s1	-	-	-
	TSP _{600s}	[m ²]	≤ 50	≤ 200	or s2	-	-	-
EN 13823	B223 Flaming droplets/particles (FDP) within 600 s							
	- FDP ≤ 10 s		-	-	-	Ν	Y	-
	– FDP > 10 s		-	-	-	N	N	not d0 or d1



4 Classification and field of application

4.1 Reference of classification

This classification has been carried out in accordance with EN 13501-1:2018 en EN 12467:2012+A2:2018

4.2 Classification

The product, Bostik Paneltack HM adhesive bonding system for Cembrit Patina fiber cement panel, has been classified to its reaction to fire behaviour as: B. The additional classification for the smoke production is: s1, the additional classification for flaming droplets is: d0.

Reaction to fire classification: B-s1, d0

4.3 Field of application

The classification is only valid for the product (Bostik Paneltack HM system) to be used as adhesive bonding system for Cembrit Patina fiber cement panel to wood substructures, as described in chapter 2 of this report.

The classification also applies to fibre cement flat sheets:

- of the same type, but with different dimensions of length and width;
- with a thickness equal to or greater than that used for the test;
- a different surface texture (smooth or embossed);
- with a density within a range of \pm 0.15 g/cm³ of the density used in the test;
- with a joint opening width equal to or smaller than those used for the test;
- fixed at different (wider or closer) horizontal or vertical fixing centres;
- without thermal insulation in the cavity or with other types of class A2-s1,d0 according to EN 13501-1 insulation materials as long as a ventilated air gap of at least (40 ± 1) mm directly behind the sheets is present.

The classification is valid for the following end use applications:

- panels mounted with the Bostik Paneltack HM bonding system to all types of supporting frames (particularly wood and aluminium) against non-combustible walls (A2-s1,d0 or better, e.g. concrete, masonry walls, excluding gypsum plasterboard), with a thickness of at least 9 mm and a density of at least 652.5 kg/m³;
- with open horizontal joints and vertical joints closed by the subframe. The result is also valid for the same type of panel used in applications without joints and used in applications with any type of closed horizontal joint (e.g. using profiles or tongues).

Y 2424-4E-RA-001 11



5 Limitations

There are no limits in time on the validity of this classification document.

This classification document does not represent type approval or certification of the product.

H.H.A. Leenders, BSc. Head of Laboratory for For Fire Testing

This report contains 12 pages

Mook,

D.J. den Boer, BSc. Management