

BOSTIK 3071

VISKOPLASTIČNO PLUTO

PREDNOSTI

- Bez otapala
- Bez mirisa



PRIMJENA

OPIS PROIZVODA

Prikladno za zvučnu i toplinsku izolaciju na okvirima prozora do zida, na okvirima vrata i na pregradnim zidovima te za druge moguće primjene zvučne i toplinske izolacije.

BOSTIK 3070 je visokokvalitetna brtva za zvučnu i toplinsku izolaciju. Materijal se sastoji od granula pluta i elastičnog veziva, tvoreći viskoplastično jednokomponentno brtvilo. Stanice pluta ispunjene zrakom daju BOSTIK 3071 odlična zvučna i toplinsko izolacijska svojstva.

PRIPREMA PODLOGE

Ljepljene površine moraju biti suhe i bez masnoće. Vrijeme odzračivanja je najmanje 30 minuta, a najviše 24 h. Primjena BOSTIK 3071 moguća je sa pištoljem na komprimirani zrak ili ručno. Pripremljene spojeve treba ravnomjerno ispuniti BOSTIK 3071.

METODA RADA

BOSTIK 3071 nanosite ravnomjerno pazeći da su rubovi spojeva u odličnom kontaktu sa BOSTIK 3071, fuge moraju biti ravnomjerno ispunjene. Otvorene spremnike BOSTIK 3071 potrošiti što je prije moguće. Nanesenu površinu zagladite lopaticu, od glatkog drvo, željezo ili prstima.

Nakon stvrdnjavanja BOSTIK 3071 treba obraditi elastičnim brtvilom da bi se zaštitio od vremenskih utjecaja. Također elastičnim brtvilom za fuge na bočnim stranama soba obradite BOSTIK 3071. Za to su prikladne brtve za fuge: BOSTIK 2720 MS i Bostik Bausilicon.

KARAKTERISTIKE PROIZVODA

➤ Sastav	granule pluta povezane ljepljom
➤ Boja	pluto
➤ Postojanost	trajno
➤ Spec težina	cca. 0,6 g/cm ³ (DIN 52451-PY)
➤ Otvrdnjavanje	Sušenjem
➤ Sušenje	otprilike 24 - 48 sati, ovisno o debljini fuge
➤ Radna temperatura	-405 °C to + 90 °C
➤ Temperatura primjene	+ 5 °C to + 35 °C

PRIPREMA PODLOGE

UTROŠAK

Za presjek spoja od 10 x 10 mm² cjevasta vrećica od 500 ml za približno 5 tekućih metara spoja. Potrošnju izračunati na način
širina fuge (mm) x dubina fuge (mm) = ml.

ČIŠĆENJE

Bostik Solvent 270, Bostik Solvent 250, u suhom stanju samo mehanički.

SKLADIŠTENJE

Čuvati na hladnom i suhom mjestu, 12 mjeseci, na temperaturi između + 5 °C i + 35 °C.

PAKIRANJE

Art. Nr.: 30110980 500-ml-duguljasta vrećica.

SAFETY

For more details, consult the safety data sheet on <https://bostiksdsthevercs.com/default.aspx>

The information given and recommendations made herein are based on Bostik's research only and are not guaranteed to be accurate. The performance of the product, its shelf life, and application characteristics will depend on many variables, including the kind of materials to which the product will be applied, the environment in which the product is stored or applied, and the equipment used for application. Any change in any of these variables can affect the product's performance. It is the buyer's obligation, prior to using the product, to test the suitability of the product for an intended use under the conditions that will exist at the time of the intended use. Bostik does not warrant the product's suitability for any particular application. The product is sold pursuant to Bostik's Terms and Conditions of Sale that accompanies the product at the time of sale. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute permission, inducement, or recommendation to practice any invention covered by any patent, without authority from the owner of the pat

BOSTIK TECHNICAL ASSISTANCE

Smart Help +XX XX XXX XXX

