

FIX A570 MULTI TACK

LJEPILO ZA FIKSIRANJE SVIH VRSTA MEKIH PODNIH OBLOGA

PREDNOSTI

- Visoke performanse, trajni prihvat
- Sve vrste podnih obloga
- Svi tipovi upojnih i neupojnih podloga
- Otporno na promet i točkove stolica
- Prikladno za novogradnju i renoviranje



PRIMJENA

OPIS

FIX A570 MULTI TACK akrilno ljepilo pogodno za fiksiranje tekstilnih ploča i tepiha s netkanim podlogama, kao što su: Ultratex, Comfort, Duo soft, te PVC, LVT obloga.

Namjenjeno fiksiranju :

- Tekstilne ploče (na bitumenu, PVC-u, vinilu)
- Tepisi sa poledinom od filca
- PVC podne obloge
- Na betonu i estrihu
- Anhidritnom estrihu
- Glatkim podlogama
- Na šperploči i drvenim podlogama
- Stari PVC
- Keramika

S preporukom vodećih proizvođača obloga. Samo za unutrašnju primjenu.

KARAKTERISTIKE PROIZVODA

| | |
|-------------------------------|--|
| ➤ Sastav/boja | Akrilna emulzija / bijela |
| ➤ Vrijeme čekanja | Od 45 do 60 min, ovisno o uvjetima |
| ➤ Otvoreno vrijeme | Nema limita (bez prašine) |
| ➤ Prohodno | Oko 12 h za PVC ploče, trenutno za tepih ploče sa netkanom poledinom |
| ➤ Potrošnja | 40-100g/m ² |
| ➤ Temperatura primjene | Najbolje između +10°C i +30°C |

*mjerjenja su rađena pri temperaturi od +23° C i 50 % relativne vlažnosti na normalno upojnoj podlozi

PRIPREMA PODLOGE

PRIPREMA PODLOGE

Priprema podloge treba biti u skladu sa građevinskim standardima (DIN 18365-rad na oblaganju podova). Podloga mora biti čvrsta, ravna, suha, bez ostataka starih ljepila, prašine, ulja, i sličnih onečišćenja.

U slučaju polaganja preko postojećih obloga osigurati da su čiste i čvrsto zaljepljene za podlogu.

Daljnja priprema podloge uključuje po potrebi Bostik primere i Bostik nivelirajuće i izravnavajuće mase. Upojne podloge potrebno je obraditi primerom da bi se smanjila upojnost. Sve površine moraju biti zaštićene od vlage, ako ne, treba ih premazati premazom HYTEC E336 XTREM Moisture Vapor Barrier.

Uvijek dopustite da se temeljni premazi i podloge temeljito osuše prije nanošenja ljepila.

METODA RADA

Nanesite ravnomjeran sloj na cijelo područje koje oblažete podnom oblogom pjenastim valjkom ili nazubljenom lopaticom. Maguće ga je nanijeti nerazrijeđeno prskanjem na tehničke podove. Izbjegavajte stvaranje nakupina i lokvica.

Da biste postavili ploče, neophodno je poštivati odgovarajuće vrijeme čekanja: približno 45 do 60 minuta, ovisno o temperaturi i vlažnosti; upojnosti podloge i vrsti podne obloge. Na neupojnim podlogama vrijeme čekanja mora biti najmanje 4 sata.

BOSTIK FIX A570 MULTI TACK osigurava trajni film visoke ljepljivosti, ploče lako možete zamijeniti, nije potreban dodatni proizvod za podizanje ploča. Ploče ili tepih čvrsto pritisnite od središta prema van, posebno pazeći na rubove.

Uklanjanje podnih obloga

Podignite oblogu počevši od ugla i polako odlijepite. Ostaci ljepila mogu se lako ukloniti 15% alkalnom otopinom deterdženta razrijeđenom u vrućoj vodi. Ostatke ljepila namočite cca. 30 minuta dok se ljepilo ne emulgira. Uklonite brisačem i krpom. Potrebno je nekoliko ispiranja da bi se dobio originalni pod bez ljepljive površine.

POKROVNOST

Od 40 do 100g/m² ovisno o tipu obloge i tipu lopatice.

SKLADIŠTENJE

12 mjeseci u originalnoj ambalaži. Osjetljivo na smrzavanje. Skladištiti između +10°C i +30°C.

ČIŠĆENJE

Alati se trebaju čistiti vodom dok je ljepilo još mokro.

| Code | UC | PCB | GENCOD |
|----------|-------|-----|---------------|
| 30615498 | 15 kg | 1 | 3549212484798 |

SAFETY

For more details, consult the safety data sheet on <https://bostiksd.thevercs.com/default.aspx>

The information given and recommendations made herein are based on Bostik's research only and are not guaranteed to be accurate. The performance of the product, its shelf life, and application characteristics will depend on many variables, including the kind of materials to which the product will be applied, the environment in which the product is stored or applied, and the equipment used for application. Any change in any of these variables can affect the product's performance. It is the buyer's obligation, prior to using the product, to test the suitability of the product for an intended use under the conditions that will exist at the time of the intended use. Bostik does not warrant the product's suitability for any particular application. The product is sold pursuant to Bostik's Terms and Conditions of Sale that accompanies the product at the time of sale. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute permission, inducement, or recommendation to practice any invention covered by any patent, without authority from the owner of the pat

BOSTIK TECHNICAL ASSISTANCE

Smart Help +XX XX XXX XXX

