

FIX A995 VLIES

PROTUKLIZNI PREMAZ ZA TEKSTILNE OBLOGE

PREDNOSTI

- Izdašno
- Jednostavna primjena
- Čišćenje vodom
- Dobra pokrovnost
- Bez otapala



PRIMJENA

OPIS

FIX A995 VLIES je protuklizni premaz za tekstilne obloge i ploče na poledini od flisa.

PRIMJENA

Namjenjeno za:

- Nivelirane estrihe
- Postojeće podne obloge
- PVC i CV obloge
- Linoleum
- Drvene obloge
- Prirodni i umjetni kamen u privatnim objektima

FIX A995 VLIES također se može koristiti za ugradnju CV obloga ali bez obrade spojnica do max. 20 m² površine na niveliranim poslogama. Obloge položene na ljepilo mogu se ukloniti u bilo kojem trenutku.

KARAKTERISTIKE PROIZVODA

➤ Sastav/boja	Akrilna emulzija / bijela
➤ Vrijeme čekanja	15-20 min
➤ Prohodno	24 h
➤ Potrošnja	Tekstil na flisu: 70 - 130 g/ m² CV ploče: 160 - 200 g/m²
➤ Temperatura primjene	Podloga od + 15 °C; zrak od + 18 °C. Do 75 % relativne vlage

*mjerjenja su rađena pri temperaturi od + 23° C i 50 % relativne vlažnosti na normalno upojnoj podlozi

PRIPREMA PODLOGE

PRIPREMA PODLOGE

Podloga mora biti ravna, čvrsta, trajno suha, bez prašine, ulja, masti, voska i drugih onečišćenja. Upojne površine moraju se tretirati GRIP A500 MULTI (razrijeđeno vodom u omjeru 1: 1). Postojeći obloge moraju biti čvrsto vezane za podlogu. Prije postavljanja poda na stari pod, mora se temeljito očistiti komercijalnim osnovnim sredstvom za čišćenje.

Prikladno za fiksiranje na drvenim podovima. Oštećenja drvene podloge zbog utjecaja vode (može dovesti do odvajanja od podloge), te zamjena starih obloga nisu obuhvaćene našim jamstvom.

METODA RADA

Nanesite FIX A995 VLIES ravnomjerno na podlogu prikladnim valjkom za i ostavite da se osuši do prozirnog filma. Vrijeme sušenja je 15 - 30 minuta na upojnim podlogama. Na neupojnim podlogama, vrijeme odzračivanja je 30 - 40 minuta, odnosno dok se premaz potpuno ne osuši.

Zatim nanesite podnu oblogu i temeljito utrljajte. Prilikom postavljanja tekstilnih ploča, osigurajte da spojevi ploča nisu zalijepljeni.

Napomena o polaganju CV podova:

Za sigurno fiksiranje CV obloga potrebno je ljepilo nanijeti valjkom od janjeće kože na podlogu u sloj od 160-200 g / m².

KRATKOROČNA IZLOŽENOST VLAZI

Kratkotrajna izloženost vlazi slabi ljepljivost, stoga osušite natopljena područja i podnu oblogu, te ako je potrebno, opteretite površinu, da bi vratiti punu snagu ljepila.

UKLANJANJE OBLOGA

Odignite oblogu u jednom kutu i potpuno je uklonite. Navlažite ostatke ljepila za fiksiranje u toploj vodi uz dodatak komercijalnog sredstva za čišćenje. Nakon 30 - 60 minuta (moguće duže) uklonite ostatke ljepila glatkom špatulom ili četkom. Izbjegavajte ponovno sušenje ljepila. Pridržavajte se uputa proizvođača podne obloge.

POKROVNOST

Tekstilne obloge na flisu:

70 - 130 g/m²

CV ploče:

160 - 200 g/m²

SKLADIŠTENJE

12 mjeseci u originalnoj ambalaži. Osjetljivo na smrzavanje.

ČIŠĆENJE

Alati se trebaju čistiti toplom vodom dok je ljepilo još mokro.

Code	UC	PCB	GENCOD
30615756	10 kg	1	4008373130481

SAFETY

For more details, consult the safety data sheet on <https://bostiksdsthevercs.com/default.aspx>

The information given and recommendations made herein are based on Bostik's research only and are not guaranteed to be accurate. The performance of the product, its shelf life, and application characteristics will depend on many variables, including the kind of materials to which the product will be applied, the environment in which the product is stored or applied, and the equipment used for application. Any change in any of these variables can affect the product's performance. It is the buyer's obligation, prior to using the product, to test the suitability of the product for an intended use under the conditions that will exist at the time of the intended use. Bostik does not warrant the product's suitability for any particular application. The product is sold pursuant to Bostik's Terms and Conditions of Sale that accompanies the product at the time of sale. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute permission, inducement, or recommendation to practice any invention covered by any patent, without authority from the owner of the pat

BOSTIK TECHNICAL ASSISTANCE

Smart Help +XX XX XXX XXX

