

## GRIP A766 ECO+

VIŠENAMJENSKI PRIMER ZA UPOJNE I NEUPOJNE PODLOGE

### PREDNOSTI

- Bazirano na obnovljivim sirovinama
- Koncentrat
- Univerzalna primjena



### PRIMJENA

#### OPIS PROIZVODA

GRIP A766 ECO + pogodan je za upotrebu na upojnim podlogama.

#### Standardne upojne podloge:

- Estrih
- Betonske ploče
- Prirodni i umjetni kamen (osim industrijskih estriha od magnezija i estriha od kamenog drveta)

Prije izravnavanja i niveliranja razrijediti 1:1 s vodom na kalcijum sulfatnom estrihu, drugi sloj po potrebi nakon približno 4 sata. Kao vezni most pri sanaciji starih zgrada, za izgradnju sportskih objekata na izravnavajućim i nivelirajućim slojevima.

### KARAKTERISTIKE PROIZVODA

➤ <b>Sastav/boja</b>	Disperzija sintetičkih smola baziranih na obnovljivim sirovinama Zelena – transparent nakon sušenja
➤ <b>Temperatura primjene</b>	Zrak: min. + 18 °C do + 23 °C; podloga: min. + 15 °C; vlaga: do max. 75%.
➤ <b>*Vrijeme sušenja</b>	0,5-3 h
➤ <b>Potrošnja</b>	75 g/m <sup>2</sup>

\* Mjerenja rađena na + 23° C i 50 % relativne vlažnosti na normalno upojnoj podlozi

## PRIPREMA PODLOGE

### PRIPREMA PODLOGE

U skladu sa zahtjevima DIN 18365, podloga mora posebno ravna, suha, čista, bez pukotina, čvrsta. Mehanički prethodno obradite estrihe od kalcijevog sulfata CA i CAF (četkanje CA, brušenje CAF) i temeljito usisajte. Slijedite upute proizvođača estriha. Primeri, spojni mostovi i premazi ne mogu učiniti nestandardne podloge "spremnim za ugradnju". Umjesto toga, oni služe postizanju optimalnih rezultata obrade u kombinaciji s odgovarajućim materijalima.

### METODA RADA (UPOJNE PODLOGE)

GRIP A766 ECO + treba razrijediti vodom u omjeru 1: 1; Na visoko upojnim cementnim podlogama može se razrijediti vodom do omjera 1: 3. Koristite čiste spremnike. Razrijeđenu disperziju nanesite ravnomjerno izbjegavajući stvaranje nakupina i ostavite da se osuši do prozirnog filma.

Naknadno niveliranje i izravnavanje može se nakon nanošenja temeljnog premaza izvesti "mokro na mokro". Za podloge osjetljive na vlagu, npr. kalcijev-sulfatni estrih, mora se primjeniti vrijeme sušenja od najmanje 4 sata; za iverice npr. tip V 100, pričekajte najmanje 24 sata. Ako se želi brža daljnja obrada, koristite GRIP A936 XPRESS.

### SIGURNOST I ZAŠTITA OKOLIŠA

GISCODE D 1 - bez otapala u skladu s TRGS 610 Čuvati izvan dohvata djece. Osigurajte temeljitu ventilaciju za vrijeme i nakon obrade / sušenja! Izbjegavajte jesti, piti i pušiti tijekom obrade proizvoda. U slučaju dodira s očima ili kožom, odmah isperite s puno vode. Ne dopustite da uđe u kanalizaciju, vodu ili tlo. Proizvod očistite vodom odmah nakon upotrebe. Osnovni preduvjeti za najbolju moguću kvalitetu zraka u zatvorenim prostorima nakon radova na podnoj oblozi su uvjeti za ugradnju u skladu sa standardima i temeljito osušene podloge, premazi i smjese za izravnavanje.

### UPRAVLJANJE OTPADOM

Prikupite i koristite ostatke proizvoda koliko god je to moguće. Ne smije dospjeti u kanalizacijski sustav, vodospreme ili tlo. Prazne plastične posude, iskidane ili suhe mogu se reciklirati (Universal Packaging GmbH). Posude s tekućim ostatkom i sakupljeni ostaci tekućeg proizvoda su opasni otpad. Kontejneri s otvrdnutim ostatkom su otpad od gradilišta / kućni otpad.

## POTROŠNJA

75 g/m<sup>2</sup> / laying

## SKLADIŠTENJE

Shelf life approx. 12 months in original packaging. Protect from frost.

Code	UC	PCB	GENCOD
30615942	10 kg	1	4008373130696

### SAFETY

For more details, consult the safety data sheet on <https://bostiksd.thevercs.com/default.aspx>

*The information given and recommendations made herein are based on Bostik's research only and are not guaranteed to be accurate. The performance of the product, its shelf life, and application characteristics will depend on many variables, including the kind of materials to which the product will be applied, the environment in which the product is stored or applied, and the equipment used for application. Any change in any of these variables can affect the product's performance. It is the buyer's obligation, prior to using the product, to test the suitability of the product for an intended use under the conditions that will exist at the time of the intended use. Bostik does not warrant the product's suitability for any particular application. The product is sold pursuant to Bostik's Terms and Conditions of Sale that accompanies the product at the time of sale. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute permission, inducement, or recommendation to practice any invention covered by any patent, without authority from the owner of the pat*

BOSTIK TECHNICAL ASSISTANCE

Smart Help +XX XX XXX XXX

