

STIX A710 LINO ECO+

LJEPILO ZA LINOLEUM NA BIO BAZI

PREDNOSTI

- Brz inicijalni prihvat
- Visok retencijski kapacitet
- Organska baza



PRIMJENA

OPIS

STIX A710 LINO ECO+ je disperzijsko ljepilo visoke inicijalne snage ljepljenja za ljepljenje linoleuma. Baziran na obnovljivim sirovinama.

KARAKTERISTIKE PROIZVODA

➤ Sastav/boja	Disperzijsko ljepilo na bio bazi/ Bež bijela
➤ Vrijeme čekanja	10-15 min
➤ Otvoreno vrijeme	20-30 min
➤ Prohodno	24 h
➤ Vrijeme sušenja	Cca.24 h
➤ Potrošnja	TKB oblika B1 cca. 400-550 g/m ²
➤ Temperatura primjene	zrak 18°C do 23°C Do 75 % relativne vlage zraka.

*mjerjenja su rađena pri temperaturi od + 23° C i 50 % relativne vlažnosti na normalno upojnoj podlozi

PRIPREMA PODLOGE

PRIPREMA PODLOGE

Priprema podloge treba biti u skladu sa građevinskim standardima (DIN 18365-rad na oblaganju podova). Podloga mora biti čvrsta, ravna, suha, bez ostataka starih ljepila, prašine, ulja, i sličnih onečišćenja.

U slučaju polaganja preko postojećih obloga osigurati da su čiste i čvrsto zaljepljene za podlogu.

Daljnja priprema podloge uključuje po potrebi Bostik primere i Bostik nivelirajuće i izravnavajuće mase. Upojne podloge potrebno je obraditi primerom da bi se smanjila upojnost.

Mastik asfaltni estrih ili druge neupojne podloge potrebno je nivelirati sa nivelirajućom masom minimalne debljine 2 mm.

METODA RADA

Kad postavljate oblogu u roli, položite je u prostor, a zatim ju preklopite natrag u središte prostorije. Nanesite STIX A710 LINO ECO + ravnomjerno na podlogu. Polako položite linoleum u ljepljivi sloj bez zatvaranja zraka u prvoj polovici prostorije, temeljito ga uvaljajte po mogućnosti sa zglobnim valjakom od 50 kg. Na isti način položite i drugu polovicu sobe. Nakon cca. 30 minuta, ponovno uvaljajte valjkom podnu oblogu i provjerite postoje li područja sa zarobljenim zrakom.

Termičko brtvljenje zglobova treba izvesti najranije nakon 24 sata.

Pridržavajte se uputa proizvođača podova, posebno u pogledu klimatizacije podova.

ZAŠTITA NA RADU I ZAŠTITA OKOLIŠA

GISCODE D1 – bez otapala, u skladu s TRGS 610

Čuvati izvan dohvata djece.

Tijekom i nakon obrade i sušenja osigurati provjetranje. Izbjegavajte jesti, piti i pušiti tijekom obrade proizvoda. U dodiru sa očima i kožom odmah ih isprati čistom vodom. Očistite alate odmah nakon uporabe vodom.

Prije upotrebe pročitati uputstva o proizvodu i sigurnosno tehničke listove.

NAPOMENA

Ostatke proizvoda sakupiti što je više moguće i dalje ih koristiti. Ne dopustiti da uđe u kanalizaciju, vodotok ili tlo. Prazna ambalaža s ostacima osušenog proizvoda može se reciklirati (Universal Packaging GmbH). Ambalaža sa ostacima mokrog proizvoda opasan su otpad. Ambalaža s očvrslim ostacima su otpad na gradilištu / kućni otpad.

POKROVNOST

od 400-550 g/m²

SKLADIŠTENJE

12 mjeseci u originalnoj ambalaži. Osjetljivo na smrzavanje.

Code	UC	PCB	GENCOD
30615764	14 kg	1	4008373130580

SAFETY

For more details, consult the safety data sheet on <https://bostiksd.thevercs.com/default.aspx>

The information given and recommendations made herein are based on Bostik's research only and are not guaranteed to be accurate. The performance of the product, its shelf life, and application characteristics will depend on many variables, including the kind of materials to which the product will be applied, the environment in which the product is stored or applied, and the equipment used for application. Any change in any of these variables can affect the product's performance. It is the buyer's obligation, prior to using the product, to test the suitability of the product for an intended use under the conditions that will exist at the time of the intended use. Bostik does not warrant the product's suitability for any particular application. The product is sold pursuant to Bostik's Terms and Conditions of Sale that accompanies the product at the time of sale. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute permission, inducement, or recommendation to practice any invention covered by any patent, without authority from the owner of the pat

BOSTIK TECHNICAL ASSISTANCE

Smart Help +XX XX XXX XXX

