

GRIP A936 XPRESS

HIGH PERFORMANCE SPECIAL PRIMER FOR NON-ABSORBENT SURFACES

KEY BENEFITS

- Fast drying
- High grip : contains quartz
- Easy to use : roller application
- Improve bond-strength of self levelling compounds
- Odourless : can be used in all types of locations



AVIS
TECHNIQUE



APPLICATIONS

DESCRIPTION

GRIP A936 XPRESS is a water-based primer and adhesion promoter that increases adhesion between self-levelling compounds and substrates. Rapid system in combination with our epoxy damp-proof membrane HYTEC E336 XTREM.

DESTINATION

Adheres very well to smooth, dense and non-absorbent concrete surfaces, ceramic tiles, terrazzo, natural and artificial stone slabs, magnesia screeds... For interior use only.

Areas of application :

- All porous or non-porous cement based surfaces
- Epoxy resins
- Old scraped adhesive residue, all types
- Old floor paints
- Heated floors
- Concrete slabs
- Mechanically planed concrete
- Existing ceramic tiles
- Semi-flexible and vinyl asbestos floor tiles
- Residues of all old adhesives
- Existing subfloors paintings

PRODUCT CHARACTERISTICS

Composition / colour	Water-based solution / white translucent
Application temperature	10 to 25°C
Curing time* / Floor installation	60 minutes for absorbent substrates 2 hours on non-absorbent surfaces
Coverage	80 to 120 g/m ²

*these times are determined at + 23° C and 50 % relative humidity on normally absorbent substrates

SUBFLOOR PREPARATION

CLEANING PREPARATION

Preparation should be in accordance with building standards. Subfloors must be sound, of adequate tensile and compressive strength; free from laitance, cracks and structural defects; clean and free from dust, grease, curing compounds, sealers or any other contaminants that would inhibit proper bond.

Substrate residual moisture content must be evaluated, and in accordance to local building standards and floor manufacturers recommendations.

Adhesive residues that are hard, sound and water-tight should be mechanically cut-back to a minimum.

Soft and weak adhesive residues, paint, and gypsum residues should be completely removed.

Substrate moisture content during application must not exceed 3%. If not, they should be primed with a Moisture Vapour Barrier coating previously to self-levelling installation.

METHOD OF USE

Whatever the subfloors, the installation must be realized with a lacquer roll 8 mm.

Impervious substrates

Apply primer evenly in a thin coat (consumption : approx. 100 g/m²). Do not over apply and avoid puddle formation. Allow to dry for approx. 120 minutes prior to over-coating with a self-levelling compound.

Smoothing and levelling compounds must be applied within 24 hours after primer application.

Existing ceramic tiles

Check the right adhesion of tiles as well as the moisture content in the subfloor. The free tiles must be rebonded. Sand the tiles and wash them with a strong lye. Rinse carefully and let completely dry before to install the primer.

Existing crunchy vinyl tiles

When the crunchy tiles are right bonded and can be maintained on place, after a complete cleaning, washing and drying, install the primer and let it dry before recovering. Coverage : 100 g/m².

Residues of old acrylic, alcohol, or bituminous adhesives : scrape as much as possible old residues to obtain slight traces of adhesives.

Old floor paintings

Check the painting's adhesion, then sand completely all the surface, wash, degrease, rinse carefully and let completely dry.

Associated to the epoxy barrier HYTEC E336 XTREM

The GRIP A936 XPRESS is installed after 24 to 48 hours maximum after the epoxy hardening time. Let it dry 2 hours minimum before the self levelling underlay installation.

Bostik Consumer & Construction
Arkema Middle East DMCC, Unit 1108, JBC3 Tower Cluster Y, Jumeirah Lakes Towers, Dubai, United Arab Emirates
Tel.: +9714 875 1700
www.bostik.com

COVERAGE

From 80 to 120 g/m²/ laying

STORAGE STABILITY

Up to 12 months in the original unopened container stored between +10°C and +30°C

REMARK

Underfloor heating systems must comply with current building regulations. Turn off the heating 48 hours before starting the work. The heating should be turned up to its operating temperatures gradually, in stages over 48 hours after laying the floor covering. Do not apply when underfloor heating is in operation.

In all cases, always observe the drying time.

CLEANING

Clean tools and fresh spillages with water.

Code	UC	PCB	GENCOD
30615707	7 kg	1	3549212484866
30615708	20 kg	1	3549212484873

SAFETY

For more details, consult the safety data sheet on <https://bostikdsd.thewerco.com/default.aspx>

The information given and recommendations made herein are based on Bostik's research only and are not guaranteed to be accurate. The performance of the product, its shelf life, and application characteristics will depend on many variables, including the kind of materials to which the product will be applied, the environment in which the product is stored or applied, and the equipment used for application. Any change in any of these variables can affect the product's performance. It is the buyer's obligation, prior to using the product, to test the suitability of the product for an intended use under the conditions that will exist at the time of the intended use. Bostik does not warrant the product's suitability for any particular application. The product is sold pursuant to Bostik's Terms and Conditions of Sale that accompanies the product at the time of sale. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute permission, inducement, or recommendation to practice any invention covered by any patent, without authority from the owner of the pat

BOSTIK SMART SUPPORT

Smart help
+971 4 875 1700

