

FP 403 Fireseal Hybrid

FIRE RETARDANT HYBRID SEALANT

ADVANTAGES

- ETA & UL-EU certified
- -Durable elastic
- Tested for sound insulation
- Up to 4-hour fire resistance
- Good paintable

PRODUCT

FP 403 Fireseal Hybrid is a high quality fire resistant sealant based on hybrid technology.

APPLICATIONS

FP 403 Fireseal Hybrid was specifically developed for fire resistant sealing of connection and expansion joints in construction, which in case of fire, should have a certain fire resistance and prevents spreading of fire, smoke and toxic gases. Also certified for horizontal joints, connection floor/ ceiling with wall, wooden and steel frames, stony substrates and all metal-stud applications. Choose the correct fire resistance for your application by consulting the classification and test reports.

FEATURES

- Extensively tested for fire resistance according to EN 1366-4
- Fire resistance up to 4 hours in lineair (movement)joints
- Can be applied in joints up to 60mm wide
- Suited for both vertical and horizontal joints
- Suitable for wall/ceiling and wall/floor connections
- Certified for steel and wooden frames
- Certified for metal-stud connections
- CE classification: EN 15651-1: F-EXT-INT-CC 25HM
- CE classification: EN 15651-2: G-CC 25HM
- Joint movement up to 25%
- Sound insulation tested according to EN ISO 10140-2:2010
- Minimum shrinkage
- Excellent application and easy toolability
- UV, water and weather resistant
- Paintable with most water based and synthetic paints
- Non corrosive towards metal
- Odourless

METHOD OF USE

Substrate: Substrate must be clean, firm, dust-free and grease-free.



Preparation: FP 403 Fireseal Hybrid adheres perfectly without the use of primer to most non porous substrates. Pretreat porous substrates with Bostik Primer MSP. Bostik Prep M is recommended for metal substrates, such as steel. Always test adhesion prior to application.

Joint construction: The fire resistance of the joint construction can be considerably increased by sealing the joint on both sides. A joint with the correct dimensions is able to absorb movements between building materials. Fill the movement joints with backerod to create the correct joint depth. The joint depth should always be in the correct relationship of the joint width. A general rule is the ratio of joint depth to the width of the joint with a joint width up to 10mm is 1:1, with a minimum of 5mm in width and depth. For joints wider than 10mm, the depth is the width divided by 3 plus 6mm.

Application: Apply FP 403 Fireseal Hybrid with a manual or pneumatic application gun. Carefully spray FP 403 Fireseal Hybrid against the joint walls and then press firmly during finishing.

Finishing: Within 10 minutes, after which skin formation begins, press the sealant against the joint walls (with a pointing trowel or wooden spatula) and then immediately smoothen the joint with the use of Bostik Finishing Soap. Prevent soapy water between joint walls and sealant (to prevent possible detachment along the edges). **Cleaning:** Cured sealant is insoluble and can only be removed mechanically. Uncured residual sealant can be removed with a clean, dye-free cloth soaked with Bostik Liquid 1.

LIMITATIONS

Not suitable for PE, PP, PC, PMMA, PFTE, soft plastics, neoprene and bituminous substrates.

FIRE RESISTANCE

Fire resistance is the time in minutes during which a construction meets the established criteria regarding stability (may not collapse), flame penetration (integrity) and heat transfer (thermal insulation criterion). The thermal insulation criterion specifies that the temperature of the structure on the non-fire side may not rise above 180°C locally and max. 140°C on average. The fire resistance is specified in time (minutes) during which the criteria for flame penetration (E) and temperature (I) are met, e.g. El 240 (4-hour fire resistance). The classification further specifies the type of material in which the joint is made and whether the joint is sealed on the fire side, the non-fire side or both sides. Also stated is stated whether the joints are vertical or horizontal, what the maximum joint width should be, and whether or not a movement is applied to the joint.

CERTIFICATION / TEST REPORTS

- Peutz summary classification reports
- ETA 20/119
- UL-EU certificate
- Fire class B-s1,d0 according to EN 13501-1
- Emicode EC1Plus
- A+ French VOC regulation
- Smoke leakage Sa / S200 according to EN 1634-3
- Sound reduction

SOUND INSULATION

Sound reduction measured according to ISO 10140-1:2012, joint 10mm x 10mm single sided seal with backer rod (PE/PU): Rs,w 53 dB.

PAINTABILITY

FP403 Fireseal Hybrid is paintable with water based and synthetic paints. We recommend testing compatibility with paint prior to application.

STORAGE STABILITY

Store in unopened packaging in dry conditions between +5 and +25 °C. Shelf life 18 months after production. Has a limited shelf life once packaging has been opened.

FURTHER INFORMATION

- Material safety data sheet is available on request

- Summary of fire resistance study

Article number	Colour
30612887	white
30612851	grey
30620686	white
30620668	grey

Packaging cartridge 290 ml cartridge 290 ml sausage 600 ml sausage 600 ml

Bostik BV Denariusstraat 11 4903 RC Oosterhout T: +31 (0) 162491000 www.bostik.nl **Bostik Belux SA - NV** Antwerpse Steenweg 19 B-9080 Lochristi T: + 32 (0) 92551717 **www.bostik.be**

Technical data		
Base	Hybrid	
Application temperature	+5°C to +40°C	
Density	1.48 g/ml (ISO 1183-1)	
Skin formation	10 minutes (at +23°C/50% RH)	
Elongation at break	350% (DIN 53504 S2)	
Shore A	24 (DIN 53505)	
Tensile strength	0,96 N/mm² (DIN 53504 S2)	
Application rate	115 g/min (Ø2,5mm/6,3 bar)	
100% Modulus	0,49 N/mm² (DIN 53504 S2)	
Curing time	2-3mm/24 hours (at +23°C/50% RH)	
Flow resistance	<2mm (ISO 7390)	
Joint movement	25%	
Sound insulation	Rs,w 53 dB (joint 10mm x 10mm) (ISO 10140-1:2012)	
Reaction to fire	Class B-s1,d0	
Temperature resistance	-40°C to +90°C	
Frost resistance during transportsation	Up to -15 °C	
Packed per	box of 12 cartridges / sausages	
Pallet quantity	1248 cartridges / 660 sausages	
Colours	White & grey	

These are typical values

BOSTIK HOTLINE

Smart help + 31 (0) 162491000

Bostik Ltd

Common Road, Stafford ST16 3EH T: +44 (0) 1785 272625 www.bostik.co.uk

Bostik Industries Ltd. Newton Swords, Co. Dublin T: +353 (1) 8624900

www.bostik.ie

All advice, recommendations, figures and safety instructions are based upon thorough research as well as the current state of our experience and are non-binding. Despite the greatest care having been taken to compile the documentation, we assume no responsibility for inaccuracies, mistakes, typographical or print errors. We reserve the right to alter the product whenever we deem necessary. Considering that the design and conditions of the substrate and the circumstances under which the application takes place are beyond our control, no responsibility with regard to the executed works can be assumed on the basis of this documentation. Therefore we advise you to perform a test on the spot yourself. All our sales and deliveries are subject to our General Conditions of Sale and Deliverv.