



BOSTIK

P985

SEAL'N'FLEX SELF-LEVELING HIGH PERFORMANCE SELF-LEVELING SEALANT FOR FLOORING JOINTS

TECHNICAL DATA SHEET

BENEFITS

- Self-leveling, pourable
- Suitable on slope $\leq 4\%$
- One component, ready-to-use
- Bubble-free curing
- Excellent adhesion to most construction materials
- Resistant to most chemicals and jet-fuel
- High durability, permanently elastic
- Suitable for traffic areas

PRODUCT DESCRIPTION

BOSTIK P985 SEAL'N'FLEX SELF-LEVELING is a durable elastic self levelling polyurethane sealant for flooring joints.

APPLICATIONS

BOSTIK P985 SEAL'N'FLEX SELF-LEVELING was specifically developed for sealing of floor joints, for sawn dilatation joints in floor industry, joints for inner and outer ceramic floors, joints for parking, garages, roof, terrace, balconies, pavements, walkways, reparation of active cracks in horizontal surfaces, dilatation joints between terrace/facade and borders and waterproof joints in metallic construction. Good resistance to water, salted water, greases, domestic detergents, most chemical, jet fuel, UV, weather variations, abrasion and indentation.

DIRECTIONS OF USE

A joint with the correct dimensions is able to absorb movements between building materials. The joint depth should always be in the correct relationship of the joint width. A general rule is the ratio of joint depth to the width of the joint with a joint width up to 10 mm is 1:1, with a minimum of 5 mm in width and depth. For wider joints we recommend a width to depth ratio of 1/0,8. For special applications please contact our local technical department for further assistance.



TECHNICAL DATA

100% modulus	ISO 37	0,45 N/mm ²
Application rate	Ø4 mm/3 bar	500 g/min
Application temperature		+5°C to +40°C
Base		Polyurethane
Curing time	@ +23°C/50% RH	3 mm/24 hours
Density	ISO 1183-1	1,35 g/ml
Elongation at break	ISO 37	1000%
Joint movement	ASTM C719	35%
Shore A hardness	ISO 868	25
Skin formation		90 min. @ +23°C/50% RH
Temperature resistance		-30°C to +80°C
Tensile strength	ISO 37	1,9 N/mm ²

These values are typical properties and may vary +/-3%

LIMITATIONS

- Not suitable for PE, PP, PC, PMMA, PTFE, soft plastics, neoprene and bituminous substrates
- Not suitable in combination with chlorides (pools)
- Slight yellowing may occur when white sealant is exposed to ultraviolet rays

SURFACE PREPARATIONS AND FINISHING

Application temperature + 5°C to + 40°C (applies to environment and substrates). All substrates must be solid, clean, dry, and free of grease and dust. Clean substrates with **Bostik T100 UNIVERSAL CLEANER**. **Bostik P985 SEAL'N'FLEX SELF-LEVELING** adheres perfectly without the use of a primer to most porous substrates. Non porous substrates to be pre-treated with **Bostik T300 UNIVERSAL PRIMER**. Always test adhesion prior to application. Use **Bostik T500 FINISHING SOAP** to smooth the joint.

CLEANING

Uncured material and tools can be cleaned by using **Bostik T100 UNIVERSAL CLEANER**. Cured material can only be mechanically removed. Hands can be cleaned with **Bostik T150 CLEANING WIPES**.

COLOUR(S)

- Concrete grey

PACKAGING

- 300 ml Cartridge, 12 per box
- 600 ml Sausages, 12 per box
- 20kg pail, 27 per pallet

SHELF LIFE

In unopened original packaging between + 5°C and + 25°C, shelf life is up to 18 months from production date, stored in a dry place.

HEALTH & SAFETY

Product Safety Data Sheet must be read and understood before use. These are available on request and at www.bostik.com.

CERTIFICATIONS

- A+ French VOC Regulation
- ASTM C 920 C35, S, P, NT, T1, M
- EN 15651-4: PW-EXT-INT-CC 25HM
- ISEGA

All information in this document and in all our other publications (including electronic ones) is based on our current knowledge and experience and is the exclusive (intellectual) property of Bostik. No part of this document may be copied, shown to third parties, reproduced, communicated to the public or used in any other way without Bostik written consent. The technical information in this document serves as an indication and is non-exhaustive. Bostik is not liable for any damage, either directly or indirectly, due to (editorial) errors, incompleteness and/or incorrectness of this document. This includes, but is not limited to, incompleteness and/or incorrectness due to technological changes or any research conducted between the date of publication of this document and the date on which the product is acquired. Bostik reserves the right to amend the wording of this document. Bostik cannot be held liable for any damage, either directly or indirectly, due to the use of the product(s) depicted in this document. The user must read and understand the information in this document and other documents relating to the products prior to the use of the product. The user is responsible for performing all the requisite tests to make sure that the product is suitable for its intended use. We have no influence in what way the product is applied and/or any circumstances relating to events occurring during storage or transport and therefore we do not accept any liability for damage whatsoever. All deliveries are made exclusively in accordance with our general terms of conditions which have been filed at the Dutch Chamber of Commerce

Bostik Benelux BV
Denariusstraat 11 • NL-4903 RC Oosterhout
Tel.: +31 (0)162 491 000
www.bostik.com

BOSTIK SMART SUPPORT

Smart help digital
Bostik.com/

Smart help
+31 (0)162 491 000

