

# **CemenTech C2**

# **TWO-COMPONENT FLEXIBLE WATERPROOFING MORTAR**

# **SMART ADVANTAGES**

- Flexible waterproofing
- Excellent adhesion strength
- Tested according to the Etag 022

# **PRODUCT DESCRIPTION**

It is cement based, two-component, composed of greycolored cementitious compound and blue-colored emulsion, flexible sealing slurry that is reinforced by polymeric additives and used in the solution of waterproofing problems. CemenTech C2 is water-repellent and can be used from the positive side only.

## **APPLICATION AREAS**

- In interior and exterior,
- From positive side only,
- Both vertical and horizontal,
- In wet volumes,
- In continuously wet, humid and damp areas such as balcony, terrace and cellar,
- Water tanks, pools, reservoirs and storage tanks,
- In foundations, basement walls, underground and surface construction works,
- In bridges and retaining walls,

#### **FEATURES**

- Suitable for brush and sprayable use
- Resistant to heavy weather conditions.
- High adhesion quality, strongly adheres to surfaces.
- High abrasion resistance.
- Flexible.
- Suitable for use in drinking waters.

# **PREPARATION OF THE SUBSTRATE**

- The surfaces to be coated should be free of adhesive preventive foreign substances such as dust, dirt, mould oil, paint etc.; residues and wastes like cement, plaster and concrete should also be removed.

- The sub-surfaces that are not strong enough to carry themselves e.g. cracked plasters, weak surfaces, or residues of moss should be cleaned from the application surface.

#### **APPLICATION**

- Powder form Bostik CemenTech C2 Waterproofing Mortar should be poured slowly on liquid component (10 kg) that has been put into a clean container filled, and should be mixed by means of a mixer with low cycle until a clusterfree mixture is obtained. Mixture duration should be minimum 5 minutes. The mixture obtained at the end of the process should be rested for 3 minutes and mixed again until it becomes homogenous for 2 minutes.

- Bostik CemenTeach C2 Waterproofing Mortar emulsion should be shaken well before use.

- Application should be at least two layers thick. After applying the first layer, at least 4-6 hours should be rested and second layer should be applied before waiting period exceeds 24 hours.

- The cracks that might be formed in the event of application to very wide surfaces should be prevented by means of application by leaving joints. Joints should be filled with flexible filling material.

- On the moving grounds that have cracking risk, Bostik FlexMesh net can be applied as an intermediate layer



TECHNICAL DATA	
Color	Grey
Applicable thickness (mm)	Max 6
Recommended applicable thickness (mm)	2
Dry unit volume weight (kg / lt)	1,3 ± 0,2
Wet unit volume weight (kg / lt)	1,8 ± 0,2
Waiting time in container (min)	~ 30
Drying time (hour)	~ 24
Carbondioxide permeability (m)	>50
Permeability to water-vapour (m)	Class I ; Sd <5
Adhesion strength (28 days)	>1(N / mm²)
Capillary water absorption	0,1 (<0,1kg/m².h0,5)
Crack bridging	>0,75
Special mixture emulsion amount	10 kg
(for 25 kg powder component)	blue-colored liquid emulsion
Application temperature	Between +5°C and +35°C
Resistance of hardened coating	Between -25°C and +80°C

Technical data are approximately provided according to a temperature of + 23°C and a relative humidity of 50%.

between the application with the aim of forming a water isolation layer which is more flexible in order to meet the tensile stress.

- It shouldn't be applied to hot or frozen surfaces directly.

**Application with machine:** CemenTech C2 is suitable for use with sprayable machine. Consult Bostik Technical Service for machine use.

#### AFTER APPLICATION

- Freshly applied surfaces should be protected against direct sun light, strong air stream, high air temperature

(above +35°C), rain and frost in the initial days. - Any kind of plaster application on the application surface or ceramic tiling works should be performed 3 days later. - To obtain the recommended long term technical performance of the product, after the completion of the all application, the application and/or work should be covered and protected with a suitable coating or covering (plaster, screed, ceramic, tile etc...) as early as possible (depending on the product's drying time within 3-7 days).

# COVERAGE

Approximately 1,5 – 2,0 kg/m<sup>2</sup> per each 1 mm thickness. Coverage amounts are theoretical values and it is recommended that coverage-controlled sample application is carried out before application.

## PACKAGE

Powder component in 25 kg craft bag, 64 sets in 1 palette Liquid component in 10 kg plastic drum.

#### STORAGE

- Dry mortar bags should be protected for water, frost and adverse weather conditions.

- They should be kept dry and cool on wooden pallets at

between +10°C and +25°C in moisture free conditions.

- The torn and opened products should be closed

immediately and consumed first.

Maximum 8 buckets should be stocked on each other.
Shelf life is maximum 12 months conditional to complying with the abovementioned storage conditions.

#### HEALTH AND SAFETY INFORMATION

For health and safety instruction, first aid measures and spillage and disposal instructions, see separate Safety Data Sheet.





Warning: Bostik is only responsible for the product quality and cannot be held responsible for its mis-use except for the recommendations regarding where and/or how the product shall be used. It is not possible to give a guarantee for the results of operations for individual cases, due to multiplicity of possible uses and storage and processing conditions of the product, which are not under our control. Where necessary, the user should make their own tests. Due to local regulations, product performance may vary from country. This technical bulletin hereby is valid until it is renewed. On somether the products in accordance with technical developments is reserved. In cases concerning the safety of the products, the material safety data sheet (SDS) containing this information should be consulted.