

# CemenTech C2 UV

# TWO-COMPONENT UV RESISTANT EXTRA FLEXIBLE WATERPROOFING MORTAR

# **SMART ADVANTAGES**

- White colour
- Extra flexible
- UV resistant

#### **PRODUCT DESCRIPTION**

It is cement-based, two-component, composed of white-coloured cementitious compound and white-coloured liquid emulsion, extra flexible and UV lights resistant sealing slurry that is reinforced by polymeric additives. It provides water insulation in roof, terraces and balconies. CemenTech C2 UV is water-repellent and can be used from the positive side only.

# **APPLICATION AREAS**

- From positive side only,
- Both vertical and horizontal,
- In wet volumes (WC, bathroom, kitchen etc.),
- In continuously wet, humid and damp areas such as balcony, terrace and cellar;
- Sunny areas,
- Water tanks, pools, reservoirs and storage tanks,
- In foundations, basement walls, underground and surface construction works,
- In bridges and sustaining walls.

# **FEATURES**

- Suitable for brush and sprayable use
- Extra flexible.
- Resistant to UV lights.
- ${\hspace{1pt}\hbox{--}\hspace{1pt}}$  Provides impermeability against the pressured water effect.
- Resistant to heavy weather conditions.
- High adherence; strongly adheres to surfaces.
- Suitable for use without any coating on the drinking water tank  $% \left( 1\right) =\left( 1\right) \left( 1\right) +\left( 1\right) \left( 1\right) \left( 1\right) +\left( 1\right) \left( 1\right)$
- High abrasion resistance.

# PREPARATION OF THE SUBSTRATE

- The surfaces to be coated should be free of adhesive preventive foreign substances such as dust, dirt, mould oil, paint etc.; residues and wastes like cement, plaster and concrete should also be removed.
- The sub-surfaces that are not strong enough to carry themselves e.g. cracked plasters, weak surfaces, or residues of moss should be cleaned from the application surface.

# APPLICATION

- Bostik CemenTech C2 UV Waterproofing Mortar in powder state should be poured slowly on liquid component (10 kg) that has been put into a clean container, and should be mixed by means of a mixer with low cycle until a clusterfree mixture is obtained. Mixture duration should be minimum 5 minutes. The mixture obtained at the end of the process should be rested for 3 minutes and mixed again until it becomes homogenous for 2 minutes.
- Bostik CemenTech C2 UV Waterproofing Mortar emulsion should be shaken well before use.
- Application should be at least two layers thick. After applying the first layer, at least 4-6 hours should be rested and second layer should be applied before waiting period exceeds 24 hours.
- The cracks that might be formed in the event of



TECHNICAL DATA	
Colour	White
Applicable thickness (mm)	Max 6
Recommended applicable thickness (mm)	2
Dry unit volume weight (kg / lt)	1,2 ± 0,2
Wet unit volume weight (kg / lt)	1,7 ± 0,2
Waiting time in container (min)	~ 30
Drying time (hour)	~ 24
Carbondioxide permeability (m)	>50
Permeability to water-vapour (m)	Class I; Sd <5
Adhesion strength (28 days)	> 2 (N / mm²)
Crack bridging	>2
Water pressure	7 bar
Special mixture emulsion amount (for 25 kg powder component)	10 kg (white-coloured liquid emulsion)
Application temperature	Between +5°C and +35°C
Resistance of hardened coating	Between -25°C and +80°C

Technical data are approximately provided according to a temperature of + 23°C and a relative humidity of 50%.

application to very wide surfaces should be prevented by means of application by leaving joints. Joints should be filled with flexible filling material.

- On the moving grounds that have cracking risk, Bostik FlexMesh net can be applied as an intermediate layer between the application with the aim of forming a water isolation layer which is more flexible in order to meet the tensile stress.
- It shouldn't be applied to hot or frozen surfaces directly.

**Application with machine:** CemenTech C2 UV is suitable for use with sprayable machine. Consult Bostik Technical Service for machine use.

# **AFTER APPLICATION**

- Freshly applied surfaces should be protected against direct sun light, strong air stream, high air temperature (above +35°C), rain and frost in the initial days (at least 5  $\,$
- Any kind of plaster application on the application surface or ceramic tiling works should be performed 3 days later.
- To obtain the recommended long term technical performance of the product, after the completion of the all application, the application and/or work should be covered and protected with a suitable coating or covering (plaster, screed, ceramic, tile etc...) as early as possible (depending on the product's drying time within 3-7 days).

#### COVERAGE

Approximately 1,5 - 2,0 kg/m<sup>2</sup> per each 1 mm thickness. Coverage amounts are theoretical values and it is recommended that coverage-controlled sample application is carried out before application.

Powder component in 25 kg craft bag, 64 sets in 1 palette Liquid component in 10 kg plastic drum.

# **STORAGE**

- Dry mortar bags should be protected for water, frost and adverse weather conditions.
- They should be kept dry and cool on wooden pallets at between +10°C and +25°C in moisture free conditions.
- The torn and opened products should be closed immediately and consumed first.
- Maximum 8 bags should be stocked on each other.
- Shelf life is maximum 6 months conditional to complying with the abovementioned storage conditions.

# **HEALTH AND SAFETY INFORMATION**

For health and safety instruction, first aid measures and spillage and disposal instructions, see separate Safety Data Sheet.











Bostik Kimya Sanayi ve Ticaret A.Ş.

Mecidiyeköy Mh. Oğuz Sk. RönesansBiz Plaza N: 4A/7 Zemin Kat 34381 Şişli, İstanbul E-mail: info@bostik.com.tr an Arkema company

www.bostik.com.tr