



BOSTIK RENDER H

HIGH STRENGTH PREPACKED CEMENT BASED PLASTER

KEY FEATURES

- High strength
- Premixed to ensure high consistent quality delivered to site
- High convenience in handling, mixing and application
- Same amount of water is added to achieve consistency in workability
- Mixing and application is easy
- Excellent bond strength
- No wastages on sand and opened unused bag cement
- Cleaning limited to just disposing the used paper bag

DESCRIPTION

Bostik Render H is a high strength prepacked cement based plaster which by simply adding water would give an excellent workability that is easy to use.

Bostik Render H consists of cement, graded sand and additives that provide a bond to concrete and brick substrates. It is meant for internal and external plastering that will surpass the specifiers' stringent requirement.

RECOMMENDED USES

Bostik Render H can be use for bedding brickwork and block work, and the backing and bedding for tiles.

Bostik Render H is highly recommended for all types of concrete substrates; lightweight autoclaved aerated blocks, brick wall and block wall.

SURFACE PREPARATION

All surfaces must be clean, dry and free from dust, grease, wax, oil, laitance, curing compounds and all other contaminants that likely to affect the adhesives bonding. Site practices like washing off the substrate a day before is highly encourage. Dampen dry concrete surface before application.

APPLICATION INSTRUCTION

PERFORMANCE PROPERTIES

Colour	Grey
Water Required	5.5L to 6.5L in 40 kg bag
Consistency	Homogeneous mortar paste
Binder	Cement
Filler	Graded Sand
Additives	Polymer for workability, water retention and adhesion
Yields	Approx. 25 Litres
Density	1850 kg/m ³
Tensile Adhesion Strength	≥ 0.75N/mm ²
Shear Adhesion Strength	Average ≥ 1.0N/mm ²
Compressive Strength 28 days	12 to 20N/mm ²
Stiffening Time - 1.0N/mm ² - 2.0N/mm ²	4 to 6 hours ≤ 8 hours 20 minutes BS EN 1015-9 (Method A)

MIXING

Add 5.5 to 6.5 liters of water to every 40kg bag of Bostik Render H. Gradually pour Bostik Render H into water and continuously mix for approximately 3-5 minutes.

Bostik Render H is ready for use after achieving a consistent homogeneous paste.

PLACING

Bostik Render H can be applied either by using a steel trowel or it can be sprayed. Bostik Render H will remain workable up to 45 minutes from mixing. Any hydration through the addition of water will degrade the performance of the mortar mix.

PACKAGING

40kg bag

STORAGE AND SHELF LIFE

12 months from the date of manufacturing if store in original, sealed and unopened packaging in cold, dry and weatherproof environment.

HEALTH AND SAFETY

Suitable protection clothing, dust masks, gloves and eye protection should be worn. Continual or extended contact with cement products can cause skin irritation. If skin irritation occurs, flush skin with water for a minimum of 15 minutes. If irritation still persists, consult medical advisers. Refer to product safety data sheet for further information.



022-089-2336

Eco-Friendly Building Material

The information and recommendations relating to the application and end-use of the product are given in good faith and based on tests which we believe to be reliable. Differing materials, substrates, environments, site conditions, and product storage, handling and application may affect results. However, no warranty in respect of merchantability or fitness for a particular purpose, nor any liability arising out of any legal relationship, whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. No guarantee of their accuracy can be made because of the great range of field conditions and variation encountered in raw materials, manufacturing equipment and methods. Thus, the products are sold with limited warranty only, and on condition that purchasers will make their own tests to determine the suitability of the product for their particular purposes. Under no circumstances will Bostik be liable to anyone except for replacement of the products or refund of the purchase price.

BOSTIK HOTLINE

Smart help
+606 678 9788



Bostik Findley (Malaysia) Sdn. Bhd. 1994010000474 (286152-V)

Lot 112 & 113, Kawasan Perindustrian Senawang,
70450 Seremban, Negeri Sembilan,
Malaysia

Tel: +606 678 9788 Fax: +606 678 9766

www.bostik.com
an Arkema company

This document supersedes all previously published literature.