



DRY TILE GROUT

CEMENTITIOUS COLOUR GROUT

KEY FEATURES

- High Strength
- Easy Clean Up
- High Surface Density
- Non Shrinking
- Excellent Workability

DESCRIPTION

Bostik DryTile Grout is a special formulated colour grout for filling joints between tiles and natural stone. It is made by select grades, proprietary additives and polymers, portland cement and graded aggregates as in the case of tile joint filler (sanded colour grout).

RECOMMENDED USES

- Filling of joints of 1 to 6mm wide (Dry Tile Grout - unsanded colour grout)
- Filling of joints of 6 to 12mm wide (Tile Joint Filler - sanded colour grout)
- Filling of joints in external installation (Tile Joint Filler - sanded colour grout)
- Filling of joints on floor and wall between glazed tiles, ceramic, mosaics, granite and marble as well as other natural stones.

SUBSTRATE TYPES

- Ceramic Tiles
- Ceramic Mosaics
- Quarry Tiles
- Brick Pavers

SUBSTRATE PREPARATION

Allow the installed tiles to be cured for at least 24 hours before joint filling. Prior to joint filling, ensure the depth is sufficient to accommodate the filling and anchoring of the colour grout. Clear any blockages in the joints.

APPLICATION

Mix one part of water or Hydroment 408, 412 or 425 to 3-4 parts of Dry Tile Grout. A soft but firm paste like mortar should be achieved by thorough mixing. Spread Dry Tile Grout over the surface of the tiles with a soft rubber grout float. Working backwards and forwards in a consistent manner to fill the joints completely. Allow the joints to become firm after 15 to 30 minutes, and compact the joints by pressing the joints with a wooden straight edge trowel along the joints.

NOTE

Mix Dry Tile Grout with Hydroment 408, 412 or 425 additive for areas where vibration, shrinkage or tile growth may occur.

Dry Tile Grout mixed with water will exhibit a lighter colour than those mixed with Hydroment 408, 412 or 425. Colours will progressively lighten after 24 to 48 hours.

CURING

For maximum durability, wipe joints with a damp sponge consecutively for 3 days after joint filling.

PACKAGING

20 and 25 kg bag.

CLEAN UP

COVERAGE (kg/m ²)			
Tile (mm)	Joint Width (mm)		
	3	6	10
25 x 25 x 6	2.8	-	-
50 x 50 x 6	1.2	-	-
100 X 100 X 10	1.1	2.2	3.8
100 X 100 X 13	1.4	2.8	4.5
100 X 200 X 10	0.8	1.6	2.5
100 X 200 X 13	1.1	2.1	3.2
150 X 150 X 10	0.8	1.5	2.2
150 X 150 X 13	1.0	1.9	2.9
150 X 150 X 19	1.4	2.8	4.2
200 X 200 X 10	0.6	1.1	1.7
200 X 200 X 13	0.8	1.5	2.3
250 X 250 X 10	0.4	0.9	1.4
300 X 300 X 10	0.3	0.8	1.2
300 X 300 X 13	0.3	1.0	1.5

Clean excessive grout from the tile surface 1-2 hours after application using a square edge synthetic sponge. Wipe across the surface of the tile in a diagonal direction. Rinse sponge often for best results.

STORAGE AND SHELF LIFE

Store all materials away from heat and moisture. The shelf life of this product is 12 months in unopened bag.


HEALTH AND SAFETY

Use goggles, gloves and mask during handling and application. For more detailed information, refer to product SDS.

The information and recommendations relating to the application and end-use of the product are given in good faith and based on tests which we believe to be reliable. Differing materials, substrates, environments, site conditions, and product storage, handling and application may affect results. However, no warranty in respect of merchantability or fitness for a particular purpose, nor any liability arising out of any legal relationship, whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. No guarantee of their accuracy can be made because of the great range of field conditions and variation encountered in raw materials, manufacturing equipment and methods. Thus, the products are sold with limited warranty only, and on condition that purchasers will make their own tests to determine the suitability of the product for their particular purposes. Under no circumstances will Bostik be liable to anyone except for replacement of the products or refund of the purchase price.

BOSTIK HOTLINE

Smart help
+606 678 9788



Bostik Findley (Malaysia) Sdn. Bhd. 1994010000474 (286152-V)

Lot 112 & 113, Kawasan Perindustrian Senawang,
70450 Seremban, Negeri Sembilan,
Malaysia

Tel: +606 678 9788 Fax: +606 678 9766

www.bostik.com
an Arkema company

This document supersedes all previously published literature.