

Block X500 CemenTech C2

Two-Component Flexible Waterproofing Mortar

WATERPROOFING SOLUTIONS

UNIVERSAL

-  Flexible waterproofing
-  Excellent adhesion strength
-  Tested according to the Etag 022



Old Name : CemenTech C2

PRODUCT DESCRIPTION

Block X500 CemenTech C2, is cement based, two-component, composed of greycolored cementitious compound and blue-colored emulsion, flexible sealing slurry that is reinforced by polymeric additives and used in the solution of waterproofing problems. **Block X500 CemenTech C2** is water-repellent and can be used from the positive side only.

APPLICATION AREAS

-  In interior and exterior,
-  From positive side only,
-  Both vertical and horizontal,
-  In wet volumes,
-  In continuously wet, humid and damp areas such as balcony, terrace and cellar,
-  Water tanks, pools, reservoirs and storage tanks,
-  In foundations, basement walls, underground and surface construction works,
-  In bridges and retaining walls,



TECHNICAL DATA

Colour	Grey
Applicable thickness (mm)	Max. 6 mm
Recommended applicable thickness (for single coat)	Max. 2 mm
Dry unit volume weight (kg / lt)	1,3 ± 0,2
Wet unit volume weight (kg / lt)	1,8 ± 0,2
Waiting time in container (min)	~ 30
Drying time (hour)	~ 24
Carbondioxide permeability (m)	>50
Permeability to water-vapour (m)	Class I ; Sd <5
Adhesion strength (28 days)	> 1 (N / mm ²)
Capillary water absorption	0,1 (<0,1kg/m ² .h0,5)
Crack bridging	>0,75

Special mixture emulsion amount (for 25 kg powder component)	10 kg blue liquid emulsion
Application temperature	Between +5°C and +35°C
Resistance of hardened coating	Between -25°C and +80°C
Technical data are approximately provided according to a temperature of + 23°C and a relative humidity of 50%.	

FEATURES

- ☞ Suitable for brush and sprayable use
- ☞ Resistant to heavy weather conditions.
- ☞ High adhesion quality, strongly adheres to surfaces.
- ☞ High abrasion resistance.
- ☞ Flexible.
- ☞ Suitable for use in drinking waters.

PREPARATION OF THE SUBSTRATE

- ☞ The surfaces to be coated should be free of adhesive preventive foreign substances such as dust, dirt, mould oil, paint etc.; residues and wastes like cement, plaster and concrete should also be removed.
- ☞ The sub-surfaces that are not strong enough to bear their own weight e.g. cracked plasters, weak surfaces, or residues of moss should be cleaned from the application surface.

APPLICATION

- ☞ Powder form **Block X500 CemenTech C2** Waterproofing Mortar should be poured slowly on liquid component (10 kg) that has been put into a clean container filled, and should be mixed by means of a mixer with low cycle until a cluster free mixture is obtained. Mixture duration should be minimum 5 minutes. The mixture obtained at the end of the process should be rested for 3 minutes and mixed again until it becomes homogenous for 2 minutes.
- ☞ **Block X500 CemenTech C2** Waterproofing Mortar emulsion should be shaken well before use.

- ☞ Application should be at least two layers thick. After applying the first layer, at least 4-6 hours should be rested and second layer should be applied before waiting period exceeds 24 hours.
- ☞ The cracks that might be formed in the event of application to very wide surfaces should be prevented by means of application by leaving joints. Joints should be filled with flexible filling material.
- ☞ On the moving grounds that have cracking risk, Bostik FlexMesh net can be applied as an intermediate layer between the application with the aim of forming a water isolation layer which is more flexible in order to meet the tensile stress.
- ☞ It shouldn't be applied to hot or frozen surfaces directly.

Application with machine:

Block X500 CemenTech C2 is suitable for use with sprayable machine. Consult Bostik Technical Service for machine use.

AFTER APPLICATION

- ☞ Freshly applied surfaces should be protected against direct sun light, strong air stream, high air temperature (above +35°C), rain and frost in the initial days (at least 5 days).
- ☞ Any kind of plaster application on the application surface or ceramic tiling works should be performed 3 days later.
- ☞ To obtain the recommended long term technical performance of the product, after the completion of the all application, the application and/or work should be covered and protected with a suitable coating or covering (plaster, screed, ceramic, tile etc...) as early as possible (depending on the product's drying time within 3-7 days).

CONSUMPTION

Approximately 1,5 – 2,0 kg/m² per each 1 mm thickness.

Coverage amounts are theoretical values, and it is recommended that coverage-controlled sample application is carried out before application.

PACKAGING

Powder component in 25 kg craft bag, 64 sets in 1 pallet

Liquid component in 10 kg jerrycan.

STORAGE

- ☞ Dry mortar bags should be protected for water, frost and adverse weather conditions.
- ☞ They should be kept dry and cool on wooden pallets at between +10°C and +25°C in moisture free conditions.
- ☞ The torn and opened products should be closed immediately and consumed first.
- ☞ Maximum 8 bags should be stocked on each other.
- ☞ Shelf life is maximum 12 months conditional to complying with the abovementioned storage conditions.

HEALTH AND SAFETY INFORMATION

For health and safety instruction, first aid measures and spillage and disposal instructions, see separate Safety Data Sheet..



The information given and recommendations made herein are based on Bostik's research only and are not guaranteed to be accurate. The performance of the products, its shelf life, and application characteristics will depend on many variables, including the kind of materials to which the product will be applied, the environment in which the product is stored or applied, and the equipment used for application. Any change in any of these variables can affect the product's performance. It is the buyer's obligation, prior to using the product, to test the suitability of the product for an intended use. Bostik does not warrant the products suitability for any application. The product is sold pursuant to Bostik's Terms and Conditions of Sale that accompanies the product at the time of sale.

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute permission, inducement, or recommendation to practice any invention covered by any patent, without authority from the owner of the past.

Bostik Kimya Sanayi ve Ticaret A.Ş.

Mecidiyeköy Mh. Oğuz Sk. RönesansBiz Plaza N: 4A/7

Zemin Kat 34381 Şişli, İstanbul

E-mail: info.tr@bostik.com

an Arkema company

www.bostik.com

BOSTIK TECHNICAL ASSISTANCE

444 10 99

