



Idenden 30-90AF

VAPO-SEAL COATING

TECHNICAL SHEET NO: TDS00646 19/02/2024

ADVANTAGES

- Fire tested
- Excellent mould resistance
- Internal use



DESCRIPTION

Bostik 30-90AF Vapo-Seal Coating is a high quality, acrylic emulsion coating. The coating is ideal for applications in the thermal insulation industry to seal internal insulated piping, equipment and air conditioning ducting. The coating can be used on faced or unfaced insulation in two coat applications to sandwich reinforcing membranes such as glass cloth scrim. Bostik 30-90AF Vapo-Seal Coating provides a suitable water barrier for HVAC applications. In areas of prolonged high humidity, e.g., external applications or where the insulated system contains chilled water, refrigerant etc. a true water vapour barrier is recommended such as Bostik ET-150 Sprayable Vapour Barrier Coating, Bostik 30-150 Brushable Vapour Barrier Coating or Bostik 30-316 Aquashield Vapour Barrier Coating. The dried film is washable and resistant to mould growth.



TECHNICAL CHARACTERISTICS

Colour	White
Form	Thixotropic liquid
Specific gravity	1.36 approx.
Composition	Acrylic emulsion
Viscosity	Approx. 500P (Brookfield RVT 5rpm at +20°C)
Application temperature	Above +5°C
Service temperature	-20°C to +90°C (depending on operating conditions)
Drying time	Touch dry: 30 to 120 minutes Through dry: 6 to 8 hours (depending on coating thickness and drying conditions)
Fire tests	Independently tested to BS 476: Part 6 – Pass Part 7 – Class 1 Building Regulations: Class 0 When tested on product coated onto calcium silicate boards in two coats, each coat at 3.4m ² per litre. Results will vary when applied at different rates and/or onto other substrates

	<p>UL Classified General Purpose Coatings R38034</p>  <p>Surface burning characteristics for building materials, UL723.</p> <p>Applied to 1/4 in. inorganic reinforced cement board</p> <table> <tr> <td>Flame spread</td> <td>5</td> </tr> <tr> <td>Smoke developed</td> <td>Zero</td> </tr> <tr> <td>Rate per coat (ft.² per gal)</td> <td>75</td> </tr> </table> <p>* Number of coats 2</p> <p>Flash point of liquid coating (closed cup): no flash to boiling</p> <p>Bostik 30-90AF Vapo-Seal Coating meets the requirements of NFPA 90A and 90B (2018 edition) for a flame spread index of less than 25 and a smoke developed index of less than 50, when tested to ANSI/UL 723, Standard for Test for Surface Burning Characteristics of Building Materials by Underwriter's Laboratories</p>	Flame spread	5	Smoke developed	Zero	Rate per coat (ft. ² per gal)	75
Flame spread	5						
Smoke developed	Zero						
Rate per coat (ft. ² per gal)	75						
Fungal resistance	ASTM G21 resistance to fungal growth - zero rating, no fungal growth						
Dubai Central Laboratory VOC content	<p>31g/l</p> 						
Water vapour permeance	Bostik 30-90AF Vapo-Seal Coating has been designed as a breather coating for internal applications. It is resistant therefore to water penetration but allows small quantities of water vapour to pass through it. It has a water vapour permeance in excess of 0.22 U.S perms (0.013 g/sMN) at 1mm dry film thickness (ASTM E96 Method A)						

COVERAGE

- 2.5 to 5.5m² per litre, per coat (depending on substrate, application technique, number of coats and performance requirements)

APPLICATION

IMPORTANT: Before using Bostik 30-90AF Vapo-Seal Coating, refer to the relevant Health & Safety Data Sheet, available at www.bostik.com/uk.

PREPARATION

- Surfaces must be clean, dry and free from dust, oil, grease and any loose materials.
- Bostik 30-90AF Vapo-Seal Coating is only suitable for internal use, unless overpainted by an additional solvent or water-based coating.

APPLICATION

Faced insulation:

- Using a brush, apply Bostik 30-90AF generously to the entire insulation surface, taking care to paste down any overlap joints.
- Apply a second coat of Bostik 30-90AF after the first is dry to the touch, and within 24 hours.

Unfaced insulation:

- Cut a reinforcement membrane such as a scrim canvas or glass cloth to size and using a brush apply Bostik 30-90AF generously to one side.
- Position the reinforcement membrane, coated side down, and pull tight around the insulation to avoid wrinkling.
- Immediately apply a second coat of Bostik 30-90AF to the entire surface.

Spray instructions:

- Bostik 30-90AF may be sprayed with a variety of airless spray systems. However, the following system has proved successful:

PUMP:	Airlessco 5100 / Graco 1095
FLUID HOSE:	7 mm up to 15m, 9mm over 15m
GUN:	Airlessco 007
TIP:	0.017 – 0.021 Reverse-a-quick nozzle

- During spraying, wear suitable personal protective equipment, including respiratory equipment, and protect adjacent surfaces.

CLEANING

- Clean tools and equipment with warm water immediately after use. Cured coating can be removed with white spirit.

STORAGE

- Store and transport securely in an upright position. Ensure the lid is secure. Store for up to 18 months from date of manufacture in original, unopened packaging in cool, dry conditions within the temperature range +5°C to +25°C and out of direct sunlight. Protect from frost.

PRECAUTIONS IN USE

NOTE: Bostik 30-90AF Vapo-Seal Coating is only suitable for internal use, unless overpainted by an additional solvent or water-based coating. It is not suitable for use on floors.

For any application not covered, please contact Technical Services on +44 (0)1785 272625 or visit www.bostik.com/uk for advice.

Recommendations and suggestions are for guidance only, since conditions of use are completely beyond our control.

For health and safety instruction, first aid measures and spillage and disposal instructions, see separate Health and Safety Data sheet for Bostik 30-90AF Vapo-Seal Coating, available at www.bostik.com/uk.

PACKAGING

Product codes	30813601	19 litre drums
----------------------	----------	----------------

This disclaimer is issued by Bostik Limited ("the Company") and applies to the use of any products supplied by the Company ("the Products") displayed on this Technical Data Sheet ("TDS"). Please read this disclaimer carefully before using any of the Products. Using this TDS and/or the Product constitutes your acceptance of this disclaimer. Its contents shall prevail over any directions of use and any disclaimer and/or exclusion or limitation of liability of the Company that may appear on the packaging of the Products.

This disclaimer sets out the entire financial liability of the Company (including any liability for the acts or omissions of its employees, agents and sub-contractors) to any user of the Products ("Product User") in respect of any use made or resale by the Product User, of any of the Products in this TDS.

This disclaimer does not affect the Company's liability for death or personal injury arising from the Company's negligence in respect of the Products, nor its liability for fraud, or fraudulent misrepresentation, nor any other liability that cannot be excluded or limited under applicable law.

The Company's total liability however arising and whether caused by tort (including negligence and breach of statutory duty), breach of contract or otherwise, arising in connection with the use made or resale by the Product User of any of the Products in this TDS shall be limited to the price paid for the Product by the Product User.

The Company shall not be liable to the Product User for any pure economic loss, loss of profit, loss of business, depletion of goodwill or otherwise, in each case whether direct, indirect or consequential, or any claims (including in respect of personal injury insofar as not caused by the Company's negligence) for consequential compensation whatsoever (howsoever caused) which arise out of or in connection with the use made or resale by the Product User of any of the Products in this TDS.

The Company shall not be liable to the Product User in relation to any loss for any use that is inappropriate or use that is otherwise than in accordance with the relevant instructions for use of the Products in this TDS or on the Product. Product Users are advised to confirm the suitability of the Products by their own tests.

This TDS covers just one of a large range of products supplied by the Company.

Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This TDS supersedes all previous TDSs relating to the Products, and users of it must ensure that it is the current issue. Destroy all previous TDS, and if in any doubt, contact the Company, quoting the code number in the top left-hand corner on the front of this document.

Sales	Tel: 0844 371 1192	customer.service@bostik.com
Technical Advice	Tel: 0844 371 1197	technical.service@bostik.com
Safety Data Sheets	Tel: 01785 272625	sds.box-eu@bostik.com

DISCLAIMER

Bostik offers this Technical Data Sheet ("TDS") for descriptive and informational use only. It is not a warranty, a contract or a substitute for expert or professional advice. Please also see the local product Safety Data Sheet for health and safety considerations.

The statements, technical information, data, and recommendations contained in this TDS are provided 'AS IS' and are not warranted or guaranteed in any way. They represent typical results for the products and are based on Bostik's research only. Since the conditions and methods of use of the products are beyond our control, Bostik expressly disclaims any and all liability and damages of whatever kind or nature that may arise from any use of the products, the results therefrom, or reliance on the information contain herein.

Bostik Ltd
Common Road,
Stafford, ST16 3EH, UK
Phone: +44 (0)1785 272625
www.bostik.com/uk

BOSTIK HOTLINE

Smart help +44 (0)1785 272625



All advice, recommendations, figures and safety regulations provided are based on careful investigations, as well as the current state of our experience and are without obligation. Although the documentation has been compiled with the greatest care, we do not accept any liability for inaccuracies, mistakes, typesetting or printing errors. We reserve the right to modify the respective product if we deem it necessary. Since the design, the quality of the substrate and the processing conditions are beyond our assessment, no liability can be accepted for work performed on the basis of this documentation. We therefore advise you to carry out practical tests on site yourself. Our general Terms and Conditions of Sale and Delivery apply to all our sales and deliveries.