



Idenden ET-150

SPRAYABLE VAPOUR BARRIER COATING

TECHNICAL SHEET NO: TDS00640 25/10/2024

SMART ADVANTAGES

- Fire tested
- Dries to form a flexible, durable water-resistant finish
- Internal and external use

DESCRIPTION

Bostik ET-150 Sprayable Vapour Barrier Coating is ideal for applications in the thermal insulation industry as a vapour barrier coating for internal and external insulated piping, equipment and air conditioning ducting. It is also suitable as an asbestos encapsulant. It is easily applied by spray or brush to provide a durable and flexible, water-resistant finish over a wide service temperature range.



TECHNICAL CHARACTERISTICS

Colour	White, black & grey
Form	Thixotropic liquid
Specific gravity	1.26 approx.
Composition	Co-polymer emulsion
Viscosity	Approx. 600P (Brookfield RVT 5rpm at +20°C)
Application temperature	Above +5°C (external work should not be completed in poor drying conditions, or when rain is imminent)
Service temperature	-29°C to +80°C (depending on operating conditions)
Drying time	Touch dry: approx. 2 hours Through dry: approx. 24 hours (depending on coating thickness and drying conditions)
Fire tests	Independently tested to BS 476: Part 6 – Pass Part 7 – Class 1 Building Regulations: Class 0 When tested on product coated onto calcium silicate boards in two coats, each coat at 3.2m ² per litre. Results will vary when

	applied at different rates and/or onto other substrates
VOC testing	Bostik ET-150 Sprayable Vapour Barrier Coating showed low VOC contents in a test specified in LEED 2009 EQ c 4.2 (paints and coatings). The VOC content is below the limit value specified as 50 grams/litre (less water) for 'Flat Topcoats': VOC g/l: 42
Water vapour permeance	Bostik ET-150 Sprayable Vapour Barrier Coating has been designed as a breather coating for internal applications. It is resistant therefore to water penetration, but allows small quantities of water vapour to pass through it. It has a water vapour permeance of 0.16 U.S. perms (0.0092 g/sMN) at 1mm dry film thickness (ASTM E96 Method A)

COVERAGE

- 2.5 to 4.0m² per litre, per coat (depending on substrate, application technique, number of coats and performance requirements)

APPLICATION

IMPORTANT: Before using Bostik ET-150 Sprayable Vapour Barrier Coating, refer to the relevant Health & Safety Data Sheet, available at www.bostik.com/uk.

PREPARATION

- Surfaces must be clean, dry and free from dust, oil, grease and any loose materials.
- External work should not be completed in poor drying conditions, or when rain is imminent.

APPLICATION

- Optimal performance is achieved by applying a minimum of two coats, each at a rate of 3.2m² per litre, to achieve a dry film thickness of 0.5mm.

Spray instructions:

- When spraying Bostik ET-150 Sprayable Vapour Barrier Coating, Bostik recommend you seek advice on suitable spraying equipment from your local distributor or specialist spraying equipment supplier.
- During spraying, wear suitable personal protective equipment, including respiratory equipment, and protect adjacent surfaces.

Pipe or duct insulation:

- Using spray or brush, apply Bostik ET-150 Sprayable Vapour Barrier Coating to the entire surface.
- Embed a reinforcement membrane such as scrim canvas or glass cloth into the wet coat, taking care to smooth out all wrinkles. Overlap all seams and joints by 50mm.

- Apply a second coat of Bostik ET-150 Sprayable Vapour Barrier Coating after the first is touch dry and within 24 hours.

Asbestos encapsulation:

- Only sound asbestos should be coated, and surface preparation & application must be in line with local authority and national regulations.
- Apply Bostik PVA as per the instructions on the Product Data Sheet.
- Using spray or brush, apply Bostik ET-150 Sprayable Vapour Barrier Coating to the entire surface, ensuring any small crevices are properly coated.
- Apply a second coat of Bostik ET-150 Sprayable Vapour Barrier Coating the following day.
- Areas subject to mechanical damage, such as joints may require additional protection with a reinforcement membrane.

Dryness test:

- A dried film can be tested by gently rubbing the coating with a clean, damp rag. If no colour is removed, the film has dried effectively and will exhibit good water resistance.
- When used externally, adequate temporary protection/tenting should be provided as Bostik ET-150 Sprayable Vapour Barrier Coating dries. This will prevent damage from precipitation and aid good film formation and through drying.

CLEANING

- Clean tools and equipment with warm water immediately after use. Remove excess coating whilst it is still wet. Cured coating can be removed with white spirit.

STORAGE

- Store and transport securely in an upright position. Ensure the lid is secure. Store for up to 18 months from date of manufacture in original, unopened packaging in cool, dry conditions within the temperature range +5°C to +25°C and out of direct sunlight. Protect from frost.

PRECAUTIONS IN USE

Use of a different colour of Bostik ET-150 Sprayable Vapour Barrier Coating is recommended for the second coat, to ensure complete coverage is achieved.

Do not allow standing water to form on Bostik ET-150 Sprayable Vapour Barrier Coating coated surfaces. Ensure the upper surface is shaped to make a 15° slope prior to application of coating. It is not suitable for use on floors.

Removal or encapsulation of asbestos containing material, dismantling of any confinement structure and disposal of both asbestos and contaminated materials must be carried out strictly within current regulations & codes of practice and only by an approved contractor.

For any application not covered, please contact Technical Services on +44 (0)1785 272625 or visit www.bostik.com/uk for advice.

Recommendations and suggestions are for guidance only, since conditions of use are completely beyond our control.

For health and safety instruction, first aid measures and spillage and disposal instructions, see separate Health and Safety Data sheet for Bostik ET-150 Sprayable Vapour Barrier Coating, available at www.bostik.com/uk.

PACKAGING		
Product codes	30811811	White 10L bucket
	30811809	Black 10L bucket
	30811810	Grey 10L bucket

This disclaimer is issued by Bostik Limited ("the Company") and applies to the use of any products supplied by the Company ("the Products") displayed on this Technical Data Sheet ("TDS"). Please read this disclaimer carefully before using any of the Products. Using this TDS and/or the Product constitutes your acceptance of this disclaimer. Its contents shall prevail over any directions of use and any disclaimer and/or exclusion or limitation of liability of the Company that may appear on the packaging of the Products.

This disclaimer sets out the entire financial liability of the Company (including any liability for the acts or omissions of its employees, agents and sub-contractors) to any user of the Products ("Product User") in respect of any use made or resale by the Product User, of any of the Products in this TDS.

This disclaimer does not affect the Company's liability for death or personal injury arising from the Company's negligence in respect of the Products, nor its liability for fraud, or fraudulent misrepresentation, nor any other liability that cannot be excluded or limited under applicable law.

The Company's total liability however arising and whether caused by tort (including negligence and breach of statutory duty), breach of contract or otherwise, arising in connection with the use made or resale by the Product User of any of the Products in this TDS shall be limited to the price paid for the Product by the Product User.

The Company shall not be liable to the Product User for any pure economic loss, loss of profit, loss of business, depletion of goodwill or otherwise, in each case whether direct, indirect or consequential, or any claims (including in respect of personal injury insofar as not caused by the Company's negligence) for consequential compensation whatsoever (howsoever caused) which arise out of or in connection with the use made or resale by the Product User of any of the Products in this TDS.

The Company shall not be liable to the Product User in relation to any loss for any use that is inappropriate or use that is otherwise than in accordance with the relevant instructions for use of the Products in this TDS or on the Product. Product Users are advised to confirm the suitability of the Products by their own tests.

This TDS covers just one of a large range of products supplied by the Company.

Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This TDS supersedes all previous TDSs relating to the Products, and users of it must ensure that it is the current issue. Destroy all previous TDS, and if in any doubt, contact the Company, quoting the code number in the top left-hand corner on the front of this document.

Telephone: 01785 272625
Sales: customer.service@bostik.com
Technical advice: technical.service@bostik.com
Safety data sheets: sds.box-eu@bostik.com

DISCLAIMER

Bostik offers this Technical Data Sheet ("TDS") for descriptive and informational use only. It is not a warranty, a contract or a substitute for expert or professional advice. Please also see the local product Safety Data Sheet for health and safety considerations.

The statements, technical information, data, and recommendations contained in this TDS are provided 'AS IS' and are not warranted or guaranteed in any way. They represent typical results for the products and are based on Bostik's research only. Since the conditions and methods of use of the products are beyond our control, Bostik expressly disclaims any and all liability and damages of whatever kind or nature that may arise from any use of the products, the results therefrom, or reliance on the information contain herein.

Bostik Ltd
Common Road,
Stafford, ST16 3EH, UK
Phone: +44 (0)1785 272625
www.bostik.com/uk

BOSTIK HOTLINE

Smart help +44 (0)1785 272625



All advice, recommendations, figures and safety regulations provided are based on careful investigations, as well as the current state of our experience and are without obligation. Although the documentation has been compiled with the greatest care, we do not accept any liability for inaccuracies, mistakes, typesetting or printing errors. We reserve the right to modify the respective product if we deem it necessary. Since the design, the quality of the substrate and the processing conditions are beyond our assessment, no liability can be accepted for work performed on the basis of this documentation. We therefore advise you to carry out practical tests on site yourself. Our general Terms and Conditions of Sale and Delivery apply to all our sales and deliveries.