



Tanking Slurry

WATERPROOF COATING FOR BRICKWORK, CONCRETE & STONE

Date: 06 June 2022

Fact Sheet No.: TDS01654

YOUR SMART ADVANTAGES

- Resists positive and negative water pressure
- Suitable for above and below ground level
- Water vapour permeable

USES

Bostik Tanking Slurry is a breathable, waterproof coating for sound internal brickwork, concrete and stone. This two-coat system is suitable for use above and below ground level. It resists positive and negative water pressure and is water vapour permeable.

Bostik Tanking Slurry can be used for basement walls (and lightly trafficked floors), retaining walls, subways, tunnels, archways, concrete storage tanks and showers/wet rooms.

PRODUCT CHARACTERISTICS

Colour	Grey
Form	Powder
Composition	Cement and special additives
Product Codes	30812810 25kg bag 30814253 20kg bucket
Storage/Shelf Life	Store and transport securely in an upright position. Ensure the lid is fully closed. Store for up to 6 months from date of manufacture in original, unopened packaging, clear of the ground, in cool, dry conditions within the temperature range +5°C to +25°C and out of direct sunlight. Protect from frost

and excessive drafts.

TYPICAL PERFORMANCE DATA (Approx.)

Application Temperature	+5°C to +25°C
Coverage	Up to 15m ² per 25kg per coat Up to 12m ² per 20kg per coat (depending on substrate and application technique)
Working Time	30 to 60 minutes approx. at +20°C
Drying Times	Touch dry after 6 hours approx. at 20°C Overcoat after 5 days approx. at 20°C (depending on coating thickness and drying conditions)
Mix Ratios	4.4 to 4.8 litres of water per 20kg bucket 5.5 to 6 litres of water per 25kg bag
Cleaning	Clean tools and equipment with warm soapy water immediately after use

DIRECTIONS FOR USE

IMPORTANT: Before using Bostik Tanking Slurry, refer to the relevant Health & Safety Data Sheet, available at www.bostik.com/uk.

PREPARATION

1. Remove any dirt, dust, grease, old paint, plaster and any loose surface material. Suitable methods of removing materials may be high-pressure jet washing or wire brushing.

2. After the above treatment, surfaces must be thoroughly washed with clean potable water to remove all dust and loose particles.
3. Bostik Tanking Slurry must not be applied over paint and plaster, as moisture may be trapped behind the coating causing the paint or plaster to deteriorate.
4. Cracks and bolt holes should be filled, and any flowing water stemmed with Bostik Rapid Hardener and Plugger, (see separate product data sheet) prior to the application of Bostik Tanking Slurry.

MIXING

25kg bag

5. Add 5.5 to 6 litres of clean, cold water into a clean plastic bucket. Too much water can result in reduced strength and shrinkage cracks.
6. Add the 25kg of Bostik Tanking Slurry slowly, mixing continually using a paint/plaster mixer fitted to an electric drill.

20kg bucket

7. Add 4.4 to 4.8 litres of clean, cold water into a clean plastic bucket. Too much water can result in reduced strength and shrinkage cracks.
8. Add the 20kg of Bostik Tanking Slurry slowly, mixing continually using a paint/plaster mixer fitted to an electric drill.

APPLICATION

9. Continue mixing until the mixture is a creamy, lump-free consistency. Do not add more water if the product starts to set, since this will weaken the finished product.
10. Apply the mixed product immediately, using it all within 30 to 60 minutes.
11. Apply in temperatures between +5°C to +25°C.
12. Always apply the mix to a pre-dampened surface.
13. Apply the first coat horizontally using a brush working into any gaps at a thickness of between 1mm to 1.5mm.
14. After approximately 2 hours, but within 24 hours, lightly dampen the first coat and remove excess water. Apply the second coat by brush, this time vertically at a thickness of between 1mm to 1.5mm. Only apply the second coat once the first coat is sound enough to receive it without damage. After an hour, the second coat can be smoothed if required by lightly brushing with water.

DRYING TIMES

15. Drying times are greatly affected by temperature and ventilation. As a guide, allow approximately 6 hours for the surface to become touch dry and 5

days before over coating. Low temperatures and poor ventilation will extend the drying time.

16. Bostik Tanking Slurry requires a through draft to avoid excessive condensation during the curing period. Please note that condensation may still occur on the coating even after it has thoroughly dried out, especially if the area is cold and poorly ventilated.
17. Do not use a dehumidifier during the curing period.

OVERCOATING

18. The product does not need to be over-coated. Please ensure that waterproofing is successful before applying plaster.
19. If plaster is to be used, ensure that it is cement based plaster and applied to between 3mm and 5mm in thickness. Do not use a gypsum based plaster.
20. If paint is to be applied, we recommend that breathable emulsion paint is used, as there may still be water vapour penetration. Do not apply solvent or vinyl based paints.

CLEANING

21. Clean tools and equipment with warm soapy water immediately after use.

PRECAUTIONS IN USE

Bostik Tanking Slurry should be applied at a temperature between +5°C to +25°C. Always apply Bostik Tanking Slurry to a pre-dampened surface

Colour indicated on pack is a guide only. It is recommended that users mix a small amount of cement and allow to dry to determine colour suitability before commencing work. Shade variations may occur between different batches. When completing projects requiring multiple buckets, please ensure they are from the same batch.

For any application not covered, please contact Technical Services on +44 (0)1785 272625 or visit www.bostik.com/uk for advice.

Recommendations and suggestions are for guidance only, since conditions of use are completely beyond our control.

For health and safety instruction, first aid measures and spillage and disposal instructions, see separate Health and Safety Data sheet for Bostik Tanking Slurry, available at www.bostik.com/uk.

BOSTIK HOTLINE

Smart help +44 (0) 1785 272625



**CONSTRUCTION PRODUCT REGULATION
DECLARATION OF PERFORMANCE**

No: TDS01654

Product Description: **Bostik Tanking Slurry**

Product Code: **5010591540224 & 5010591540170**

Intended Use: **Renovation rendering mortar (R) for internal use**

Manufacturer: **Bostik Ltd**
Contact Address: **Common Road
Stafford
ST16 3EH**

System of Assessment: **System 4**

Harmonised Standard: **EN 998-1:2010**

Declared Performance:

Essential Characteristics	Performance	Harmonised technical specification
Reaction to fire	F	EN 998-1:2010
Adhesion	0.8 N/mm² Fracture Pattern B	
Dangerous substances	See MSDS	

The performance of the product Bostik Tanking Slurry 5010591540224, 5010591540170, 5010591004054 & 3549212479848 is in conformity with the declared performance shown in the table above.

This declaration of performance is issued under the sole responsibility of Bostik Ltd.

Signed for and on behalf of Bostik Ltd by:

Name: Marrienne Drayton

Function: Quality Manager

Signature:



Date: February 2018

This disclaimer is issued by Bostik Limited ("the Company") and applies to the use of any products supplied by the Company ("the Products") displayed on this Technical Data Sheet ("TDS"). Please read this disclaimer carefully before using any of the Products. Using this TDS and/or the Product constitutes your acceptance of this disclaimer. Its contents shall prevail over any directions of use and any disclaimer and/or exclusion or limitation of liability of the Company which may appear on the packaging of the Products.

This disclaimer sets out the entire financial liability of the Company (including any liability for the acts or omissions of its employees, agents and sub-contractors) to any user of the Products ("Product User") in respect of any use made or resale by the Product User, of any of the Products in this TDS.

This disclaimer does not affect the Company's liability for death or personal injury arising from the Company's negligence in respect of the Products, nor its liability for fraud, or fraudulent misrepresentation, nor any other liability which cannot be excluded or limited under applicable law.

The Company's total liability however arising and whether caused by tort (including negligence and breach of statutory duty), breach of contract or otherwise, arising in connection with the use made or resale by the Product User of any of the Products in this TDS shall be limited to the price paid for the Product by the Product User.

The Company shall not be liable to the Product User for any pure economic loss, loss of profit, loss of business, depletion of goodwill or otherwise, in each case whether direct, indirect or consequential, or any claims (including in respect of personal injury insofar as not caused by the Company's negligence) for consequential compensation whatsoever (howsoever caused) which arise out of or in connection with the use made or resale by the Product User of any of the Products in this TDS.

The Company shall not be liable to the Product User in relation to any loss for any use which is inappropriate or use which is otherwise than in accordance with the relevant instructions for use of the Products in this TDS or on the Product. Product Users are advised to confirm the suitability of the Products by their own tests.

This TDS covers just one of a large range of products supplied by the Company.

Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This TDS supersedes all previous TDSs relating to the Products, and users of it must ensure that it is the current issue. Destroy all previous TDS, and if in any doubt, contact the Company, quoting the code number in the top right hand corner on the front of this document.

Sales	Tel: 0844 371 1192	customer.service@bostik.com
Technical Advice	Tel: 0844 371 1197	technical.service@bostik.com
Safety Data Sheets	Tel: 01785 272625	sds.box-eu@bostik.com