



A150 SUPER-GRIP

NON-SLIP WALL TILE ADHESIVE

Date: 6 May 2020

Fact Sheet No.: TDS01594

YOUR SMART ADVANTAGES

- High bonding strength
- Exceptional non-slip properties
- Advanced acrylic formulation

USES

Bostik A150 Super Grip is a thin-bed adhesive suitable for fixing ceramic wall tiles to most types of sound interior surfaces, including: plaster, sand and cement rendering, plasterboard, bricks and old glazed tiles. Bostik A150 Super Grip is suitable for use in kitchen and bathroom areas subject to intermittent wetting, and for domestic shower walls, when applied by the solid bed method and when used with a water resistant grout. It is not recommended for exterior use, or on areas subjected to total immersion i.e swimming pools. For areas of permanent immersion, such as swimming pools the use of a cementitious adhesive from the Bostik range is recommended i.e. Bostik MC310 One Part Flexible.

PRODUCT CHARACTERISTICS

CE Classification	D1TE
Colour	Buff
Form	Paste
Composition	Acrylic dispersion based formulation
Product Code	30811605 10 Litre
Storage/Shelf Life	Store and transport this container in a secure upright position. Store for up to 24 months from date of manufacture when stored in original, unopened packaging under cool, dry conditions within the temperature

range +5°C to +30°C. Protect from frost.

TYPICAL PERFORMANCE DATA (approx.)

Application Temperature	+5°C to +35°C		
Coverage	Size (litres)	Notched Trowel	Solid Bed
	10	10m ²	5.4m ²
Coverage is dependent upon the nature of the substrate, the adhesive bed thickness and the tile dimensions.			
Open Time	20 minutes at 20°C		
Drying Times	24 hours at 20°C on standard backgrounds		
	72 hours at 20°C on impervious backgrounds		

DIRECTIONS FOR USE

IMPORTANT: Before using Bostik A150 Super Grip refer to the relevant Health & Safety Data Sheet, available at www.bostik.com/uk.

Tiling and grouting should be carried out in accordance with the relevant British Standards Codes of Practice.

PREPARATION

1. Ensure that all surfaces are clean, dry, sound and free from paint, dust, grease or any contaminating barrier.
2. Make good any unsound areas and remove flaky or peeling layers before tiling.
3. If tiling over old ceramic tiles, check for stability and re-fix if loose.
4. With new concrete rendering, or new brickwork do not commence tiling for at least four weeks to allow for shrinkage.
5. Consult the Bostik Primers Data Sheet for priming

requirements.

6. Over-trowelled or shiny plastered surfaces should be wire brushed to key the surface, before priming with Bostik AP 250 Flexibond diluted 1 part to 2 parts water.
7. Check before use that the colour of the adhesive does not cause staining or discolouration of light coloured or translucent tiles.

APPLICATION

Notched Trowel Method (dry areas):

8. Stir the contents well before use.
9. The adhesive should be spread onto the wall with a plane trowel, or float to a depth of 3mm.
10. 'Comb' the adhesive immediately with a notched trowel, e.g. one having 6mm x 6mm notches at 12mm centres.
11. Press the dry tiles with a slight twisting action into the adhesive.
12. Spread only sufficient material for about 20 minutes tiling work i.e. approx. 1m².
13. It is good practice to remove a tile occasionally to check that adequate contact and wetting out are being achieved; a minimum of 70% of the back of each tile should be in good contact with the adhesive, and 100% if being used in a bathroom/shower situation.

Solid Bed Method (wet areas):

14. For areas that will be frequently wet, including showers, the adhesive should be spread on the background to a depth of 3mm and then 'combed' very lightly, simply as a means of leveling any projections. The dry tiles should then be pressed into the adhesive bed, ensuring no voids are left behind them.

Spacing of Tiles:

15. Tile joints for standard tiles should be a minimum of 2mm with guidance taken from the grout being used for maximum space. The joint should be left around each tile by the insertion of tile spacers during fixing. When tiling mosaics joint gaps may vary dependent on style of mosaics used. Please follow manufactures recommendations.
16. Ceramic tiles should never be fixed with tight joints.
17. Minor adjustments to the position of a tile may be made up to 5 minutes after the application.
18. Spacers may be removed approximately 2 hours after application, when the adhesive has dried sufficiently.

GROUTING

19. Ensure that the adhesive has completely set and that the tiles are firm before grouting. Bostik A150 Super Grip should normally be set after 24 hours but a longer setting period may be required on sealed or impervious surfaces or at low ambient temperature when 72 hours should be allowed prior to grouting. Protect wall tiling from water for at least 72 hours after grouting, or according to instructions on the grout packaging.

CLEANING

20. Surplus adhesive should be removed immediately from the surface of the tiles and grout lines.
21. Clean tools and equipment immediately after use with water.

PRECAUTIONS IN USE

For any application not covered please contact Technical Services on +44 (0)1785 272625 or visit www.bostik.com/uk for advice.

Recommendations and suggestions are for guidance only, since conditions of use are completely beyond our control.

For health and safety instruction, first aid measures and spillage and disposal instructions, see separate Health & Safety Data Sheet for Bostik A150 Super Grip, available at www.bostik.com/uk.

SURFACE CONSIDERATIONS

Concrete/Masonry:

22. Before covering and after curing, concrete and masonry should be left to dry out by exposure to air for at least 6 weeks.

Sand/Cement Render:

23. Before tiling, allow to dry out by exposure to air for at least 2 weeks.

Gypsum Plaster:

24. All plasterwork should be firm and soundly fixed to its substrate and be sufficiently strong to support the specified tiling. The maximum weight of tiling which can be supported by a dry, firmly adhered plaster background is 20kg/m². Before tiling, the plaster must be left to dry for at least 4 weeks and be thoroughly dry. Never tile on to a soft backing plaster. Remove any defective areas, including badly cracked plaster, to straight horizontal and vertical edges. Smooth plaster should be mechanically roughened to supply a suitable key and primed using diluted Bostik AP 250 Flexibond diluted 1 : 2 with water. Gypsum plaster is sensitive to water, and in wet areas, care should be made to prevent water ingress. In this situation we would recommend tanking out the installation with Bostik Watertite Tanking & Wetroom Kit. A polymer modified cement based adhesive such as Bostik MC310 One Part Flexible must then be used.

Plasterboard:

25. Ensure that boards are dry, securely fixed and rigid, and the face intended to receive the decorative finish is exposed. Plasterboard should be screwed into the supporting joists at maximum 300mm centres. The weight of the tiling should not exceed 32kg/m². Plasterboard is sensitive to water and in wet areas care should be made to prevent water ingress. In this situation we would recommend tanking out the installation with Bostik Watertite Tanking & Wetroom Kit. A polymer modified cement based adhesive such as Bostik MC310 One Part Flexible must then be used.

Plywood:

26. Not suitable for use with Plywood.

Chipboard:

27. Not suitable for use with chipboard.

Tile Backerboards:

28. Ensure that boards are securely fixed and rigid. Boards should be screwed to the supporting joists at maximum 300mm centres vertically and horizontally. Do not seal or prime surfaces to be tiled. When using paste adhesives on impervious backgrounds grouting should be deferred for as long as possible to allow the moisture from the adhesive to dry out through the joints. Alternatively, use a polymer modified cement based adhesive such as Bostik MC310 One Part Flexible.

Existing Tiling:

29. Existing glazed tiles must be firmly fixed to their bed and the bed and original substrate must be sufficiently strong to support the weight of new tiling. Tiles should be thoroughly cleaned to remove any oils or greases that may prevent good adhesion. Any loose or hollow sounding areas must be removed and made good before tiling. When using paste adhesives on impervious backgrounds and large format tiles grouting should be deferred for as long as possible to allow the moisture from the adhesive to dry out through the joints. Alternatively, use a polymer modified cement based adhesive such as Bostik MC310 One Part Flexible.

Painted Walls:

30. Any painted surface where tiling would be required should have any loose and flaking paint removed. One way of checking if paint is sound is by applying a self-adhesive tape directly on the clean dry paint surfaces. After 10 minutes remove the tape. If any paint is removed with the tape, the paint is not suitable to be tiled over. Remove all unsound paint mechanically. Do NOT use paint strippers. Please note when tiling on to paint drying times will be extended. It is recommended to leave adhesive to dry for a minimum of 3 days before grouting.

Swimming Pools:

31. Not suitable for swimming pools.



BOSTIK HOTLINE

Smart help +44 (0) 1785 272625
Ireland +353 (0) 1 8624998

The banner features a green lizard with orange spots on its back, positioned on the right side. The background is split into a blue top half and a dark blue bottom half.

**CONSTRUCTION PRODUCT REGULATION
DECLARATION OF PERFORMANCE**

No.:TDS01594

Product Description: **BOSTIK A150 SUPER-GRIP**

Product Code: **5010591068292**

Intended Use: **Normal dispersion adhesive with extended open time and reduced slip for internal tiling**

Manufacturer: **Bostik Ltd**

Contact Address: **Common Road
Stafford
ST16 3EH**

System of Assessment: **System 3**

Harmonised Standard: **EN12004:2007+A1:2012**

Notified Body: **The notified body No.NB1289 carried out the determination of the product type on the basis of type testing on samples taken by the manufacturer under system 3 and issued the test report (131338)-5695**

Declared Performance: **D1TE**

Essential Characteristics	Performance	Harmonised technical specification
Reaction to fire	F	EN12004:2007+A1:2012
Initial Shear adhesion strength	$\geq 1 \text{ N/mm}^2$	
Shear adhesion strength after heat aging	$\geq 1 \text{ N/mm}^2$	
Slip	$\leq 0.5 \text{ mm}$	
Extended open time: tensile adhesion strength	$\geq 0.5 \text{ N/mm}^2$ after not less than 30 minutes	
Dangerous substances	See MSDS	

The performance of the Bostik A150 Super-Grip 5010591068292 is in conformity with the declared performance shown in the table above.

This declaration of performance is issued under the sole responsibility of Bostik Ltd.

Signed for and on behalf of Bostik Ltd by:

Name: Alison Jamieson

Function: S.H.E.Q. Manager

Signature: 

Date: May 2014

This disclaimer is issued by Bostik Limited ("the Company") and applies to the use of any products supplied by the Company ("the Products") displayed on this Technical Data Sheet ("TDS"). Please read this disclaimer carefully before using any of the Products. Using this TDS and/or the Product constitutes your acceptance of this disclaimer. Its contents shall prevail over any directions of use and any disclaimer and/or exclusion or limitation of liability of the Company which may appear on the packaging of the Products.

This disclaimer sets out the entire financial liability of the Company (including any liability for the acts or omissions of its employees, agents and sub-contractors) to any user of the Products ("Product User") in respect of any use made or resale by the Product User, of any of the Products in this TDS.

This disclaimer does not affect the Company's liability for death or personal injury arising from the Company's negligence in respect of the Products, nor its liability for fraud, or fraudulent misrepresentation, nor any other liability which cannot be excluded or limited under applicable law.

The Company's total liability however arising and whether caused by tort (including negligence and breach of statutory duty), breach of contract or otherwise, arising in connection with the use made or resale by the Product User of any of the Products in this TDS shall be limited to the price paid for the Product by the Product User.

The Company shall not be liable to the Product User for any pure economic loss, loss of profit, loss of business, depletion of goodwill or otherwise, in each case whether direct, indirect or consequential, or any claims (including in respect of personal injury insofar as not caused by the Company's negligence) for consequential compensation whatsoever (howsoever caused) which arise out of or in connection with the use made or resale by the Product User of any of the Products in this TDS.

The Company shall not be liable to the Product User in relation to any loss for any use which is inappropriate or use which is otherwise than in accordance with the relevant instructions for use of the Products in this TDS or on the Product. Product Users are advised to confirm the suitability of the Products by their own tests.

This TDS covers just one of a large range of products supplied by the Company.

Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This TDS supersedes all previous TDSs relating to the Products, and users of it must ensure that it is the current issue. Destroy all previous TDS, and if in any doubt, contact the Company, quoting the code number in the top right hand corner on the front of this document.

Sales	Tel: 01785 272625	Fax: 01785 241818	customer.service@bostik.com
Technical Advice	Tel: 01785 272625	Fax: 01785 272867	technical.service@bostik.com
Ireland	Ireland +353 (0) 18624998		www/bostik.com/ireland
Safety Data Sheets	Tel: 01785 272625	Fax: 01785 212962	sds.box-eu@bostik.com