

## Laboratory for Fire Safety

### Summary of a fire resistance tests:

#### *Bostik FP 401 Fireseal Acrylic connecting stone to stone and gypsum to gypsum*

On behalf of Bostik, four tests were performed in the Peutz Laboratory for Fire Safety for determination of the fire resistance of several linear joint seals with Bostik FP 401 Fireseal Acrylic (further called FP 401 Fireseal Acrylic or Bostik FP 401) in walls of aerated concrete and / or gypsum. The tests were performed in accordance with the European standard EN 1366-4:2006+A1:2010 using the standard heating curve.

This summary provides an outline of the product performance and the conclusions of the test. For a complete description of the examined linear joint seals, please refer to the reports mentioned in the footnote.

Based on the tests performed in accordance with EN 1366-4:2006+A1:2010 and the extended application in accordance with EN 15882-4:2012, the system was classified in accordance with EN 13501-2:2007+A1:2009 and EN 13501-2:2016. Taking into account the possible classification times mentioned in the standard, a linear joint seal made out of FP 401 Fireseal Acrylic, is classified according to the following combinations of performance parameters and classes.



Fire resistance classification (vertical linear joint seals in a stone wall)		
Stone to stone wall thickness $\geq 115$ mm		Stone to stone Wall thickness $\geq 100$ mm
<b>Bostik FP 401 unexposed face</b> <b>Bostik FP 404 exposed face</b>	<b>Bostik FP 401 applied at unexposed face</b>	<b>Bostik FP 401 applied at both faces</b>
EI 180 – V – X – F – W 8 to 30	EI 45 – V – X – F – W 5 to 20	EI 120 – V – X – F – W 5 to 30
EI 240 – V – X – F – W 8	EI 240 – V – X – F – W 5	EI 180 – V – X – F – W 5 to 10
E 240 – V – X – F – W 8 to 30	E 240 – V – X – F – W 5 to 20	E 240 – V – X – F – W 5 to 30


E = Criterion integrity, I = Criterion insulation, V = Vertical application in a vertical wall, X = No movement applied, F = Splice applied in the field, W = Permitted width range in millimetres (see Graph 1 for seal depth)

This summary consists out of 5 pages. The classification reports that form the basis for this summary are available for inspection at the client and are registered as YB 1567-1E-RA-002 dated June 24, 2015, YB 1692-1E-RA-002 dated September 16, 2016 and 18565C dated September 28, 2017.	<b>Reference</b> HL/RO//YC 2088-2E-RA-001 29 January 2020	<b>Page</b> 1/5	<b>Initials</b> 
---	---	--------------------	---------------------

The following conditions apply:

- the classifications are valid for linear joint seals in a wall with an orientation as mentioned (vertical);
- the linear joint seals may be applied in any type of wall of aerated concrete (class G4/600 or heavier), concrete, limestone or masonry with a minimal thickness as mentioned (100 or 115 mm);
- the surfaces of the material on which FP 401 Fireseal Acrylic and Bostik FP 404 Fire Retardant PU (Gun)Foam is applied are thoroughly cleaned and treated with primer and moistened with water when needed. Except for the fully filled linear joint seals, the use of suitable PE / PU backing material is mandatory;
- the depth of FP 401 Fireseal Acrylic depends on the width of the linear joint seal. The minimum depth of FP 401 Fireseal Acrylic in relation to the width of the linear joint seal is shown in Graph 1 below. The depth of the sealant may also be increased with respect to the Graph (the lines are the minimum and recommended seal depth). If applicable, the rest of the slot is fully filled with Bostik FP 404 Fire Retardant PU (Gun)Foam;
- the allowed movement capability in practice is maximized to 7.5 %;
- when FP 401 Fireseal Acrylic is applied at both faces, the classifications are valid for both directions. When FP 401 Fireseal Acrylic is applied at one face, the classifications are valid for FP 401 Fireseal Acrylic at the unexposed face.

**Graph 1: Minimum seal depth in relation to the seal width**



This summary consists out of 5 pages. The classification reports that form the basis for this summary are available for inspection at the client and are registered as YB 1567-1E-RA-002 dated June 24, 2015, YB 1692-1E-RA-002 dated September 16, 2016 and 18565C dated September 28, 2017.

**Reference**

HL/RO//YC 2088-2E-RA-001  
29 January 2020

**Page**

2/5

**Initials**


*[Handwritten initials]*

<b>Fire resistance classification</b> <b>(horizontal linear joint seals in a stone wall and a wall abutting a floor, ceiling or roof)</b>
<b>Applied connecting stone to stone, thickness wall <math>\geq 100</math> mm</b>
<b>Bostik FP 401 applied at both faces</b>
El 180 – T – M 5 – F – W 10 to 30
E 240 – T – M 5 – F – W 10 to 30

E = Criterion integrity, I = Criterion insulation, T = Horizontal application in a vertical wall and a wall abutting a floor, M = Movement induced in %, F = Splice applied in the field, W = Permitted width range in millimetres (see Graph 2 for seal depth)

The following conditions apply:

- the classifications are valid for linear joint seals in a wall and a wall abutting a floor, ceiling or roof with an orientation as mentioned (horizontal);
- the linear joint seals may connect to any type of construction of aerated concrete (class G4/600 or heavier), concrete, block work or masonry with a minimal thickness as mentioned (100 mm);
- the surfaces of the material on which FP 401 Fireseal Acrylic is applied are thoroughly cleaned and treated with Primer when needed;
- the use of suitable PE / PU backing material is mandatory;
- the required depth of FP 401 Fireseal Acrylic depends on the width of the linear joint seal. The minimum depth of FP 401 Fireseal Acrylic in relation to the width of the linear joint seal is shown in Graph 2 below. The required depth of the sealant may also be increased with respect to the Graph (the lines are the minimum and recommended seal depth);
- deformation of the linear joint seals in practice is maximized to 7.5 %;
- the classifications are valid for both directions.



This summary consists out of 5 pages. The classification reports that form the basis for this summary are available for inspection at the client and are registered as YB 1567-1E-RA-002 dated June 24, 2015, YB 1692-1E-RA-002 dated September 16, 2016 and 18565C dated September 28, 2017.

#### Reference

HL/RO//YC 2088-2E-RA-001  
29 January 2020

#### Page

3/5

#### Initials


*[Handwritten initials]*

Fire resistance classification (vertical linear joint seal in a gypsum and / or stone wall)		
Bostik FP 401 applied at both faces connecting gypsum to gypsum		Bostik FP 401 applied at both faces connecting gypsum to stone
Wall thickness $\geq 75$ mm (see Figure 1)	Wall thickness $\geq 100$ mm (see Figure 2)	Wall thickness $\geq 100$ mm (see Figure 3)
EI 60 – V – X – F – W 10	EI 120 – V – X – F – W 10 E 180 – V – X – F – W 10	EI 120 – V – X – F – W 10 E 180 – V – X – F – W 10

E = Criterion integrity, I = Criterion insulation, V = Vertical application in a vertical wall, X = No movement applied, F = Splice applied in the field, W = Permitted width range in millimetres

The following conditions apply:

- the classifications are valid for linear joint seals in a wall with an orientation as mentioned (vertical);
- the linear joint seals in wall with a thickness  $\geq 100$  mm may connect on one side to any type of wall of aerated concrete (class G4/600 or heavier), concrete, block work, limestone or masonry with a minimal thickness as mentioned (100 mm). In practice, the metal profiles of the gypsum wall are mechanically fixed at a distance every 300 mm or less. Mechanically fixation of the metal profiles is mandatory;
- the linear joint seals may connect on both sided to a gypsum wall with a minimum thickness as mentioned (75 or 100 mm). In practice, the metal profiles of the gypsum wall are mechanically fixed at a distance every 300 mm or less. Mechanically fixation of the metal profiles is mandatory;
- the classifications are only valid for constructions shown in Figures 1 to 3;
- the surfaces of the material on which the sealant is applied are thoroughly cleaned and treated with primer when needed;
- the depth of FP 401 Fireseal Acrylic in a wall of 75 mm is 12.5 mm at both faces, representing the full thickness of the gypsum panel, see Figure 1. The depth of FP 401 Fireseal Acrylic in a wall of 100 mm is 10 mm at both faces. The rest of the cavity is filled up with suitable PE / PU backing material, see Figure 2 and 3;
- the allowed movement capability in practice is maximized to 7.5 %;
- the classifications are valid for both directions.




This summary consists out of 5 pages. The classification reports that form the basis for this summary are available for inspection at the client and are registered as YB 1567-1E-RA-002 dated June 24, 2015, YB 1692-1E-RA-002 dated September 16, 2016 and 18565C dated September 28, 2017.	Reference HL/RO//YC 2088-2E-RA-001 29 January 2020	Page 4/5	Initials <i>[Signature]</i>
---	--	-------------	--------------------------------

<b>Fire resistance classification</b> <b>(horizontal linear joint seals in a gypsum and stone wall)</b>
<b>Bostik FP 401 applied at both faces connecting gypsum to stone</b>
<b>Thickness wall <math>\geq 100</math> mm (see Figure 4)</b>
$EI\ 120 - T - X - F - W\ 10$ $E\ 180 - T - X - F - W\ 10$

E = Criterion integrity, I = Criterion insulation, T = Horizontal application in a vertical wall, X = No movement applied, F = Splice applied in the field, W = Permitted width range in millimetres

The following conditions apply:

- the classifications are valid for linear joint seals in a wall with an orientation as mentioned (horizontal);
- the linear joint seals in wall with a thickness  $\geq 100$  mm may connect on one side to any type of wall of aerated concrete (class G4/600 or heavier), concrete, block work, limestone or masonry with a minimal thickness as mentioned (100 mm). In practice, the metal profiles of the gypsum wall are mechanically fixed at a distance every 300 mm or less. Mechanically fixation of the metal profiles is mandatory;
- the linear joint seals may connect on the other side to a gypsum wall with a minimum thickness as mentioned (100 mm). In practice, the metal profiles of the gypsum wall are mechanically fixed at a distance every 300 mm or less. Mechanically fixation of the metal profiles is mandatory;
- the surfaces of the material on which FP 401 Fireseal Acrylic is applied are thoroughly cleaned and treated with Primer when needed;
- the use of suitable PE / PU backing material is mandatory;
- the depth of FP 401 Fireseal Acrylic in a wall of 100 mm is 10 mm at both faces. The rest of the cavity is filled up with suitable PE / PU backing material, see Figure 4;
- deformation of the linear joint seals in practice is maximized to 7.5 %;
- the classifications are valid for both directions.



This summary consists out of 5 pages. The classification reports that form the basis for this summary are available for inspection at the client and are registered as YB 1567-1E-RA-002 dated June 24, 2015, YB 1692-1E-RA-002 dated September 16, 2016 and 18565C dated September 28, 2017.

**Reference**  
HL/RO//YC 2088-2E-RA-001  
29 January 2020

**Page**  
5/5

**Initials**  
*[Signature]*