



# Kizen<sup>®</sup>

## PROS

### HOT MELT ADHESIVE

#### KEY FEATURES

- Strong bonds to a variety of difficult substrates
- Broad temperature performance range
- Designed to withstand board stock variation

#### DESCRIPTION

Kizen PROS is a robust case and carton sealing adhesive designed for an array of package types to keep your production lines moving and streamline your inventory. Able to reliably bond to the most challenging substrates, including coated, highly recycled or ones that vary over time, Kizen PROS eliminates pop-opens that cause downtime and field failures that increase cost. Additionally, its broad temperature range makes it suitable for many applications within case and carton sealing, consolidating SKUs while improving end-use performance.

Based on water-white technology, Kizen PROS also has outstanding thermal stability, aiding in low maintenance and char-free operations. Enhancing ease of use, it enables ultra-precise application and clean cut off, which makes it ideal for auto-feed, melt-on-demand systems.

#### PACKAGING

Available in mini-pastille form in 35 lb cartons and 1000 lb supersacks.

#### SHELF LIFE

Can be stored 730 days in a clean dry place, in its original package at an average temperature of 77°F (25°C) or below. Storage temperature should not exceed 100°F (38°C).

#### COUNTRY OF MANUFACTURE

United States

#### HEALTH AND SAFETY PRECAUTIONS

The Safety Data Sheet should be consulted for proper handling, clean up and spill containment before use. Keep containers covered to minimize contamination.

#### LIMITED WARRANTY

Limited Warranty found at [www.bostik.com/us](http://www.bostik.com/us) or call 800-726-7845. TO THE MAXIMUM EXTENT ALLOWED BY LAW, BOSTIK DISCLAIMS ALL OTHER EXPRESS OR IMPLIED WARRANTIES, INCLUDING WITHOUT LIMITATION WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. UNLESS OTHERWISE STATED IN THE LIMITED WARRANTY, THE SOLE REMEDY FOR BREACH OF WARRANTY IS REPLACEMENT OF THE PRODUCT OR REFUND OF THE BUYER'S



#### TYPICAL PROPERTIES\*

Description	Results
Thermosel Viscosity (Brookfield - ASTM D3236)	4,162 cP @ 275°F (135°C) 2,545 cP @ 300°F (149°C) 1,650 cP @ 325°F (163°C) 1,132 cP @ 350°F (177°C)
Softening Point (Ring and Ball Herzog - ASTM E28)	221°F (105°C)
Suggested Running Temperature	325 - 350°F (163 - 177°C)

PURCHASE PRICE. BOSTIK DISCLAIMS ANY LIABILITY FOR DIRECT, INCIDENTAL, CONSEQUENTIAL, OR SPECIAL DAMAGES TO THE MAXIMUM EXTENT ALLOWED BY LAW. DISCLAIMERS OF IMPLIED WARRANTIES MAY NOT BE APPLICABLE TO CERTAIN CLASSES OF BUYERS AND SOME STATES DO NOT ALLOW THE EXCLUSION OR LIMITATION OF INCIDENTAL OR CONSEQUENTIAL DAMAGES, SO THE ABOVE LIMITATIONS MAY NOT APPLY TO YOU. It is the buyer's obligation to test the suitability of the product for an intended use prior to using it. The Limited Warranty extends only to the original purchaser and is not transferable or assignable. Any claim for a defective product must be filed within 30 days of discovery of a problem, and must be submitted with written proof of purchase.

#### BOSTIK HOTLINE

Smart help  
**1-800-726-7845**

**Bostik, Inc.**  
11320 W Watertown Plank Road  
Wauwatosa, WI 53226  
[www.bostik.com/us](http://www.bostik.com/us)

This document supersedes all previously published literature.  
09.04.19

