



# Scree/master Epoxy Primer

## TWO COMPONENT WATER DISPERSIBLE PRIMER

Date: 16 September 2015

Fact Sheet No.: TDS00850

### YOUR SMART ADVANTAGES

- High specification primer
- Bonding agent
- Suitable as a barrier on calcium sulphate

### USES

Bostik Scree/master Epoxy Primer is a non-flammable, two component water dispersible epoxy primer containing exact quantities of resin and hardener, ready for mixing together. Curing is by chemical reaction, producing a semi-gloss film finish. The primer is coloured to identify coated areas.

Bostik Scree/master Epoxy Primer can be used as a primer/bonding agent prior to the application of any of the Bostik Scree/master range of smoothing compounds. It can be used on all smooth and dense surfaces, power floated concrete, ceramic tiles, quarry tiles, terrazzo, rigid metal, asphalt and surface membranes.

Bostik Scree/master Epoxy Primer may be used as a barrier primer on anhydrite (calcium sulphate) screeds prior to application of cementitious materials. For further information please contact Flooring Technical Services.

### PRODUCT CHARACTERISTICS

Colour	Opaque White
Form	Liquid paste
Composition	Resin mix
Specific Gravity	1.0 approx.
Product Code	30811706 6KG
Storage/Shelf Life	Store for up to 12 months from date of manufacture when stored in original, unopened packaging under cool, dry conditions at a minimum temperature of +5°C. Protect from frost.

### TYPICAL PERFORMANCE DATA (Approx.)

Coverage	50 - 60 m <sup>2</sup> (on smooth surfaces)
Application Temperature	+5°C to +40°C
Drying Times	Overnight (13°C or above)
Flashpoint	Part A: > 150°C Part B: Non flammable

### DIRECTIONS FOR USE

IMPORTANT: Before using Bostik Scree/master Epoxy Primer refer to the relevant Health and Safety Data Sheet, available at [www.bostik.co.uk](http://www.bostik.co.uk).

All phases of the installation should comply with the latest editions of the following standards:

BS 8102 Code of Practice for protection of buildings against water from the ground.

BS 8203 Code of Practice for installation of resilient floor coverings.

BS 5325 Code of Practice for installation of textile floor coverings.

### PREPARATION

#### Subfloor:

1. The sub-floor must be clean, structurally sound, dry and free from all contaminants, including surface hardeners and additives that may hinder adhesion. It should also have an effective structural damp-proof membrane and be suitably dry.
2. The only British Standard approved test for dryness is by properly calibrated and insulated hygrometer giving a reading less than 75% RH.
3. Where this has not been achieved the use of a suitable Bostik Scree/master surface membrane will suppress residual moisture in a power floated concrete slab or sand/cement screed provided that a base DPM has been incorporated. Please refer to the relevant data sheets for full information.



FM 01696  
BS EN ISO 9001:2008

Bostik Limited, Common Road, Stafford, ST16 3EH, UK. Tel: +44 (0) 1785 272625 [www.bostik.co.uk](http://www.bostik.co.uk)

Bostik, Evo-Stik & Sealocrete are registered trademarks of Bostik Ltd.

## MIXING

4. Mix the two components together, adding hardener B to resin A until a completely uniform colour is obtained, using an electric drill and propeller blade.
5. The components should not be mixed together until application is ready to start, and should be applied as soon as mixing has been completed. Any unmixed material will not harden.

## APPLICATION

6. The mixed material should be applied by brush or lambswool roller ensuring that the primer is well worked into the surface.
7. As soon as it has become transparent, i.e. when the primer is tacky but not wet, the appropriate Bostik Screedmaster Smoothing Compound may be applied. Keep the area dust free until the smoothing compound is applied.
8. For best results leave to dry for 12 hours. If the primed surface is left for longer than 24 hours it may lose its tack and may require a repeat application.

## DRYING CONDITIONS

9. Bostik Screedmaster Epoxy Primer will cure between 6 to 24 hours of application depending upon substrate, temperature and ventilation. Under cold conditions the curing rate will be considerably slower. The use of warm air blowers can assist curing.

**Note:** Fuel burning space heaters produce water vapour which will increase humidity and extend curing time. Electric fans, where permissible, are more effective.

## CLEANING

10. Clean tools and equipment immediately after use with clean water. Use white spirit or dispose of equipment if the material has dried.

## PRECAUTIONS IN USE

For any application not covered please contact Technical Services on +44 (0)1785 272625 or visit [www.bostik.co.uk](http://www.bostik.co.uk) for advice.

Recommendations and suggestions are for guidance only, since conditions of use are completely beyond our control.

For health and safety instruction, first aid measures and spillage and disposal instructions, see separate Health and Safety Data Sheet for Bostik Screedmaster Epoxy Primer, available at [www.bostik.co.uk](http://www.bostik.co.uk).

BOSTIK HOTLINE

Smart help +44 (0) 1785 272625



FM 01696  
BS EN ISO 9001:2008

Bostik Limited, Common Road, Stafford, ST16 3EH, UK. Tel: +44 (0) 1785 272625 [www.bostik.co.uk](http://www.bostik.co.uk)  
Bostik, Evo-Stik & Sealocrete are registered trademarks of Bostik Ltd.

This disclaimer is issued by Bostik Limited ("the Company") and applies to the use of any products supplied by the Company ("the Products") displayed on this Technical Data Sheet ("TDS"). Please read this disclaimer carefully before using any of the Products. Using this TDS and/or the Product constitutes your acceptance of this disclaimer. Its contents shall prevail over any directions of use and any disclaimer and/or exclusion or limitation of liability of the Company which may appear on the packaging of the Products.

This disclaimer sets out the entire financial liability of the Company (including any liability for the acts or omissions of its employees, agents and sub-contractors) to any user of the Products ("Product User") in respect of any use made or resale by the Product User, of any of the Products in this TDS.

This disclaimer does not affect the Company's liability for death or personal injury arising from the Company's negligence in respect of the Products, nor its liability for fraud, or fraudulent misrepresentation, nor any other liability which cannot be excluded or limited under applicable law.

The Company's total liability however arising and whether caused by tort (including negligence and breach of statutory duty), breach of contract or otherwise, arising in connection with the use made or resale by the Product User of any of the Products in this TDS shall be limited to the price paid for the Product by the Product User.

The Company shall not be liable to the Product User for any pure economic loss, loss of profit, loss of business, depletion of goodwill or otherwise, in each case whether direct, indirect or consequential, or any claims (including in respect of personal injury insofar as not caused by the Company's negligence) for consequential compensation whatsoever (howsoever caused) which arise out of or in connection with the use made or resale by the Product User of any of the Products in this TDS.

The Company shall not be liable to the Product User in relation to any loss for any use which is inappropriate or use which is otherwise than in accordance with the relevant instructions for use of the Products in this TDS or on the Product. Product Users are advised to confirm the suitability of the Products by their own tests.

This TDS covers just one of a large range of products supplied by the Company.

Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This TDS supersedes all previous TDSs relating to the Products, and users of it must ensure that it is the current issue. Destroy all previous TDS, and if in any doubt, contact the Company, quoting the code number in the top right hand corner on the front of this document.

Sales	Tel: 0844 371 1192	Fax: 01785 241818	<a href="mailto:customer.service@bostik.com">customer.service@bostik.com</a>
Technical Advice	Tel: 0844 371 1197	Fax: 01785 272867	<a href="mailto:technical.service@bostik.com">technical.service@bostik.com</a>
Technical Data & COSHH (MSDS) Data Sheets	Tel: 01785 272625	Fax: 01785 212962	<a href="mailto:stafford.gatehouse@bostik.com">stafford.gatehouse@bostik.com</a>



FM 01696  
BS EN ISO 9001:2008

Bostik Limited, Common Road, Stafford, ST16 3EH, UK. Tel: +44 (0) 1785 272625 [www.bostik.co.uk](http://www.bostik.co.uk)  
Bostik, Evo-Stik & Sealocrete are registered trademarks of Bostik Ltd.