

# CemenTech C2 Combi

## TWO-COMPONENT SEMI-FLEXIBLE WATERPROOFING MORTAR

### SMART ADVANTAGES

- Flexible waterproofing
- Suitable for use in potable water
- Economic

### PRODUCT DESCRIPTION

It is cement-based, two-component, semi flexible sealing slurry that is reinforced by polymeric additives and used in the solution of waterproofing problems. It can be from the positive side only.

### APPLICATION AREAS

- Interiors and exteriors
- From positive side only,
- Both vertical and horizontal,
- In wet volumes (eg.WC, bathroom, kitchen),
- In continuously wet, humid and damp areas such as balcony, terrace and cellar,
- Water tanks, pools, reservoirs and storage tanks,
- In foundations, basement walls, underground and surface construction works,
- In bridges and sustaining walls.

### FEATURES

- Suitable for brush or spray use
- Resistant to heavy weather conditions.
- High adherence; strongly adheres to surfaces.
- Non-corrosive for steel and reinforcements
- High abrasion resistance.
- Flexible.
- Suitable for direct contact with freshwater, without any coverings.

### PREPARATION OF THE SUBSTRATE

- The surfaces to be coated should be free of adhesive preventive foreign substances such as dust, dirt, mould oil, paint etc.; residues and wastes like cement, plaster and concrete should also be removed.
- The sub-surfaces that are not strong enough to bear their own weight e.g. cracked plasters, weak surfaces, or residues of moss should be cleaned from the application surface.

### APPLICATION

- Powder form Bostik CemenTech C2 Combi Waterproofing Mortar should be poured slowly on liquid component (5 kg) that has been put into a clean container, and should be mixed by means of a mixer with low cycle until a cluster-free mixture is obtained. Mixture duration should be minimum 5 minutes. The mixture obtained at the end of the process should be rested for 3 minutes and mixed again until it becomes homogenous for 2 minutes.
- Bostik CemenTech C2 Combi Waterproofing Mortar emulsion should be shaken well before use.
- Application should be at least two layers thick. After applying the first layer, at least 4-6 hours should be rested and second layer should be applied before waiting period exceeds 24 hours.
- The cracks that might be formed in the event of application to very wide surfaces should be prevented by means of application by leaving joints. Joints should be filled with flexible filling material.
- On the moving grounds that have cracking risk, Bostik FlexMesh net can be applied as an intermediate layer



### TECHNICAL DATA

Colour	Grey
Applicable thickness (mm)	Max 6
Recommended applicable thickness (mm)	2
Dry unit volume weight (kg / lt)	1,3 ± 0,2
Wet unit volume weight (kg / lt)	1,8 ± 0,2
Waiting time in container (min)	~ 30
Drying time (hour)	~ 24
Permeability to water-vapour (m)	Class I ; Sd <5
Adhesion strength (28 days)	> 2 (N / mm <sup>2</sup> )
Capillary water absorption (<0,1kg/m <sup>2</sup> .h0,5)	< 0,1
Special mixture emulsion amount (for 20 kg powder component)	5 kg (white-coloured liquid emulsion)
Application temperature	Between +5°C and +35°C
Resistance of hardened coating	Between -25°C and +80°C

Technical data are approximately provided according to a temperature of + 23°C and a relative humidity of 50%.

between the application with the aim of forming a water isolation layer which is more flexible in order to meet the tensile stress.

- It shouldn't be applied to hot or frozen surfaces directly.

### APPLICATION WITH MACHINE

CemenTech C2 Combi is suitable for use with sprayable machine. Consult Bostik Technical Service for machine use.

### AFTER APPLICATION

- Freshly applied surfaces should be protected against direct sun light, strong air stream, high air temperature (above +35°C), rain and frost in the initial days (at least 5 days).

- Any kind of plaster application on the application surface or ceramic tiling works should be performed 3 days later.
- To obtain the recommended long term technical performance of the product, after the completion of the all application, the application and/or work should be covered and protected with a suitable coating or covering (plaster, screed, ceramic, tile etc...) as early as possible (depending on the product's drying time within 3-7 days).

#### COVERAGE

Approximately 1,5 – 2,0 kg/m<sup>2</sup> per each 1 mm thickness.  
Coverage amounts are theoretical values and it is recommended that coverage-controlled sample application is carried out before application.

#### PACKAGE

Powder component in 20 kg craft bag, 60 sets in 1 palette  
Liquid component in 5 kg plastic drum.

#### STORAGE

- Dry mortar bags should be protected for water, frost and adverse weather conditions.
- They should be kept dry and cool on wooden pallets at between +10°C and +25°C in moisture free conditions.
- The torn and opened products should be closed immediately and consumed first.
- Maximum 8 bags should be stocked on each other.
- Shelf life is maximum 12 months conditional to complying with the abovementioned storage conditions.


#### HEALTH AND SAFETY INFORMATION

For health and safety instruction, first aid measures and spillage and disposal instructions, see separate Safety Data Sheet.



**BOSTIK HOTLINE**

**Smart help**  
**444 10 99**



**Bostik Kimya Sanayi ve Ticaret A.Ş.**

Mecidiyeköy Mh. Oğuz Sk. RönesansBiz Plaza N: 4A/7

Zemin Kat 34381 Şişli, İstanbul

E-mail: [info@bostik.com.tr](mailto:info@bostik.com.tr)

an Arkema company

[www.bostik.com.tr](http://www.bostik.com.tr)

Warning: Bostik is only responsible for the product quality and cannot be held responsible for its mis-use except for the recommendations regarding where and/or how the product shall be used. It is not possible to give a guarantee for the results of operations for individual cases, due to multiplicity of possible uses and storage and processing conditions of the product, which are not under our control. Where necessary, the user should make their own tests. Due to local regulations, product performance may vary from country to country. This technical bulletin hereby is valid until it is renewed. BOSTIK's right to amend the products in accordance with technical developments is reserved. In cases concerning the safety of the products, the material safety data sheet (SDS) containing this information should be consulted.