

MAXI BOND EXPRESS

Grab adhesive

PRODUCT DESCRIPTION

Maxi Bond Xpress is the ideal grab adhesive when you are short of time. Apply and load within 15 minutes. Maxi Bond Xpress takes up unevenness in the substrate to ensure that the entire adhesive surface helps to bear load. Maxi Bond Xpress gives the performance of a superglue, but it is easy to apply and environment-friendly, with no solvents. Remains permanently flexible even after hardening, making it vibration damping. Maxi Bond Xpress is an SMP-based grab adhesive hardened by air humidity. It hardens without shrinking to a flexible adhesive grout.

Adhesion performance

Final tensile strength: 280 ton/m2 Initial tensile strength: 200 kg/m2 Final shear strength: 190 ton/m2

Mounting hook/wall mounted; 100 kg/m2

Strength build-up

Wall mounted after 15 min. : 300 kg/m2
Wall mounted after 30 min. : over 600 kg/m2
Full adhesive strength achieved within 3-5 days

AREA OF USAGE

Maxi Bond Xpress is used to glue most material types on wet and dry substrates, indoors and outdoors when a resistant and flexible adhesive is needed. Use when immediate loading of the glued joint is needed or when the glued object has to be moved within a short space of time. Adheres in principle to all building materials such as: wood, metals (painted and untreated), concrete, metal, ceramics, glass, stone, marble and plastic (not PE/PP/PFTE). Adheres two non-absorbent surfaces. Best result is when at least one surface is absorbent.

WORKING INSTRUCTION

Surfaces must be clean, dry and non-greasy. Apply to one surface using a cartridge extruder. Apply adhesive strings 5 mm wide in rows 30 mm apart. Press together for 10 seconds to a layer of around 2-3 mm. Strength build-up in the adhesive starts after a few minutes. The glued object can usually be used without impact or fixing subsequently (providing the weight does not initially exceed 100 kg per square meter glue surface). Final adhesive strength is achieved after 3-5 days (190 ton/m2). Moisture can be added when gluing dense materials to accelerate hardening. E.g. by careful spraying with water. The strength of a grout can never be higher than the bearing capacity of the substrate. Always test-adhere plaster or rubber. The product will not adhere to PP/PE/PTFE plastics.

SAFETY

In accordance with the law, the product contents are not a health or fire risk. The product does not contain biocides. For more details, see safety data sheet.

TECHNICAL DATA

Properties before application	
Consistency	Thixotropic, supple
	paste
Working temperature	5 deg to 35 deg
Amount to use	Glue string 5 mm dia.
	15 m/l
Fire hazard	No
Application	Hand extruder
Shelf life	Min. 12 months in
	unopened packaging.
	Store in a dry, cool
	place.
Density	1.50 g/cm3
·	s after use
Hardening system	Hardened by air
<i>y = 1,222</i>	humidity
Skin formation	5-10 min
Hardness	65 Shore A
Adhesion growth	Full adhesion achieved
Admesion grower	after 3-5 days,
	depending on
	construction,
	temperature and
	humidity
Tomporatura	Permanently elastic
Temperature resistance	-
	-40 deg to 100 deg
Ageing resistance	Very good
Cleaning agent	Non-hardened
	adhesive can be
	removed with
	Methylated sppirit (or
	white spirit). Remove
	dried adhesive
	mechanically.
Chemical resistance	Good when in contact
	with diluted acids, lye
	and solvents
Overpainting	Yes, with dispersion
	paints. Painting using
	alkyd and solvent-
	based paints can
	disrupt and extend
	drying time. Test
	painting is
	recommended.

CONTACT US

Bostik LLC

ООО «БОСТИК» 127018 г. Москва, ул. Двинцев, д.12,

Fax: (495) 787 31 72

корп.1

Phone: (495) 787 31 71 E-mail: inforu@bostik.com

www.bostik.ru

Disclaimer: The technical data we present, as well as our instructions are recommendations are all based on a variety of tests and our experience. They are intended to help the user to find the most suitable working method and get the best possible results. Since the users working conditions is beyond our control, we cannot accept any responsibility for the results obtained by the product.

BOSTIK HOTLINE

Smart help +7 495 787 31 71

