



MSP 133

MS Polymer bonding putty. Special for tiles.

ADVANTAGES

- Flexible collage.
- Fast setting.
- Excellent adhesion, including on wet surfaces (unsaturated and non-dripping).
- Contains no solvents or isocyanates
- Good resistance to weather and UV rays.
- Easy to extrude.
- Outdoor use.

PRODUCT USE

Especially for tile bonding: channel tiles and silicone tiles.

Collage of tiles between them, on fiber cement plates, on battens and battens.

Complement of fixing the interlocking tiles.

TECHNICAL CHARACTERISTICS

Color: tile

Polymerization rate: 3 mm per 24 hours at 23°C

Dry extract: 100%

Temperature of implementation: + 5°C to + 23°C

Operating temperature: - 20°C to + 70°C

Maximum open time: 15 minutes

Final take: about 24 hours

Performances

Shore hardness A: 55

Tensile strength on tile support according to standard NF P 85-611: > 0.6 MPa

Complies with standard NF P 85-610: Sealants for tile bonding.

PREPARATION SURFACES

Surfaces should be sound, dust-free, free of grease and any loose parts.

Laying tiles of current on:

- tile support plates
- wooden and wooden battens

APPLICATION

Simple gluing using a manual or pneumatic gun, by removing blocks of the size of a hazelnut.

Assemble the elements immediately, taking care to crush the glue pads. Do not handle the assembly

or do not stress the bonding for the next 12 hours.

CLEANING

- Fresh product: with cleaning wipes or SOLVENT AK.
- Dry product: by scratching.

CONSUMMATION

4 to 6 m² according to surface so 10 to 15 tiles.

STORAGE

18 months in closed original packaging, stored in a dry room between + 5 ° C and + 30 ° C

SECURITY

For more details, consult the safety data sheet on the base www.quick-fds.com or ask us for a copy by fax.

The implementation recommendations are defined in relation to standards of use. They must be respected, but do not dispense with prior testing, especially in the case of first use and /

or particular constraints of the support, site or environment. Consult our safety data sheets for precautions for use.

CONDITIONNING

Code	Packaging	Quantity per pallet	Barcode
30135103	Brun - Car-touche 290 ml	12	3549210031345
30135104	Brun - Poche 400 ml	12	3549210031352

BOSTIK HOTLINE

Smart help +7 495 787 31 71



Bostik LLC

ООО «БОСТИК» 127018 г. Москва, ул. Двинцев, д.12, корп.1
Phone : (495) 787 31 71 Fax :(495) 787 31 72
E-mail : inforu@bostik.com
www.bostik.ru