



Bostik S/A  
 D319 Coubert  
 77257 Brie Comte Robert cedex  
 France

Eurofins Product Testing A/S  
 Smedeskovvej 38  
 DK-8464 Galten  
 Denmark

Tel. +45 70 22 42 76  
 Fax +45 70 22 42 75  
 voc@eurofins.dk  
 www.eurofins.com/product-emissions

Date  
 6 August 2013  
 Our ref.  
 G23494

## Test Report – LEED 2009 EQ c4.1, SCAQMD rule 1168 (2005)

### Sample material

Sample identification	<b>Power Elastic</b>
Product type	Multipurpose construction adhesive
Product data, according to manufacturer	Density: 1.3 g/ml at 20 °C ** Water content: 325 g/l** Exempt compounds: none ***
Date received	12.07.2013
Analytical period	01.08.2013

### Methods applied

Method	Principle	Parameter	Detection limit	Uncertainty, U <sub>m</sub> (%)
LEED 2009 EQ c4.1 ASTM D 2369 - 10	Gravimetric	Total Volatiles, SCAQMD rule 304	1 g/l	10 %
Volatile content of the sample was determined gravimetrically by heating up to 110 °C during 60 minutes. The result is the average of double testing. The result was calculated as: $([g \text{ all volatiles}] - [g \text{ water}] - [g \text{ exempt compounds}]) / ([l \text{ material}] - [l \text{ water}] - [l \text{ exempt compounds}])$				

U<sub>m</sub> (%): The expanded uncertainty U<sub>m</sub> is equal to 2 x RSD%, see also [www.eurofins.dk/uncertainty](http://www.eurofins.dk/uncertainty).

### Analytical results

	Solid content, % mass	Water content, % mass	Exempt compounds, % mass	VOC less water less exempt compounds, g/l	VOC limit g/l
<b>Power Elastic</b>	74.5	25 **	0***	9	70 *

\* VOC limit for "Multipurpose construction adhesive"

\*\* Given by the client

\*\*\* No information about exempt compounds. Set to zero.

Eurofins Product Testing A/S

Thomas Neuhaus  
 Head of product emission test centre