



# Prep P

### Product

Simson Prep P is a liquid pretreatment for improving the adhesion of several Simson products on porous substrates. Consult the Technical Data Sheet of the particular product.

### Applications

- Pretreatment of mineral substrates, such as brickwork, concrete and lightweight concrete.
- Pretreatment of wooden substrates (such as seams in teakwood ship decks).

### Method of use

Substrates should be clean, firm, dry and free of dust and grease. Substrates can be cleaned with Simson Cleaner E. Keep the packaging well closed until the moment of use. Do not use Prep P direct from the original packaging. Pour as much Prep P into a clean glass or tin as can be used within 30 minutes and immediately close the original tin firmly.

Always use a clean brush for the application of Prep P. Apply Prep P to the adhesion surface only in such a way, that Prep P forms a continuous coat or film. Prep P should be applied in a thin coat. Do not apply Prep P on already dried product. The application temperature can vary from +5°C till +30°C.

The minimum drying time of Prep P is 60 minutes.

Best results are obtained when the bonding/sealing is realised within 6 hours after applying Prep P. Therefore do not apply more Prep P than can be sealed within 6 hours. Avoid contact with the cleaned and pretreated surfaces because greasy fingers can cause bad adhesion. Also, condensation can negatively influence the adhesion. It is not recommended to use Prep P and to seal the joints during very high air humidity, for example during fog.



## ADHESIVES AND SEALANTS

# Prep P

### Technical data

Dry contents	50%
Specific gravity	1.06 g/ml
Flashpoint	+21°C
Drying time	> 60 minutes
Colour	light yellow/transparant
Packaging	500 ml tin

### Coverage

The coverage depends on the type of substrate and will be between 8 - 10 m<sup>2</sup> per liter.

### Storage stability

Prep P can be stored for 12 months in an original, unopened container in a dry place at temperatures between +5°C and +30°C.

### Further information

The following publication is available on request:

- Material Safety Data Sheets (MSDS)

#### UK

Bostik Ltd.  
Stafford  
Tel: +44 (0) 1785 27 27 27  
Fax: +44 (0) 1785 22 26 65

#### France

Bostik S.A.  
Paris  
Tel: +33 (0) 1 74 96 91 18  
Fax: +33 (0) 1 47 96 94 20

#### Germany

Bostik GmbH  
Borgholzhausen  
Tel: +49 (0) 54 25/8 01-0  
Fax: +49 (0) 54 25/80 11 40

#### The Netherlands

Bostik B.V.  
's-Hertogenbosch  
Tel: +31 (0) 73 6 244 244  
Fax: +31 (0) 73 6 244 344

For more Bostik locations please consult [www.bostik.com](http://www.bostik.com)

**Bostik**  
The Adhesive Company

All figures, recommendations and safety precautions are based on thorough investigations and our actual experience and are without engagement. Although the documentation has been set up with most carefulness, we do not accept any responsibility for mistakes, inaccuracies or printer's errors. We reserve the right to adjust the product, whenever we feel necessary. Because the design, the quality of the substrate and the conditions during application fall beyond our control, no responsibility for executed works can be accepted on the basis of this documentation. We therefore recommend to carry out own tests on the spot. All our sales and deliveries are subject to our general sales- and delivery conditions.