

# 8015 COMBI LIGHT TECHNICAL DATASHEET

Version: 2018-06-27

## **PRODUCT DESCRIPTION**

8015 Combi Light is a light fix for ceramic floor tiles, mosaics and natural stone. The fix can be used indoors in try and wet rooms. The fix can be used as a ceramic tile adhesive on floors and walls.

## **AREA OF USAGE**

8015 Combi Light can be used on many different surfaces such as concrete, floor screed, rendered surfaces and plasterboard. The fix can also be used for minor repairs (max. 5 mm). The fix also works together with underfloor heating. Large format floor tiles must be double-glued.

#### **WORKING INSTRUCTION**

The substrate must be solid, dry, and withstand at least +10C. More absorbent substrates should be primed before laying. Add approx. 4.8 litres of water to 15 kg powder. Stir for 2 min. to achieve a lump. free consistency, let sit for 2 min. and stir again. Application time approx. 3 hours. Spread and work the ceramic tile adhesive into the substrate using the smooth side of the tiling/ notched trowel and then smooth it off using the serrated side. Select the correct size of the tiling/notched trowel based on the size of the ceramic floor tiles. Do not spread out onto a larger fix surface than what you can manage to lay in 10 min. Press and rotate the floor tiles in place. Ensure good backfilling of the floor tiles during application by picking up a floor tile now and then for inspection, 95 % coating of the ceramic floor tile adhesive is applied both on the substrate and the back side of the floor tiles larger than 25 x 25 cm should be double-glued (ceramic tile adhesive is applied both on the substrate and the back side of the floor tiles). Remove the ceramic tile adhesive that penetrates up between the floor tiles. Walls can be seamed after approx. 12 hours and floors after approx. 24 hours.

#### SAFETY

The product contains cement and can irritate skin. For additional information, read the safety data sheet.



**Bostik AB**, Strandbadsvägen 22, Box 903, SE-251 09 Helsingborg Tlf: +46 (0)42-19 50 00, Fax: +46 (0)42 19 50 21, **www.bostik.se** 

Disclaimer: The technical data we present, as well as our instructions and recommendations are all based on a variety of tests and our experience. They are intended to help the user to find the most suitable working method and get the best possible results. Since the users working conditions is beyond our control, we cannot accept any responsibility for the results obtained by the product.

# **TECHNICAL DATA**

Properties before application	
Adhesive	Special Cement
Aggregate	Light filler
Colour	Light grey
Working temp.	Min. +10C, Max +25C
Water consumption	Approx. 4.8 litre/15 kg
Consumption	1.2 – 3.5 kg/m2
Usage time	approx. 3 hours
Groutable	Wall:12 hours, Floor: 24 hours
Full pressure	approx. 7 days
Cleaning of tools	lukewarm water
Shelf life	12 months dry, cool and in an unopened package

**CONTACT US** 

# TEL +46 (0)42-19 50 00 info.se@bostik.com

Disclaimer: The technical data we present, as well as our instructions and recommendations are all based on a variety of tests and our experience. They are intended to help the user to find the most suitable working method and get the best possible results. Since the users working conditions is beyond our control, we cannot accept any responsibility for the results obtained by the product.

**Bostik AB**, Strandbadsvägen 22, Box 903, SE-251 09 Helsingborg Tlf: +46 (0)42-19 50 00, Fax: +46 (0)42 19 50 21, www.bostik.se