

# Kitchen & Bathroom

# **PREMIUM SILICONE ACETIC CURE**

# DESCRIPTION

Bostik Kitchen & Bathroom Silicone is an acetic (acetoxy) curing sealant. It is specially formulated to resist mildew when exposed to prolonged hot and humid environments.

# FEATURES AND BENEFITS

- Flexible Silicone Rubber
- Anti Fungal (fungicide added).
- Joint movement capabilities ± 25%
- Maintains a Waterproof flexible joint.
- Acetoxy silicones stay clearer than oxime silicones over time.
- Excellent UV resistance

#### **RECOMMENDED USES**

- Sealing in wet areas
- Bathtubs and showers
- Glass to Glass screens
- Ceramic Tile
- Most laminated surfaces
- Fibre glass
- Rimless sinks
- Bathroom & Kitchen fixtures
- Vitreous toilet pans..

(note: not to be used on marble, granitite or stone).

# **APPLICATION PREPARATION**

#### Surface Preparation

Surfaces to be sealed must be clean, dry and free of wax, grease, cutting oils or any loose of flaking materials. Use the two-wipe process for impervious substrates. Ensure the cloths are clean and changed frequently, and use a suitable cleaner/solvent such as 100% White Spirits. To achieve satisfactory adhesion a primer may be required for some substrates. Consult Bostik for more information.

#### Application

- Use masking tape each side of joint to simplify clean up, to protect surfaces and to ensure a neat job.
- Use a closed cell polyethylene-backing rod 25% larger than the joint width, to control the depth of the joint where required.
- Cut nozzle at 45° angle to desired thickness. Cut



opening on cartridge and fix nozzle. Insert cartridge into caulking gun.

- Hold gun at 45° angle with nozzle in contact with both sides of joint. Apply by pushing sealant ahead of nozzle, thus ensuring sealant is pushed firmly into place.
- Tool off / smooth before skin forms (within 5 minutes). Remove excess sealant immediately with a cloth dampened with mineral turpentine. If used, remove masking tape before skinning has started. (Cured sealant can be removed by trimming with a sharp blade).
- The incompatibility of some substrates may cause discoloration of sealant, poor sealant adhesion or long term degradation of the sealant. Always carry out compatibility tests where contact with potentially incompatible materials occurs.

# LIMITATIONS

Bostik Kitchen & Bathroom Acetic Cure is **NOT** suitable for use in the following applications:

- Totally confined spaces as the sealant requires atmospheric humidity to cure, it will not cure where it does not have access to atmospheric humidity.
- Aquariums
- Adhering Mirrors (Bostik V60 can be used test first)
- Structural Glazing (Bostik V70 refer to Bostik guide lines first).

- Composite panels- (Bostik recommends Bostik 5CLMsubject to test first)
- Under Water Applications (including swimming pools subject to substrate). Refer to Bostik for these applicationst
- Below Grade Applications
- All Stone (We recommend the completion of a stain testing program before using any sealant on stone) Bostik 5CLM is recommended for marble, granite (after stain test).
- Horizontal walkways and trafficable areas
- Polycarbonate sheeting
- Sealant may discolour copper & brass.
- Do not clean or treat the sealant with materials, cleaning agents or solvents that may affect or discolour the sealant, particularly during product curing.
- This silicone is not paintable.
- Not recommended for marble, granite or stone
- Not recommended for concrete, light metal in roof gutter applications (Colorbond etc)

#### **IMPORTANT NOTES**

Chemical exposure to certain agents such as chlorinated cleaning solutions (ie bleach), chemical solvents, and the fumes of some paints (enamel or solvent – containing types where not fully dried), may cause the sealant to display a slight colour shift.

The silicone sealant must be kept clean at all times when used around the shower or bath; (sealant must be regularly cleaned and kept dry) or mould growth can start over the top of the sealant.

#### TIP:

For granite, marble or porous masonry and stone materials, Bostik Plumb Seal is recommended. Plumb Seal is also paintable

#### COVERAGE

Approximately 16 lineal metres per 300ml cartridge based on an average joint size of 6 mm depth and 3 mm width.

#### **SETTING TIME**

Sealant will skin over within 5 minutes (subject to humidity in air – lower the humidity longer time to skin over and cure, high humidity shorter skin and cure time).

#### DISCLAIMER:

The information in this Technical Data Sheet is intended for the assistance of users and is of a general nature. It reflects the extent of our knowledge and experience of our products and is based on tests which we believe to be reliable. However, no guarantee of accuracy can be given due to the wide range of surfaces, environmental and field conditions and variations encountered in raw materials, manufacturing equipment and methods at the place where the work is performed. Some of these will be beyond our knowledge and control. Users are asked to make sure that the TDS in their possession is the latest issue. Likewise, we recommend users carry out their own tests to determine the suitability of the product for their particular purposes.

Any claim for a defective product must be filed within 30 days of discovery of a problem and must be submitted with written proof of purchase. Claims are not transferrable or assignable and extend only to the original purchaser/user. Bostik reserves the right to inspect alleged failure and no responsibility will be accepted unless Bostik is given the opportunity to do so. Bostik limits its liability to the replacement of the product/s proven faulty.

**BOSTIK PHILIPPINES, INC.** 

35/F Penthouse Raffles Corporate Center F. Ortigas Jr. Road, Ortigas Business Center Pasig City Philippines Tel No: +63 2 900 5856 | Fax: +63 2 900 5616

PROPERTIES			
Colours	Translucent /White	Hardness Shore A (ASTM D-2440)	20
Tooling / Skin Time	5 Minutes approx.	Tensile Strength (ASTM D-412)	1.3-1.5 MPa
Tack Free Time	30 minutes approx.	Sag, Slump	0.1 inches max
Cure Time (To 10mm depth @ 23ºC & 50% RH)	5-7 days	Specific Gravity	1.03
Application Range	10ºC to +40ºC	Cure Method	Acetoxy
Performance Range	-62ºC to +180ºC	UV and Ozone resistance	Excellent

# STORAGE & SHELF LIFE

Store between 5°C-25°C in a dry, ventilated area, out of direct sunlight

Shelf life is 18 months in unopened container.

# PACKAGING

300ml cartridges

#### SAFETY PRECAUTIONS

#### CAUTION:

Full product safety information required for safe use is not included in this data sheet. Before handling, read the separate Material Safety Data Sheet (MSDS) and packaging for safe use. Always ready the Technical Data Sheet and Material Safety Data Sheet (MSDS) before opening or using this product.

In case of product emergency refer to product labelling or MSDS and contact phone numbers. A copy of the product MSDS is available from Bostik or its distributors.

#### FIRST AID:

If poisoning occurs, contact a Doctor or Poisons Information Centre (Phone Australia 131 126; New Zealand 0800 764 766)

EMERGENCY INFORMATION: 1800 033 111 (ALL HOURS)

# **BOSTIK HOTLINE**

Smart help +63 2 900 5656