

BOSTIK S.A.
420 rue d'Estienne d'Orves
92700 Colombes
FRANCE

Eurofins Product Testing A/S
Smedskovvej 38
8464 Galten
Denmark

CustomerSupport@eurofins.com
www.eurofins.com/VOC-testing

VOC TEST REPORT

VOC Content

26 May 2020

1 Sample Information

Sample name	STIX P956 2K
Sample no.	392-2018-00470106
Production date	19-06-2018
Batch No.	FR18A78144
Sample reception	10/08/2018

2 Brief Evaluation of the Results

Regulation or protocol	Conclusion	Version of regulation or protocol
SCAQMD Rule 1168	Pass	January 2005
LEED v4 (VOC Content)	Pass	

Full details based on the testing and direct comparison with limit values are available in the following pages



Rasmus Stengaard Christensen
Analytical Service Manager, MSc in Chemistry



Morten Sielemann
Analytical Chemist

3 Applied Test Methods

3.1 General Test References

Regulation, protocol or standard	Scope	Version
SCAQMD Rule 1168	Adhesive and sealant applications	January 2005

3.2 Specific Laboratory Sampling and Analyses

Test	Regulation, protocol or standard	Version	Internal SOP	Limit of detection [g/L]	Uncertainty Um _a
Solids Content	ASTM D2369	2010	71 M 544830	1	10
VOC	ASTM D2369	2010	71 M 544830	1	10

4 Results

	Remarks on the test results	Results	Unit
Density *	Supplied by the Customer	1.40	g/mL
Water Content *	Supplied by the Customer	0	% (w/w)
Exempt compounds *	Assumed to be 0	0	% (w/w)
Solids Content	Tested by the lab	100	% (w/w)
VOC content (less water)	Calculated based on the results above	< 1	g/L
VOC content (less water)	Calculated based on the results above	< 0.1	% (w/w)

4.1 Comparison with Limit Values of VOC Content (less Water)

Parameter	Results [g/L]	Product type	Regulation or protocol	VOC limit [g/L]
VOC content	< 1	Indoor Carpet Adhesive	SCAQMD Rule 1168	50

5 Appendices

5.1 How to Understand the Results

5.1.1 Acronyms Used in the Report

- < Means less than
- > Means bigger than
- * Not a part of our accreditation
- ⌘ Please see section regarding uncertainty in the Appendices.
- 1 Analysed by another Eurofins laboratory

5.2 Description of VOC Content Test

5.2.1 Testing of VOC

Volatile content of the sample was determined gravimetrically by heating to 110 °C in 60 minutes. Multicomponent products are mixed according to the manufacturer's instructions and allowed to cure before heating.

The result is the average of two replicates. The result was calculated as:

$$VOC = \frac{([g \text{ All Volatiles}] - [g \text{ Water}] - [g \text{ Exempt Compounds}])}{([liter \text{ Material}] - [liter \text{ Water}] - [liter \text{ Exempt Compounds}])}$$

5.3 Uncertainty of the Test Method

The relative standard deviation of the overall analysis is 10%. The expanded uncertainty U_m equals 2 x RSD. For further information please visit www.eurofins.dk/uncertainty.