

P795

SEAL'N'FLEX FC PREMIUM

ADVANCED DURABLE FLEXIBLE BUILDING AND CONSTRUCTION SEALANT

TECHNICAL DATA SHEET

BENEFITS

- 3-in-1 sealant (vertical & horizontal) & adhesive
- Bubble free curing
- Excellent toolability
- Suitable for wider joints (up to 50mm)
- Permanently elastic
- High mechanical resistance
- No shrinkage
- Adheres perfectly without primer on most, even damp, surfaces

PRODUCT DESCRIPTION

Bostik P795 SEAL'N'FLEX FC PREMIUM is a *New Generation* one component user friendly low MDI fast curing high performance and durable polyurethane sealant. **Bostik P795 SEAL'N'FLEX FC PREMIUM** will **not form bubbles** during its curing process. It has total movement capability of 100% ($\pm 50\%$) for continuous expansion and compression cycles.

APPLICATIONS

Bostik P795 SEAL'N'FLEX FC PREMIUM is specifically developed as a universal sealant for sealing construction & expansion joints, joints in pedestrian walkways and suitable for roofing applications, complies NFP 85-610. **Bostik P795 SEAL'N'FLEX FC PREMIUM** is also bonding adhesive for light fixtures and accessories.

DIRECTIONS OF USE

A joint with the correct dimensions is able to absorb movements between building materials. The joint depth should always be in the correct relationship of the joint width. A general rule is the ratio of joint depth to the width of the joint with a joint width up to 10mm is 1:1, with a minimum of 5mm in width and depth. For joints wider than 10mm, the depth is the width divided by 3 plus 6mm.

LIMITATIONS

- Not suitable for PE, PP, PC, PMMA, PTFE, soft plastics, neoprene and bituminous substrates
- Not suitable in combination with chlorides (pools)



TECHNICAL DATA

100% modulus	ASTM D 412, BTM-U023	>1.0 N/mm ²
Application temperature		+5°C to + 40°C
Base		New Generation PU
Curing time	@ +23°C/50% RH	3 mm/24 hours
Density	ISO 1183-1	1.30 g/ml
Elongation at break	ASTM D 412, BTM-U023	> 900%
Flow	ISO 7390	0 mm
Movement Capability	ASTM C 719	$\pm 50\%$
Shore A hardness	BTM-P003, ASTM C 661-15	37 - 44
Shrinkage	ISO 10563	< 10%
Skin formation	ASTM C 676	50 min.
Temperature resistance		-30°C to +80°C
Tensile strength	ASTM D 412, BTM-U023	1.69 N/mm ²

These values are typical properties and may vary +/-3%

SURFACE PREPARATIONS AND FINISHING

Application temperature + 5°C to + 40°C (applies to environment and substrates). All substrates must be solid, clean, dry, and free of grease and dust. Clean substrates with Bostik Cleaner. **Bostik P795 SEAL'N'FLEX FC PREMIUM** adheres perfectly without the use of a primer to most porous & non-porous substrates. In order to achieve maximum adhesion especially to concrete in which dust can't be avoided, Bostik Primer (or Bostik N49) is highly

recommended. Always test adhesion prior to application. Use Bostik Finisher to smooth the joint.

PAINTABILITY

Bostik P795 SEAL'N'FLEX FC PREMIUM is paintable with water based and most 2-component paints. Synthetic paints can dry slower. We recommend testing compatibility with paint prior to application.

CLEANING

Uncured material and tools can be cleaned by using Bostik Cleaner. Cured material can only be mechanically removed. Hands can be cleaned with Bostik Wipes.

COLOUR(S)

- White
- Off-white
- Light-grey
- Mid-grey
- Dark-grey
- Black

PACKAGING

- 300 ml Cartridge, 12 per box
- 600 ml Sausages, 12 per box

For product specifications, please refer to the Online Product Detail Page

SHELF LIFE

In unopened original packaging between + 5°C and + 25°C, shelf life is up to 15 months from production date, stored in a dry place.

HEALTH & SAFETY

Product Safety Data Sheet must be read and understood before use. These are available on request and via the websites.

CERTIFICATIONS

- F-EXT-INT-CC 25HM
- PW-EXT-INT-CC 25HM
- SNJF 25E
- ASTM C-920 as Type S, Grade NS, Class 50, use T, G, A, M & O as external & traffic joint sealant
- ISEGA (direct food contact)
- A+ French VOC Regulation

The information and recommendations relating to the application and end-use of the product are given in good faith and based on tests which we believe to be reliable. Differing materials, substrates, environments, site conditions, and product storage, handling and application may affect results. However, no warranty in respect of merchantability or fitness for a particular purpose, nor any liability arising out of any legal relationship, whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. No guarantee of their accuracy can be made because of the great range of field conditions and variation encountered in raw materials, manufacturing equipment and methods. Thus, the products are sold with limited warranty only, and on condition that purchasers will make their own tests to determine the suitability of the product for their particular purposes. Under no circumstances will Bostik be liable to anyone except for replacement of the products or refund of the purchase price.

Bostik S.A

420 rue d'Estienne d'Orves, 92700, Colombes, France
Tel.: +31 (0)162 491 000
www.bostik.com

BOSTIK SMART SUPPORT

Smart help digital
Bostik.com/

Smart help
+31 (0)162 491 000

